

Is 5522 Fire Hose

Page 1: Material Specifications and Pressure Testing

IS 5522 specifies the requirements for synthetic fiber jacketed rubber-lined fire fighting delivery hoses. The hose must consist of a circular woven reinforcement jacket made of high-tenacity synthetic yarns (polyester or nylon) and an internal lining of vulcanized natural or synthetic rubber.

The hose must have a smooth internal finish to minimize friction loss. Hoses must undergo pressure tests: proof pressure of 21 kg/cm², working pressure of 15 kg/cm², and a minimum burst pressure of 35 kg/cm². The hose must not show any leakage, weeping, or yarn breakage during testing.