

Appendix A. Complete LA-ICPMS data for sphalerite

1. Hetaoping

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
HTP27.1	2844	35051	109	0.03	9	0.87	2.61	<0.26	20.04	5.9	4170	0.015	0.11	0.50	<0.06	<0.008	0.006	1.9	0.012	<0.002
HTP27.2	2839	37358	108	<0.04	8	0.43	2.6	<0.19	20.42	5.1	4244	0.011	0.11	1.10	<0.10	0.008	<0.002	2.8	0.020	<0.002
HTP27.3	2818	37927	111	0.05	7	0.49	2.83	<0.21	14.24	4.5	4314	0.01	0.1	0.00	<0.08	<0.006	<0.003	0.2	0.015	<0.002
HTP27.4	2819	39021	111	0.04	9	0.33	2.64	<0.21	11.55	6	4328	0.013	0.1	3.30	<0.07	0.010	<0.003	6.4	0.016	<0.002
HTP27.5	2822	38631	110	<0.04	13	1.43	2.75	<0.18	32.28	6	4242	0.009	0.11	1.60	<0.10	0.014	<0.003	3.4	0.015	<0.002
HTP27.6	2830	38555	112	0.04	16	1.02	2.7	<0.25	29.1	8	4237	0.007	0.1	5.80	<0.10	0.013	0.003	6.6	0.015	0.002
HTP27.7	2819	38187	110	0.04	9	0.58	2.8	<0.24	19.19	5.5	4259	0.007	0.09	2.70	<0.07	<0.008	<0.003	5	0.013	<0.001
HTP27.8	2866	32878	109	<0.03	8	1.84	2.64	<0.22	29.4	5	4128	0.009	0.12	0.30	0.03	<0.007	<0.003	2	0.010	0.001
174HTP1	5438	102151	71	<0.25	33	0.1	3.11	<1.92	18.86	4.7	5532	0.158	<0.23	0.30	<0.52	<0.071	<0.022	0.9	<0.055	<0.002
174HTP2	4339	114483	84	0.09	8337	0.07	3.26	<1.61	7.65	25.2	6995	0.179	0.13	21.50	<0.45	<0.070	0.062	63	0.931	<0.015
174HTP3	5578	97556	83	<0.03	41	0.06	3.03	0.23	17.85	7.5	5892	0.104	0.07	4.10	<0.08	0.020	0.006	6.6	0.260	<0.002
174HTP4	5366	92512	80	<0.04	12	0.46	2.76	<0.22	33.43	6.5	5486	0.09	0.09	1.50	<0.13	0.015	0.004	3.2	0.115	<0.002
174HTP5	4840	102774	72	<0.03	2853	0.08	3.15	0.28	11.79	14.5	5756	0.136	0.11	10.50	<0.07	0.091	0.075	56	0.675	<0.002
174HTP6	5232	103733	70	<0.04	2180	0.08	3.26	<0.19	10.21	15.9	5989	0.153	0.06	15.20	<0.08	0.107	0.036	22	0.847	<0.002
174HTP7	4359	92567	71	<0.04	533	0.14	2.85	<0.26	9.83	16	5420	0.133	0.09	13.40	<0.10	0.036	0.034	18	0.765	<0.002
174HTP8	5766	96416	94	<0.02	35	0.28	2.85	<0.21	22.72	11.5	5705	0.119	0.11	7.90	<0.09	0.042	0.010	17	0.619	<0.002
163HTP1	1295	21160	442	0.47	12	0.32	3.1	<3.49	85.89	8	4091	0.002	<0.23	6.40	<0.63	<0.051	<0.018	78	7.226	<0.014
163HTP2	1241	20311	428	0.20	9	0.45	2.62	<0.44	27.56	7.6	4237	0.005	0.08	3.20	<0.10	0.073	0.002	364	4.981	<0.002
163HTP3	1247	20417	443	0.21	6	0.74	2.78	<0.39	79.96	5.4	4179	0.004	0.09	0.50	<0.04	<0.010	<0.003	1.5	0.440	<0.002
163HTP4	1272	20852	428	0.20	9	0.35	2.51	<0.37	57.15	6.1	4218	0.004	0.07	2.90	<0.09	0.012	0.004	7.2	3.043	0.008
163HTP5	1260	20684	431	0.19	6	0.6	2.79	<0.42	25.37	4.9	4192	0.003	0.09	0.30	<0.07	<0.009	<0.003	60	0.828	<0.002
163HTP6	1296	21359	473	0.18	7	0.85	2.88	0.36	55.62	5	4004	0.002	0.07	0.80	<0.10	<0.007	<0.003	2.1	0.755	<0.002
163HTP7	1325	21367	473	0.20	7	0.87	2.95	<0.37	73.39	4.4	4092	0.002	0.10	0.10	0.05	<0.006	<0.003	0.5	0.102	<0.002
163HTP8	1250	20646	473	0.15	778	0.35	2.73	<0.51	40.29	10.1	3991	0.001	0.10	6.60	<0.11	0.111	0.003	169	7.980	<0.002

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
HTP27.1	0.09	1.70	0.01	0.03	0.11	0.01	0.15	0.26	0.40	0.009	0.07	0.002	0.02	0.01	0.06	0.01	0.003	0.003	0.01	0.002
HTP27.2	0.08	1.42	0.00	0.04	0.08	0.01	0.21	0.19	0.33	0.006	0.08	0.001	0.02	0.01	0.10	0.01	0.002	0.004	0.01	0.002
HTP27.3	0.10	1.52	0.01	0.03	0.11	0.01	0.18	0.21	0.37	0.005	0.04	0.003	0.03	0.01	0.08	0.01	0.003	0.005	0.01	0.002
HTP27.4	0.06	1.65	0.01	0.03	0.11	0.01	0.20	0.21	0.32	0.006	0.04	0.002	0.03	0.01	0.07	0.01	0.003	0.003	0.01	0.002
HTP27.5	0.07	1.24	0.01	0.04	0.10	0.01	0.19	0.18	0.29	0.009	0.03	0.002	0.03	0.01	0.10	0.01	0.003	0.003	0.01	0.002
HTP27.6	0.07	1.26	0.01	0.03	0.09	0.01	0.15	0.25	0.34	0.005	0.05	0.002	0.03	0.01	0.10	0.01	0.002	0.004	0.01	0.002
HTP27.7	0.08	1.36	0.01	0.02	0.10	0.01	0.21	0.24	0.33	0.014	0.05	0.001	0.03	0.01	0.07	0.01	0.003	0.003	0.01	0.001
HTP27.8	0.08	1.50	0.01	0.03	0.13	0.01	0.23	0.22	0.30	0.009	0.05	0.002	0.02	0.01	0.08	0.01	0.003	0.005	0.01	0.001
174HTP1	0.77	9.78	0.04	0.25	0.92	0.08	1.96	1.92	2.38	0.075	0.44	0.016	0.23	0.07	0.52	0.07	0.022	0.034	0.05	0.020
174HTP2	0.64	11.61	0.05	0.27	0.90	0.07	1.53	1.61	3.09	0.091	0.48	0.018	0.19	0.07	0.45	0.07	0.015	0.036	0.06	0.015
174HTP3	0.09	1.40	0.01	0.03	0.13	0.01	0.19	0.22	0.39	0.007	0.04	0.002	0.03	0.01	0.08	0.01	0.003	0.005	0.01	0.002
174HTP4	0.10	1.75	0.01	0.04	0.12	0.01	0.20	0.22	0.42	0.012	0.04	0.001	0.03	0.01	0.13	0.01	0.002	0.004	0.01	0.002
174HTP5	0.09	1.26	0.01	0.03	0.10	0.01	0.23	0.25	0.32	0.006	0.05	0.002	0.03	0.01	0.07	0.01	0.002	0.004	0.01	0.002
174HTP6	0.09	2.34	0.01	0.04	0.10	0.01	0.19	0.19	0.40	0.011	0.08	0.002	0.03	0.02	0.08	0.01	0.003	0.004	0.01	0.002

174HTP7	0.09	1.60	0.01	0.04	0.12	0.01	0.24	0.26	0.42	0.007	0.08	0.003	0.03	0.01	0.10	0.01	0.003	0.006	0.01	0.002
174HTP8	0.10	1.35	0.01	0.02	0.10	0.01	0.21	0.21	0.33	0.003	0.03	0.002	0.02	0.01	0.09	0.01	0.002	0.006	0.01	0.002
163HTP1	0.70	11.13	0.05	0.29	0.94	0.05	1.39	3.49	2.62	0.084	0.65	0.017	0.23	0.10	0.63	0.05	0.018	0.044	0.05	0.014
163HTP2	0.07	1.46	0.01	0.03	0.08	0.01	0.22	0.44	0.38	0.009	0.05	0.002	0.02	0.01	0.10	0.01	0.002	0.003	0.01	0.002
163HTP3	0.08	1.25	0.01	0.04	0.12	0.01	0.20	0.39	0.34	0.005	0.05	0.002	0.02	0.01	0.04	0.01	0.003	0.004	0.01	0.002
163HTP4	0.09	1.05	0.01	0.03	0.07	0.01	0.23	0.37	0.27	0.003	0.04	0.003	0.03	0.01	0.09	0.01	0.002	0.005	0.01	0.001
163HTP5	0.08	1.40	0.01	0.05	0.10	0.01	0.15	0.42	0.36	0.007	0.03	0.002	0.03	0.01	0.07	0.01	0.003	0.006	0.01	0.002
163HTP6	0.08	1.88	0.01	0.04	0.10	0.01	0.17	0.31	0.32	0.010	0.05	0.004	0.03	0.01	0.10	0.01	0.003	0.005	0.01	0.002
163HTP7	0.11	1.71	0.01	0.03	0.11	0.01	0.20	0.37	0.33	0.012	0.06	0.002	0.02	0.01	0.05	0.01	0.003	0.005	0.01	0.002
163HTP8	0.08	1.63	0.01	0.03	0.09	0.01	0.23	0.51	0.39	0.008	0.06	0.004	0.03	0.01	0.11	0.01	0.003	0.006	0.01	0.002

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
HTP27.1	5	5	5	74	5	6	6	360	5	5	4	14	14	6	63	463	40	5	33	129
HTP27.2	5	5	5	1154	5	7	6	69	5	5	4	15	17	6	294	58	166	5	18	109
HTP27.3	5	5	5	43	5	7	6	454	6	5	4	20	19	28	138	123	651	10	21	747
HTP27.4	5	5	5	57	5	8	6	192	6	5	4	16	18	6	196	41	156	5	24	148
HTP27.5	5	5	5	88	5	7	6	193	5	5	4	20	17	6	241	28	168	5	23	513
HTP27.6	5	5	5	60	5	7	6	150	5	5	4	21	20	5	189	48	79	5	21	47
HTP27.7	5	5	5	48	5	7	6	630	5	5	4	19	22	5	64	87	161	5	30	109
HTP27.8	5	5	5	162	5	6	6	372	5	5	4	21	14	7	118	399	179	6	34	45
174HTP1	8	8	8	183	13	47	25	374	14	8	7	13	114	18	376	810	195	10	123	73
174HTP2	8	8	8	191	8	69	20	1099	34	7	7	14	99	7	85	134	28	21	9	469
174HTP3	7	7	8	116	14	18	8	53	8	7	7	9	25	7	191	31	50	8	8	159
174HTP4	7	7	8	107	8	9	8	1726	7	8	7	9	22	13	880	44	57	13	12	116
174HTP5	8	7	8	96	8	14	8	47	8	7	7	8	17	7	404	14	10	17	8	630
174HTP6	7	8	7	263	9	15	8	74	9	8	7	8	33	8	51	13	13	8	8	76
174HTP7	8	7	7	201	11	19	9	148	9	7	7	9	30	8	148	29	20	8	8	565
174HTP8	7	8	8	221	10	10	8	65	8	7	7	9	17	7	301	21	22	7	7	86
163HTP1	7	7	7	44	10	17	19	268	9	8	7	407	228	13	163	409	214	34	12	69
163HTP2	7	7	7	17	7	9	8	361	7	7	7	29	22	8	233	14	137	20	10	210
163HTP3	7	7	7	17	7	8	8	98	6	7	7	42	19	10	73	111	137	8	8	168
163HTP4	7	7	7	16	7	9	8	69	6	7	7	45	26	7	103	33	53	7	7	24
163HTP5	7	7	7	23	7	9	8	103	7	7	7	52	21	10	111	252	173	38	23	188
163HTP6	7	7	7	20	7	8	8	49	7	7	7	105	32	8	86	431	5783	8	7	189
163HTP7	7	7	7	19	8	8	8	1608	6	7	7	85	18	10	55	283	95	10	9	268
163HTP8	8	8	8	24	99	10	9	430	8	8	8	228	20	8	69	13	103	22	8	76

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
HTP27.1	1	1	1	24	2	2	2	4	3	1	1	10	5	5	21	24	15	2	7	21
HTP27.2	1	1	1	27	2	4	2	4	3	2	1	12	6	5	23	19	31	3	7	24
HTP27.3	1	1	1	21	2	4	2	4	4	2	1	11	6	14	25	20	29	8	7	20
HTP27.4	1	1	1	25	2	4	2	4	4	1	1	11	6	3	25	18	28	2	7	22
HTP27.5	1	1	1	42	2	3	1	4	3	2	1	14	6	4	19	14	29	2	7	20
HTP27.6	1	1	1	20	2	3	2	4	2	1	1	14	7	2	26	15	17	1	7	20

HTP27.7	1	1	1	24	2	3	2	5	3	1	1	17	6	2	24	18	23	1	9	28
HTP27.8	2	1	1	28	2	2	2	4	2	2	1	15	5	5	24	30	24	3	7	19
174HTP1	2	2	2	38	10	13	2	4	7	4	1	9	9	10	34	22	20	5	9	29
174HTP2	2	2	2	27	3	18	2	4	10	2	1	10	8	2	29	18	15	20	4	24
174HTP3	1	1	2	28	12	10	2	4	4	1	1	5	7	2	27	17	15	2	3	24
174HTP4	1	1	1	29	2	4	2	4	3	3	1	5	6	10	32	18	19	10	8	25
174HTP5	2	1	2	23	4	9	2	4	4	1	1	3	5	3	36	10	6	15	4	25
174HTP6	1	1	1	29	5	9	2	4	4	3	1	4	7	3	20	7	9	2	4	30
174HTP7	2	1	1	45	9	15	3	6	5	2	1	5	12	5	48	20	16	2	4	36
174HTP8	1	1	1	38	7	4	2	4	3	1	1	4	7	1	27	12	12	1	2	33
163HTP1	2	2	2	18	5	11	2	2	5	5	2	26	8	11	29	22	27	33	9	19
163HTP2	1	1	1	11	2	4	2	3	2	2	1	17	6	5	27	10	21	19	8	22
163HTP3	1	1	1	10	2	3	1	2	2	2	1	16	5	7	30	22	21	5	4	23
163HTP4	2	2	1	10	3	5	2	2	2	2	1	16	6	2	22	18	23	2	2	21
163HTP5	1	1	1	14	3	3	2	3	3	2	1	22	7	7	28	27	33	37	22	27
163HTP6	1	1	1	12	2	3	2	3	2	2	1	22	7	5	16	25	23	4	3	25
163HTP7	1	1	1	13	4	3	2	3	2	2	1	21	6	7	24	28	22	8	4	20
163HTP8	3	3	3	16	98	6	3	3	4	3	3	18	6	4	32	8	23	21	4	23

2. Luziyuan

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
47LZY1	1251	43693	436	<0.16	58	0.22	3.3	<1.28	95.1	7.6	2233	0.112	0.24	26.1	<0.43	0.47	0.055	1545	55.3	<0.012
47LZY2	1241	44682	461	0.23	194	0.19	2.9	<1.39	109.4	4.4	2290	0.106	0.03	6.1	<0.43	0.19	<0.017	62.5	11.5	<0.014
47LZY3	1392	43179	435	0.32	5	0.26	2.82	<0.18	116.9	3.8	2299	0.117	0.09	0.9	<0.07	0.02	<0.003	1.1	2.3	<0.001
47LZY4	1553	44123	440	0.32	8	0.22	2.69	<0.17	122	3.9	2323	0.11	0.1	0.3	<0.08	0.02	<0.003	0.6	2.3	0.139
47LZY5	1252	44138	420	0.23	32	0.16	2.82	<0.18	136.5	4.5	2393	0.117	0.12	5.6	<0.09	0.13	0.043	1173.8	22.9	<0.002
47LZY6	2143	44768	427	0.47	11	1.03	2.9	<0.25	123.3	3.8	2168	0.11	0.14	4	0.09	0.05	0.158	5	3.0	0.003
47LZY7	1431	43310	429	0.19	13	0.26	2.7	<0.20	124.6	4.4	2235	0.111	0.13	6.6	<0.10	0.10	0.015	10.9	7.3	<0.002
47LZY8	1430	43040	427	0.20	13	0.21	2.77	<0.20	112.3	4.6	2303	0.109	0.1	6.3	<0.06	0.12	0.002	13.9	13.3	<0.002
29LZY1	601	105858	257	<0.47	111	0.62	2.8	<1.48	<2.85	5.4	2091	0.06	1.23	4.1	<0.40	<0.06	0.018	2.5	<0.06	<0.021
29LZY2	684	97175	228	0.65	16	0.58	2.96	<2.34	2.57	4.4	2050	0.047	0.14	<0.10	<0.62	<0.06	<0.021	0.6	<0.07	<0.013
29LZY3	658	99246	313	0.24	56	0.54	3.19	<1.84	1.27	5.3	2068	0.023	0.14	0.7	<0.69	<0.04	0.025	0.9	<0.06	0.011
29LZY4	635	93164	220	0.72	67	0.67	2.57	<1.71	<2.21	6.3	2004	0.069	9.11	8.1	<0.80	0.06	0.032	3.4	<0.06	<0.018
29LZY5	737	105621	246	<0.25	40	0.47	3.73	<2.00	<2.76	5.3	2020	0.024	0.04	2.9	<0.71	<0.05	<0.026	2.6	<0.07	<0.011
29LZY6	630	94392	245	1.00	399	0.48	3.21	<2.02	1.18	14.1	1795	0.071	4.7	19.1	<0.73	<0.08	0.121	30.8	0.1	<0.017
29LZY7	642	98574	212	0.38	873	0.52	3.63	<1.85	<2.54	17.2	2017	0.012	0.52	21.5	<0.50	0.13	<0.025	18.8	0.1	<0.019
29LZY8	645	99906	231	1.16	472	0.59	2.53	4.74	1.62	10.7	1688	0.053	8.1	19.3	<0.88	0.05	0.228	63.7	0.4	<0.019
LZY61.1	1105	56786	413	0.35	12	0.12	2.93	<0.34	13.96	4.7	2160	0.007	0.12	0.6	0.05	0.02	<0.003	1.6	0.4	<0.001
LZY61.2	1085	57485	411	0.28	17	0.12	2.93	<0.30	13.36	4.8	2181	0.01	0.15	1.2	<0.06	0.05	<0.003	3.4	0.8	<0.003
LZY61.3	1021	56723	406	0.31	10	0.11	3.15	0.41	14.2	4.4	2184	0.005	0.09	0.9	<0.05	0.03	0.006	2.6	0.4	0.001
LZY61.4	1036	55373	410	0.32	8	0.11	3.06	<0.33	18.16	4.2	2099	0.007	0.1	<0.01	<0.09	0.01	<0.004	0	<0.01	<0.002
LZY61.5	996	55462	409	0.25	15	0.11	2.98	<0.34	16.88	4.7	2111	0.008	0.15	0.5	<0.09	0.02	<0.004	2.2	0.4	<0.002
LZY61.6	1008	60554	413	0.31	16	0.12	3.13	<0.36	21.49	4.4	2362	0.008	0.13	1.3	<0.07	0.04	0.011	2.9	0.7	<0.002
LZY61.7	1223	57473	412	0.24	20	0.16	3.08	<0.36	18.18	5.4	2220	0.01	0.17	3.5	<0.07	0.04	<0.004	8.4	1.1	<0.002
LZY61.8	1270	58588	413	0.35	13	0.13	2.93	<0.32	12.17	4.7	2237	0.006	0.15	1.9	<0.08	0.11	0.005	5.4	1.0	<0.002

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
47LZY1	0.605	8.597	0.046	0.165	0.577	0.054	1.159	1.281	2.457	0.021	0.341	0.017	0.143	0.058	0.426	0.04	0.019	0.031	0.039	0.012
47LZY2	0.505	10.101	0.047	0.200	0.799	0.064	1.241	1.385	2.150	0.041	0.208	0.015	0.219	0.075	0.434	0.06	0.017	0.022	0.043	0.014
47LZY3	0.079	1.016	0.004	0.053	0.087	0.008	0.202	0.181	0.352	0.006	0.045	0.002	0.027	0.010	0.065	0.01	0.003	0.004	0.005	0.001
47LZY4	0.102	1.075	0.008	0.030	0.100	0.012	0.192	0.167	0.332	0.007	0.040	0.001	0.019	0.013	0.079	0.00	0.003	0.003	0.006	0.002
47LZY5	0.079	1.438	0.008	0.027	0.117	0.015	0.216	0.182	0.386	0.010	0.060	0.002	0.023	0.011	0.092	0.01	0.004	0.004	0.006	0.002
47LZY6	0.106	1.669	0.004	0.033	0.116	0.017	0.270	0.252	0.358	0.019	0.057	0.003	0.021	0.008	0.048	0.01	0.004	0.007	0.006	0.002
47LZY7	0.075	1.509	0.006	0.039	0.118	0.010	0.171	0.199	0.289	0.007	0.061	0.002	0.024	0.010	0.099	0.01	0.002	0.003	0.006	0.002
47LZY8	0.068	1.094	0.008	0.040	0.096	0.009	0.191	0.232	0.367	0.006	0.051	0.002	0.032	0.006	0.062	0.01	0.002	0.006	0.007	0.002
29LZY1	0.657	11.234	0.058	0.469	0.876	0.076	1.432	1.476	2.848	0.050	0.315	0.012	0.203	0.066	0.400	0.06	0.017	0.038	0.057	0.021
29LZY2	0.636	11.517	0.041	0.242	0.707	0.095	1.413	2.341	2.312	0.043	0.309	0.018	0.273	0.095	0.622	0.06	0.021	0.035	0.068	0.013
29LZY3	0.724	11.345	0.063	0.200	0.700	0.092	1.415	1.835	2.212	0.067	0.304	0.019	0.224	0.084	0.691	0.04	0.017	0.034	0.064	0.009
29LZY4	0.671	12.730	0.058	0.180	0.766	0.077	1.757	1.713	2.206	0.066	0.528	0.017	0.208	0.075	0.801	0.05	0.018	0.030	0.058	0.018
29LZY5	0.671	12.154	0.066	0.248	0.828	0.107	1.410	2.004	2.760	0.075	0.310	0.017	0.248	0.089	0.709	0.05	0.026	0.048	0.073	0.011
29LZY6	0.721	11.748	0.043	0.213	0.848	0.092	1.693	2.019	2.514	0.080	0.323	0.020	0.237	0.105	0.729	0.08	0.023	0.041	0.061	0.017
29LZY7	0.475	11.200	0.031	0.252	0.758	0.127	1.380	1.847	2.543	0.067	0.409	0.018	0.214	0.090	0.503	0.06	0.025	0.032	0.065	0.019
29LZY8	0.565	12.818	0.039	0.221	0.836	0.091	1.687	2.221	2.407	0.066	0.336	0.019	0.305	0.074	0.881	0.05	0.021	0.029	0.068	0.019
LZY61.1	0.093	1.502	0.007	0.044	0.120	0.011	0.184	0.337	0.337	0.008	0.041	0.002	0.022	0.011	0.042	0.01	0.003	0.005	0.006	0.001
LZY61.2	0.100	1.504	0.008	0.035	0.115	0.009	0.188	0.300	0.313	0.008	0.042	0.002	0.029	0.012	0.060	0.01	0.003	0.006	0.006	0.003
LZY61.3	0.091	2.024	0.010	0.039	0.119	0.009	0.177	0.343	0.321	0.013	0.048	0.003	0.029	0.013	0.052	0.01	0.002	0.004	0.008	0.001
LZY61.4	0.105	1.631	0.007	0.050	0.108	0.008	0.188	0.332	0.302	0.009	0.061	0.002	0.030	0.009	0.095	0.01	0.004	0.005	0.008	0.002
LZY61.5	0.094	1.612	0.009	0.035	0.099	0.014	0.219	0.344	0.458	0.006	0.047	0.002	0.019	0.011	0.091	0.01	0.004	0.006	0.008	0.002
LZY61.6	0.073	1.560	0.006	0.043	0.110	0.012	0.188	0.358	0.343	0.009	0.051	0.003	0.025	0.013	0.068	0.01	0.003	0.005	0.006	0.002
LZY61.7	0.103	1.592	0.006	0.038	0.086	0.012	0.215	0.359	0.296	0.007	0.059	0.001	0.024	0.009	0.074	0.01	0.004	0.005	0.007	0.002
LZY61.8	0.089	1.574	0.005	0.029	0.090	0.017	0.196	0.324	0.335	0.010	0.047	0.002	0.024	0.015	0.080	0.01	0.003	0.004	0.008	0.002

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
47LZY1	7	7	7	169	8	20	16	107	7	7	6	15	39	7	63	15	35	13	7	297
47LZY2	7	7	7	69	13	23	18	589	7	7	6	15	411	7	436	23	248	12	7	206
47LZY3	7	7	7	15	7	9	7	163	6	6	6	8	20	7	73	25	154	6	6	15265
47LZY4	7	7	7	13	7	9	7	82	6	6	6	8	16	7	641	23	193	7	6	50
47LZY5	6	7	7	16	8	11	7	93	6	6	6	8	16	7	131	14	19	19	14	270
47LZY6	8	7	7	14	18	12	8	288	6	7	6	8	14	12	34	21	13	18	10	34
47LZY7	7	7	7	18	7	9	7	197	6	6	6	8	16	6	144	13	20	6	6	139
47LZY8	7	7	7	20	7	9	7	228	6	6	6	8	22	6	69	13	104	7	7	18136
29LZY1	7	7	7	231	8	14	21	248	122	8	7	23	15	18	221	120	91	20	193	129
29LZY2	7	7	7	31	8	16	20	721	68	8	7	30	113	317	366	234	102	48	150	402
29LZY3	7	7	8	62	12	17	19	221	140	8	7	57	99	12	720	104	62	10	166	40
29LZY4	7	7	7	24	8	13	26	3203	4129	7	6	23	8	7	109	51	56	9	277	20759
29LZY5	7	7	7	711	8	21	18	470	330	8	6	52	376	8	83	117	109	8	835	804
29LZY6	7	7	7	21	8	16	21	99	155	7	7	21	9	7	263	332	22	11	61	489
29LZY7	7	7	7	50	9	17	17	93	100	8	7	98	28	7	224	30	93	7	63	213
29LZY8	7	7	7	21	7	15	28	26	113	7	6	25	8	7	1283	62	16	8	22	158
LZY61.1	9	9	9	15	9	13	9	564	9	9	8	28	17	10	48	35	196	9	9	1504
LZY61.2	9	9	9	16	9	13	9	200	9	9	8	21	17	10	144	19	129	9	9	642
LZY61.3	9	9	9	16	9	13	9	45	9	9	8	37	23	9	150	23	43	9	9	58

LZY61.4	9	9	9	16	9	13	9	591	9	9	8	31	23	47	131	79	77	12	15	406
LZY61.5	9	9	9	17	9	14	10	362	9	9	8	22	14	11	2335	34	916	10	9	138
LZY61.6	9	9	9	16	11	13	9	252	8	9	8	27	17	9	101	24	29	9	9	147
LZY61.7	9	9	9	19	9	13	9	90	8	9	8	19	14	9	123	18	706	9	9	297
LZY61.8	9	9	9	16	9	14	9	351	9	9	8	28	16	9	114	14	55	9	9	74

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
47LZY1	2	2	2	31	5	11	2	4	4	3	1	9	7	2	21	10	17	12	4	24
47LZY2	2	2	2	25	11	10	2	4	3	4	1	11	8	3	30	10	23	11	2	23
47LZY3	1	1	1	9	2	4	2	4	2	2	1	5	6	3	21	14	23	2	1	30
47LZY4	1	1	1	9	2	4	2	4	2	2	1	4	6	4	27	14	26	2	1	49
47LZY5	1	1	1	12	5	6	2	5	2	2	1	4	7	3	21	9	15	18	12	25
47LZY6	5	2	2	11	16	9	2	4	2	2	2	5	6	11	23	13	11	17	8	16
47LZY7	2	1	1	10	2	5	2	4	2	2	1	4	6	2	24	7	12	1	2	22
47LZY8	1	1	1	13	2	5	2	4	2	2	1	4	6	2	22	7	20	4	3	23
29LZY1	2	2	2	24	5	8	2	4	12	4	2	17	6	17	38	27	21	19	8	19
29LZY2	2	1	1	16	4	9	2	4	12	3	1	17	8	20	30	22	31	45	7	20
29LZY3	2	2	2	25	10	10	2	4	13	4	1	19	7	8	24	22	18	7	9	20
29LZY4	1	2	2	16	4	8	2	4	12	3	2	15	3	3	28	19	19	6	9	23
29LZY5	2	2	2	61	4	12	3	6	22	4	1	26	12	5	49	28	38	4	12	52
29LZY6	2	2	3	14	4	9	2	4	11	3	2	12	4	3	29	19	11	8	7	23
29LZY7	2	2	2	20	7	7	2	4	13	5	2	22	7	3	37	15	26	3	7	26
29LZY8	2	2	2	15	2	9	2	3	13	3	1	14	4	3	30	20	11	5	13	24
LZY61.1	1	1	2	9	2	7	2	3	4	2	1	15	6	4	27	12	22	2	3	31
LZY61.2	1	1	1	11	2	7	2	3	4	1	1	14	6	5	36	11	21	2	4	20
LZY61.3	1	1	1	10	2	7	1	3	3	2	1	14	6	3	32	11	20	1	3	19
LZY61.4	1	1	1	8	2	7	2	3	3	2	1	19	7	19	31	20	29	6	6	22
LZY61.5	1	1	1	11	2	6	2	3	3	2	1	15	6	6	30	15	21	5	3	23
LZY61.6	1	1	2	10	6	7	2	3	3	2	1	13	6	3	26	11	15	1	2	22
LZY61.7	1	1	1	12	2	6	2	3	3	1	1	14	5	2	26	10	18	2	3	22
LZY61.8	1	1	1	11	2	7	2	3	3	2	1	16	6	4	26	9	16	3	3	24

3.Dabaoshan

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1DBS1	1982	110512	0.21	<0.04	172	35.69	3.01	<0.27	0.52	19.6	5633	131	1.4	1.4	<0.11	0.010	0.003	2.3	0.034	<0.002
1DBS2	2140	109212	0.3	<0.04	110	31.35	2.95	<0.22	0.55	14.4	5536	130	1.9	0.6	<0.11	<0.010	<0.002	1.4	0.021	<0.002
1DBS3	1695	108962	0.1	<0.04	188	63.46	2.95	<0.17	<0.41	24.6	5636	113	6.6	1.2	<0.10	<0.010	0.005	2.5	0.017	<0.002
1DBS4	2133	113814	0.21	<0.03	169	33.96	3.02	<0.20	0.52	24.1	5563	115	1.9	1.1	<0.10	0.023	0.005	3.3	0.023	2.27
1DBS5	2171	113487	0.23	<0.04	134	65.78	3.08	<0.26	0.67	12.5	5532	111	5.2	0.2	<0.14	0.013	<0.003	1	0.013	<0.002
1DBS6	1654	107715	0.02	0.20	117	32.38	3.62	<2.08	0.38	24.7	5561	119	1.5	10.2	<0.56	<0.062	<0.024	487	0.908	<0.013
1DBS7	2025	114283	0.41	<0.27	191	19.89	2.96	<2.08	4.07	21.5	5459	118	2.4	1.5	<0.60	<0.055	<0.026	6.3	<0.051	<0.020
1DBS8	1419	109593	0.16	<0.21	126	28.71	2.79	<1.79	<3.02	14.7	5591	121	2.8	0.3	<0.59	<0.057	0.034	2.5	<0.047	<0.018

1DBS9	1723	112884	0.21	<0.25	160	37	3.41	<1.78	<3.01	31.4	5650	131	6.7	2.3	<0.47	<0.088	0.015	2.4	<0.048	<0.020
1DBS10	675	102897	0.03	<0.28	186	37.64	3.03	<1.53	<2.52	32.1	5645	132	24.2	11.1	<0.70	0.068	0.075	8.1	<0.052	<0.014
2DBS1	2430	120126	4.71	<0.07	446	10.31	3.14	<0.44	0.89	21.9	5878	201	3	0.2	<0.09	0.004	0.008	2.2	<0.009	<0.002
2DBS2	2353	117369	4.32	0.04	333	11.06	3.18	<0.35	0.64	20.8	5706	234	8	2.5	<0.14	<0.009	<0.005	1.7	<0.010	<0.002
2DBS3	2460	121925	6.59	0.05	282	13.66	3.3	<0.41	0.97	10.5	5882	415	18	0.1	<0.06	<0.009	0.006	1	<0.010	<0.002
2DBS4	2430	121013	5.96	0.12	246	13.3	3.41	<0.39	0.65	13.3	5777	348	15	0.5	<0.09	<0.012	<0.003	0.5	0.013	<0.003
2DBS5	2475	125179	5.88	0.37	1576	11.27	3.37	<4.05	<2.93	48.5	4817	322	20	4.3	<0.66	<0.092	<0.044	46	<0.077	<0.019
2DBS6	2326	121782	6.14	<0.30	228	8	4.18	<3.91	<3.01	9.3	4659	339	11	0.3	<0.72	<0.058	<0.025	49	<0.081	<0.021
2DBS7	2067	113228	4.91	<0.24	5803	21.48	2.57	3.17	<3.16	97.7	5689	280	46	8.5	<0.67	<0.038	0.064	17	<0.069	<0.016
2DBS8	2233	118598	4.63	<0.53	2433	13.04	2.97	<3.12	<3.25	27.5	5391	258	32	1	<0.75	<0.077	<0.024	1.4	<0.061	<0.013
DBS6.1	2595	125441	1.26	<0.06	455	28.6	3.33	<0.37	0.7	20.3	5644	260	5	0.4	<0.12	0.015	0.004	1.1	0.012	<0.003
DBS6.2	2223	119439	1.1	0.11	2088	30.29	3.41	<0.32	<0.42	41.3	5748	266	5	2.8	<0.09	0.034	0.010	4.7	0.010	<0.003
DBS6.3	2642	124592	1.15	<0.06	241	10.98	3.51	<0.33	<0.54	41.6	5547	270	8	19	<0.07	<0.012	0.045	3.6	0.011	<0.002
DBS6.4	2440	121251	0.74	<0.07	386	57	3.56	<0.38	<0.36	32	5720	294	20	12.7	<0.10	<0.008	0.116	2.8	0.010	<0.002
DBS6.5	2188	114119	0.53	0.06	968	91.68	3.43	<0.38	<0.52	76	5911	276	47	19	<0.10	<0.011	0.062	10.8	<0.011	<0.003
DBS6.6	2642	124575	2.09	<0.03	229	14.37	3.51	<0.32	0.66	18.5	5773	284	6	0.4	<0.07	<0.010	0.005	0.7	<0.009	<0.003
DBS6.7	2250	116805	0.14	0.04	194	17.65	3.54	<0.43	<0.49	10.2	5951	291	2	0.2	<0.11	<0.009	<0.003	0.9	<0.008	<0.003
DBS6.8	2417	120510	3.67	0.06	3006	20.91	3.29	<0.32	<0.44	198.1	5936	336	11	4	<0.10	0.026	0.144	49	<0.010	<0.002

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1DBS1	0.094	1.821	0.007	0.042	0.086	0.011	0.221	0.274	0.378	0.012	0.045	0.0000	0.0274	0.0142	0.1107	0.0073	0.0029	0.0051	0.0097	0.0025
1DBS2	0.100	1.560	0.005	0.039	0.099	0.013	0.197	0.222	0.440	0.007	0.049	0.0021	0.0290	0.0107	0.1091	0.0104	0.0023	0.0037	0.0071	0.0016
1DBS3	0.112	1.408	0.004	0.035	0.112	0.009	0.195	0.169	0.410	0.008	0.077	0.0022	0.0264	0.0117	0.0991	0.0101	0.0032	0.0050	0.0058	0.0018
1DBS4	0.091	1.316	0.007	0.031	0.114	0.008	0.220	0.204	0.388	0.010	0.034	0.0031	0.0259	0.0135	0.0974	0.0076	0.0021	0.0040	0.0062	0.0019
1DBS5	0.088	1.342	0.006	0.040	0.118	0.011	0.223	0.256	0.357	0.008	0.072	0.0023	0.0274	0.0124	0.1414	0.0088	0.0033	0.0055	0.0079	0.0017
1DBS6	0.738	10.588	0.053	0.151	0.716	0.052	1.714	2.083	2.948	0.048	0.287	0.0140	0.1968	0.0871	0.5574	0.0621	0.0244	0.0248	0.0562	0.0127
1DBS7	0.604	12.223	0.037	0.267	0.735	0.090	1.586	2.076	2.239	0.059	0.370	0.0189	0.1612	0.0808	0.6029	0.0548	0.0259	0.0335	0.0513	0.0197
1DBS8	0.734	12.468	0.055	0.207	1.005	0.055	2.096	1.793	3.018	0.068	0.252	0.0154	0.1417	0.1157	0.5940	0.0572	0.0062	0.0475	0.0473	0.0176
1DBS9	0.801	10.396	0.076	0.248	0.877	0.069	1.546	1.781	3.008	0.065	0.417	0.0154	0.1470	0.0766	0.4690	0.0880	0.0152	0.0225	0.0478	0.0200
1DBS10	0.687	11.815	0.079	0.279	0.785	0.082	1.719	1.532	2.524	0.065	0.577	0.0187	0.1712	0.0662	0.7041	0.0435	0.0142	0.0265	0.0523	0.0136
2DBS1	0.109	1.561	0.010	0.070	0.137	0.011	0.247	0.439	0.579	0.011	0.038	0.0029	0.0293	0.0160	0.0923	0.0087	0.0025	0.0072	0.0095	0.0015
2DBS2	0.095	1.407	0.008	0.041	0.152	0.012	0.270	0.345	0.507	0.010	0.067	0.0021	0.0317	0.0121	0.1445	0.0091	0.0047	0.0056	0.0097	0.0021
2DBS3	0.072	1.868	0.009	0.032	0.122	0.014	0.257	0.409	0.442	0.008	0.051	0.0034	0.0354	0.0127	0.0648	0.0094	0.0023	0.0057	0.0104	0.0023
2DBS4	0.100	1.528	0.007	0.027	0.108	0.013	0.199	0.386	0.507	0.006	0.048	0.0035	0.0345	0.0142	0.0892	0.0116	0.0030	0.0052	0.0097	0.0025
2DBS5	0.783	13.371	0.055	0.128	0.816	0.102	1.851	4.048	2.930	0.085	0.535	0.0168	0.2378	0.1099	0.6643	0.0922	0.0436	0.0361	0.0769	0.0194
2DBS6	0.664	13.551	0.042	0.304	0.850	0.086	1.801	3.909	3.009	0.070	0.559	0.0181	0.2353	0.0855	0.7211	0.0581	0.0248	0.0569	0.0806	0.0212
2DBS7	0.745	11.251	0.044	0.243	0.741	0.096	1.441	3.047	3.155	0.060	0.415	0.0132	0.2233	0.0715	0.6670	0.0384	0.0222	0.0375	0.0691	0.0162
2DBS8	0.875	11.857	0.057	0.531	0.847	0.087	1.600	3.115	3.252	0.084	0.426	0.0183	0.2360	0.1662	0.7472	0.0775	0.0244	0.0512	0.0609	0.0129
DBS6.1	0.110	1.732	0.010	0.056	0.132	0.014	0.278	0.366	0.404	0.009	0.072	0.0026	0.0347	0.0129	0.1188	0.0076	0.0030	0.0068	0.0088	0.0028
DBS6.2	0.108	1.933	0.009	0.026	0.111	0.013	0.263	0.322	0.624	0.014	0.099	0.0035	0.0312	0.0160	0.0942	0.0096	0.0043	0.0069	0.0085	0.0028
DBS6.3	0.113	1.821	0.010	0.055	0.099	0.016	0.287	0.328	0.538	0.013	0.042	0.0029	0.0370	0.0126	0.0743	0.0118	0.0035	0.0076	0.0078	0.0024
DBS6.4	0.085	2.233	0.012	0.069	0.128	0.011	0.266	0.377	0.361	0.012	0.099	0.0029	0.0295	0.0116	0.1002	0.0077	0.0045	0.0031	0.0085	0.0025
DBS6.5	0.127	2.003	0.007	0.053	0.143	0.012	0.223	0.375	0.525	0.012	0.036	0.0033	0.0388	0.0157	0.0975	0.0108	0.0054	0.0055	0.0109	0.0028
DBS6.6	0.095	1.681	0.012	0.032	0.113	0.013	0.244	0.316	0.435	0.013	0.076	0.0024	0.0339	0.0103	0.0657	0.0100	0.0030	0.0053	0.0094	0.0033
DBS6.7	0.104	1.762	0.009	0.032	0.114	0.014	0.298	0.431	0.493	0.009	0.073	0.0033	0.0361	0.0163	0.1091	0.0087	0.0035	0.0053	0.0076	0.0027
DBS6.8	0.147	2.157	0.008	0.048	0.138	0.011	0.257	0.320	0.438	0.008	0.055	0.0028	0.0330	0.0090	0.1033	0.0076	0.0071	0.0071	0.0096	0.0021

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1DBS1	7	7	9	641	8	8	8	2505	56	7	7	7	8	7	181	45	101	8	17	4372
1DBS2	7	8	9	176	7	8	8	63	60	7	7	7	8	8	491	1302	199	7	20	53
1DBS3	7	7	11	1013	7	8	8	65	5797	7	7	7	11	12	782	165	62	10	22	119
1DBS4	7	7	9	249	7	8	8	190	55	7	7	7	8	8	3402	29	42	8	17	31
1DBS5	7	7	9	105	7	9	8	219	41	7	7	7	8	10	1147	43	945	15	34	67
1DBS6	8	8	182	62	7	9	20	204	563	8	7	8	13	11	495	975	159	10	11	169
1DBS7	8	8	14	2010	8	9	23	176	44	8	7	8	10	10	158	192	129	20	177	96
1DBS8	8	8	27	95	8	9	29	328	117	7	7	8	10	31	192	113	27	18	109	348
1DBS9	8	8	27	136	8	9	20	256	496	8	7	8	10	11	238	320	99	13	57	97
1DBS10	8	8	145	214	8	9	23	91	378	15	7	8	9	9	134	44	24	23	178	784
2DBS1	7	7	7	607	10	8	8	260	49	7	7	7	7	13	200	119	35	13	174	66
2DBS2	7	7	7	62	7	8	8	123	60	7	7	7	7	8	96	322	203	8	631	123
2DBS3	7	7	7	46	7	8	8	70	37	7	7	7	7	19	65	182	47	58	73	142
2DBS4	7	7	7	24	7	8	8	56723	56	7	6	7	8	24	2144	98	232	28	40	179
2DBS5	7	7	8	37	7	8	23	851	139	7	7	7	8	10	1110	160	211	15	177	3830
2DBS6	8	8	9	426	8	9	19	178	177	8	7	8	8	25	1425	424	451	14	79	69
2DBS7	8	8	9	184	8	9	25	54	660	8	7	8	9	8	196	42	34	8	132	821
2DBS8	8	8	9	232	12	9	23	569	255	9	8	8	8	13	116	207	152	14	5249	215
DBS6.1	10	10	11	113	11	11	11	88	47	10	9	10	10	12	18136	36	74	11	43	281
DBS6.2	11	11	11	25	12	12	11	56	314	11	10	11	11	11	132	24	44	12	47	161
DBS6.3	10	10	11	85	10	11	11	152	82	11	9	10	11	11	1446	532	15	11	39	17181
DBS6.4	10	10	11	1156	11	11	11	123	1792	10	9	10	10	10	196	70	12	10	45	92
DBS6.5	10	10	11	69	10	11	11	630	122	10	9	10	10	11	277	157	19	11	94	122
DBS6.6	10	10	11	92	10	11	11	114	53	10	9	10	10	20	52	158	58	11	63	122
DBS6.7	10	10	14	64	10	11	11	152	125	10	9	10	11	15	533	461	#DIV/0!	31	73	163
DBS6.8	10	10	10	64	10	11	11	91	386	10	9	10	11	12	156	29	14	14	291	70

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1DBS1	1	1	5	27	3	1	2	4	10	1	1	1	2	2	29	16	18	2	5	19
1DBS2	1	1	5	30	2	1	2	4	9	2	1	1	2	3	23	20	20	1	6	18
1DBS3	1	1	8	25	1	1	1	4	12	1	1	1	8	9	33	23	18	7	8	19
1DBS4	1	1	5	29	1	1	2	4	10	1	1	1	3	3	27	18	18	2	6	30
1DBS5	1	1	5	24	2	2	1	4	10	1	1	1	2	6	21	17	18	13	7	18
1DBS6	2	2	26	33	1	3	2	5	14	3	1	2	6	8	42	33	20	7	7	33
1DBS7	2	2	10	26	3	4	2	4	11	2	1	1	5	6	25	23	26	19	8	29
1DBS8	2	2	13	29	3	2	2	3	11	2	1	1	5	16	23	39	21	16	9	23
1DBS9	1	2	13	37	3	2	2	5	11	3	1	2	5	8	33	27	23	11	9	28
1DBS10	2	2	20	27	4	2	2	4	12	13	2	1	4	5	27	21	15	22	10	21
2DBS1	1	1	2	22	8	2	2	2	8	3	1	1	2	10	26	20	18	11	7	23
2DBS2	1	1	2	22	1	1	2	2	9	1	1	1	2	5	24	24	18	3	8	23
2DBS3	1	1	2	22	1	2	2	3	10	1	1	1	2	16	29	21	24	57	10	31
2DBS4	1	1	1	17	1	2	2	2	8	2	1	1	3	23	32	25	24	27	6	27
2DBS5	2	2	4	27	1	3	2	2	10	2	1	1	3	7	27	24	15	13	8	18
2DBS6	2	2	4	27	2	4	2	2	11	3	2	2	3	15	30	24	22	12	10	26
2DBS7	2	2	4	30	3	3	2	2	12	3	2	1	5	4	22	22	13	4	8	24

2DBS8	1	2	4	24	9	2	2	2	9	4	1	1	3	8	42	30	25	11	9	31
DBS6.1	1	1	3	20	4	1	2	3	11	2	1	1	2	7	23	19	21	3	9	27
DBS6.2	3	3	4	17	7	3	2	3	11	3	3	3	4	4	49	12	16	5	8	22
DBS6.3	1	1	3	20	3	2	2	3	11	4	1	1	4	5	38	23	9	5	8	21
DBS6.4	1	1	4	26	3	2	2	4	13	1	1	1	1	3	22	22	5	2	8	22
DBS6.5	1	1	4	27	1	2	2	3	16	2	1	1	1	6	41	25	12	4	10	28
DBS6.6	1	1	3	30	1	2	1	3	11	1	1	1	2	17	27	25	23	5	10	23
DBS6.7	1	1	9	32	1	1	2	4	18	1	1	1	4	10	41	42	38	29	13	31
DBS6.8	1	1	2	25	2	1	2	4	18	2	1	1	4	6	35	17	7	9	14	24

4.Bainiuchang

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
3BNC1	3905	135607	5.88	0.47	2074	16.25	3.07	<1.49	<5.39	23	8384	75	1826	0.9	0.58	0.06	0.03	1.3	0.02	<0.02
3BNC2	3837	146533	6.73	0.46	10512	14.42	3.33	<1.70	<4.82	173	8564	38	2082	1.3	<0.62	<0.07	<0.03	2.3	<0.08	<0.01
3BNC3	3444	125433	7.04	0.56	2240	9.06	3.11	<2.03	7.48	41	8243	262	1818	3.7	<0.69	<0.07	<0.04	2.9	<0.05	0.01
3BNC4	3461	124408	7.15	<0.32	1102	15.18	2.79	<2.22	<4.86	25	8279	136	845	1.9	<0.46	<0.06	0.03	2.8	<0.07	<0.02
3BNC5	2965	119171	6.67	<0.31	471	6.77	3.1	<1.83	3.99	21	7764	254	38	9.7	<0.65	<0.05	<0.03	5.1	<0.06	<0.02
3BNC6	3481	126876	7.49	0.33	242	18.15	3.99	<1.99	<3.71	13	8008	97	123	3.1	<0.46	<0.05	<0.03	2.7	<0.07	<0.02
3BNC7	3554	130538	6.3	<0.24	1960	19.02	3.17	<2.08	<4.53	38	8334	96	1696	4.8	<0.70	<0.05	<0.03	3.2	<0.07	<0.02
3BNC8	3930	157870	6.46	<0.30	132	7.35	3.69	<1.95	<4.34	9	7744	55	65	0.3	<0.70	<0.02	<0.03	0.7	<0.07	<0.02
3BNC9	3714	135934	4.44	<0.31	981	11.78	4.69	<1.79	<3.34	9	8171	35	238	1.4	<0.51	<0.06	<0.02	2.2	<0.06	<0.02
3BNC10	6537	143164	5.21	0.57	2825	23.22	3.26	1.73	3.96	38	8459	49	2558	1.8	<0.74	<0.07	<0.03	1.6	<0.05	0.01
10BNC1	4459	153729	0.04	<0.25	1874	3.51	3.57	<2.34	<3.41	65.5	5256	5.6	541	2.2	<0.95	<0.10	<0.02	4.8	<0.08	<0.02
10BNC2	4121	157498	0.07	<0.28	8769	3.49	2.99	<2.55	<3.22	47.7	5298	3.5	26	3.1	<1.11	<0.05	<0.02	4.4	<0.08	<0.02
10BNC3	5782	171476	0.11	<0.65	1283	2.16	3.43	<3.29	<5.13	46.9	5876	6.6	8	0.1	<0.81	<0.07	<0.03	1	<0.08	<0.03
10BNC4	3279	142679	0.31	<0.38	9450	24.31	20.78	<3.13	<3.27	188.7	5448	49	3097	15.4	<0.78	<0.08	0.09	64.6	<0.09	0.08
10BNC5	4576	160196	0.22	<0.61	2394	11.25	3.04	<2.93	<3.50	81.4	5735	47	176	8	<0.86	<0.08	0.04	17.3	<0.09	0.08
10BNC6	4077	159703	0.01	<0.34	7694	8.43	3.66	<3.84	3.8	123.4	5776	39	39	6.1	0.47	<0.05	0.05	30.4	<0.11	0.05
10BNC7	2825	146043	0.08	<0.31	11261	4.41	3.38	<3.69	<3.66	116.4	5805	18	1380	17.9	<0.71	<0.06	0.08	14.9	<0.08	0.69
10BNC8	2439	142091	0.02	<0.62	2892	3.09	1.99	<5.72	13.93	91.1	5345	6	14	13.3	<1.49	<0.18	<0.06	8.6	<0.14	<0.04

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
3BNC1	0.721	10.911	0.050	0.230	1.194	0.074	1.774	1.4917	5.3897	0.0678	0.2580	0.0285	0.2262	0.0902	0.4801	0.0501	0.0232	0.0452	0.0589	0.0178
3BNC2	0.975	11.563	0.061	0.245	1.098	0.072	1.870	1.6971	4.8202	0.0357	0.6623	0.0277	0.2765	0.1263	0.6158	0.0696	0.0335	0.0419	0.0770	0.0124
3BNC3	0.787	9.765	0.038	0.299	1.050	0.073	1.503	2.0345	3.1279	0.0691	0.2640	0.0194	0.1976	0.0732	0.6946	0.0696	0.0411	0.0394	0.0522	0.0127
3BNC4	0.756	10.143	0.053	0.319	0.862	0.086	1.710	2.2193	4.8592	0.0681	0.4664	0.0170	0.1805	0.1356	0.4618	0.0558	0.0239	0.0304	0.0669	0.0192
3BNC5	0.660	13.452	0.051	0.310	0.771	0.098	1.794	1.8296	3.7549	0.0590	0.2865	0.0248	0.1637	0.1217	0.6509	0.0482	0.0331	0.0386	0.0587	0.0161
3BNC6	0.609	12.010	0.062	0.152	0.773	0.050	1.366	1.9873	3.7058	0.0510	0.3749	0.0255	0.2282	0.0899	0.4620	0.0528	0.0308	0.0304	0.0653	0.0162
3BNC7	0.738	12.616	0.055	0.239	0.872	0.101	1.485	2.0837	4.5283	0.0740	0.3886	0.0225	0.2338	0.0819	0.7040	0.0680	0.0288	0.0401	0.0718	0.0151
3BNC8	0.662	10.447	0.050	0.303	0.969	0.063	1.761	1.9493	4.3378	0.0581	0.4817	0.0146	0.2099	0.0846	0.6992	0.0627	0.0259	0.0300	0.0704	0.0168
3BNC9	0.829	11.230	0.078	0.307	0.907	0.085	1.761	1.7942	3.3441	0.0825	0.3573	0.0136	0.2317	0.1004	0.5055	0.0605	0.0247	0.0345	0.0629	0.0192
3BNC10	0.720	13.443	0.061	0.218	0.802	0.058	1.660	1.5770	2.5685	0.0750	0.3082	0.0197	0.2295	0.0910	0.7356	0.0657	0.0290	0.0297	0.0488	0.0106

10BNC1	0.748	17.492	0.087	0.255	1.258	0.101	2.153	2.3375	3.4137	0.0762	0.4672	0.0247	0.2761	0.1441	0.9527	0.0974	0.0249	0.0404	0.0791	0.0210
10BNC2	1.037	13.042	0.090	0.281	1.266	0.105	2.128	2.5475	3.2221	0.1233	0.4584	0.0296	0.2832	0.1108	1.1115	0.0540	0.0198	0.0274	0.0778	0.0220
10BNC3	0.943	18.552	0.029	0.648	1.135	0.090	2.556	3.2935	5.1309	0.0982	0.5830	0.0191	0.3020	0.1426	0.8074	0.0712	0.0319	0.0610	0.0836	0.0252
10BNC4	0.999	13.386	0.084	0.379	1.127	0.106	2.029	3.1276	3.2729	0.0493	0.4277	0.0214	0.3510	0.0989	0.7818	0.0753	0.0230	0.0434	0.0898	0.0199
10BNC5	0.976	17.297	0.048	0.606	1.225	0.106	2.462	2.9324	3.5033	0.0874	0.7483	0.0187	0.2414	0.1071	0.8567	0.0850	0.0342	0.0352	0.0909	0.0090
10BNC6	0.896	14.737	0.088	0.339	0.882	0.091	1.923	3.8352	3.4649	0.0706	0.5587	0.0257	0.2486	0.1211	0.2993	0.0502	0.0229	0.0656	0.1058	0.0223
10BNC7	0.884	17.389	0.062	0.307	1.169	0.093	2.379	3.6878	3.6605	0.0483	0.7370	0.0138	0.2879	0.0962	0.7126	0.0619	0.0312	0.0454	0.0757	0.0169
10BNC8	1.878	26.238	0.105	0.621	1.963	0.197	3.446	5.7198	5.3199	0.1833	0.7109	0.0392	0.5102	0.2580	1.4916	0.1802	0.0624	0.0970	0.1425	0.0395

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
3BNC1	7	7	8	41	8	8	24	82	148	7	6	7	7	10	39	61	80	8	139	56
3BNC2	7	7	8	46	10	8	23	130	160	20	7	7	11	11	330	184	433	9	1637	330
3BNC3	7	7	7	42	6	8	21	80	37	6	6	7	6	9	4639	627	72	8	176	85
3BNC4	7	7	8	586	9	10	25	73	108	8	6	7	9	9	328	408	80	7	1107	752
3BNC5	7	7	7	62	11	8	23	141	73	7	6	7	17	8	196	119	2382	8	101	97
3BNC6	7	7	8	40	8	9	17	140	154	7	7	7	8	8	148	351	510	8	100	339
3BNC7	7	7	7	88	7	8	20	113	232	6	6	7	7	7	306	157	1052	7	783	205
3BNC8	7	8	8	470	7	8	20	152	75	8	7	7	7	19	119	142	209	9	94	161
3BNC9	8	8	10	133	12	9	17	143	1402	8	7	10	9	10	49	989	268	9	506	448
3BNC10	7	7	8	31	7	8	21	50	56	7	6	7	7	9	92	358	297	8	145	64
10BNC1	9	9	117	92	12	11	26	221	112	9	8	11	22	23	268	250	450	13	1554	894
10BNC2	9	9	75	72	13	12	30	627	188	9	8	9	10	15	1344	84	49	14	90	18
10BNC3	9	9	30	1113	9	12	30	262	346	9	8	9	10	58	208	271	125	21	95	974
10BNC4	11	10	23	81	9	12	12	819	134	9	9	9	13	12	2100	90	31	9	428	23
10BNC5	9	9	20	143	9	11	31	1072	438	9	8	9	9	9	272	2474	79	10	197	20
10BNC6	9	9	445	262	10	11	23	90	68	10	9	10	11	13	44	81	47	9	332	26
10BNC7	9	9	54	82	9	11	29	42	516	9	8	9	14	9	257	83	38	9	132	29
10BNC8	18	19	424	-	18	21	97	388	51	17	16	17	15	16	278	-	201	14	200	224

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
3BNC1	2	2	4	21	4	3	2	4	9	3	1	3	3	6	22	24	21	5	6	30
3BNC2	2	2	4	25	8	3	2	5	11	19	1	2	9	7	32	30	25	5	6	32
3BNC3	1	1	3	20	1	3	2	4	12	2	1	2	1	6	32	25	23	5	8	22
3BNC4	2	2	4	24	6	7	2	4	13	4	2	2	7	6	36	26	21	3	9	23
3BNC5	2	2	3	57	8	4	2	4	13	3	2	2	15	4	24	24	24	5	7	23
3BNC6	2	2	3	25	3	5	2	4	13	3	1	2	3	4	28	28	26	4	9	24
3BNC7	2	2	3	25	1	2	2	4	13	2	2	2	1	4	29	29	24	3	9	34
3BNC8	2	3	4	28	3	2	2	4	12	3	2	1	2	11	21	23	23	5	9	20
3BNC9	3	3	7	33	10	4	2	4	13	5	3	7	5	6	22	27	26	6	9	27
3BNC10	2	2	4	17	3	5	2	3	12	2	2	2	2	6	42	30	22	5	9	22
10BNC1	1	2	20	33	8	4	3	3	11	3	2	6	20	21	32	23	22	9	8	25
10BNC2	1	1	20	24	9	6	2	3	12	2	2	3	4	12	25	27	20	11	9	16
10BNC3	2	2	23	26	2	7	2	3	13	2	2	2	5	16	30	24	27	17	9	22

10BNC4	6	3	13	20	3	6	4	3	13	1	3	3	10	8	30	18	16	2	9	15
10BNC5	1	2	13	40	1	5	2	3	13	1	2	1	3	3	21	26	16	4	9	17
10BNC6	2	2	21	24	4	4	2	3	10	4	2	4	7	9	32	25	18	3	11	15
10BNC7	1	2	20	26	3	5	2	3	13	2	2	3	11	3	27	22	16	2	9	27
10BNC8	12	12	108	108	11	15	10	16	31	10	10	10	5	9	70	70	108	4	40	108

5. Laochang

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
9LC1	2626	130008	0.34	<0.29	139	8.66	2.83	<1.74	<4.36	5.8	8798	191	3.33	0.10	<0.48	<0.062	<0.028	0.8	0.05	<0.010
9LC2	2660	127420	0.08	<0.31	162	9.73	2.52	<1.65	3.68	4.8	8534	188	4.01	0.00	<0.54	<0.072	<0.023	0.3	<0.06	<0.016
9LC3	2707	129613	0.16	0.27	148	6.6	2.98	<1.89	<2.83	6.3	8709	184	2.86	0.10	<0.79	<0.057	<0.035	3.4	<0.06	<0.015
9LC4	2844	126228	0.61	0.27	167	13.83	3.57	<1.70	<3.31	5.5	8607	232	5.17	0.10	<0.51	<0.084	0.029	0.3	<0.06	<0.014
9LC5	2845	129302	0.57	<0.30	206	22.5	4.94	4.08	<4.71	6.6	8631	230	9.64	4.10	<0.50	<0.040	1.355	556	0.05	<0.020
9LC6	2761	127308	0.51	0.25	165	5.62	3.6	<2.06	<4.75	5.8	8939	196	5.5	0.00	<0.62	<0.056	0.024	0.5	<0.06	<0.017
9LC7	2879	130321	0.65	<0.29	163	12.72	2.93	<1.71	<3.86	6.3	8766	206	2.38	0.20	<0.75	<0.079	0.052	9.7	<0.07	<0.015
9LC8	2711	128769	0.38	<0.25	149	10.5	3.64	<2.09	<4.06	5.7	8765	193	3.72	0.00	<0.79	<0.064	<0.029	0.4	<0.05	<0.020
9LC9	2678	125661	0.08	<0.48	155	10.62	2.76	<2.29	<4.57	7.6	8526	179	13.58	1.90	<0.54	<0.115	0.032	1.7	-0.03	<0.024
9LC10	2690	127950	0.56	<0.31	146	11.62	3.13	<1.15	<4.50	6.7	8832	176	4.98	0.10	<0.71	<0.069	<0.042	0.4	-0.01	<0.013
9LC11	2645	123724	0.35	<0.28	236	7.100	7.13	2.02	<3.04	8	8420	183	4.94	2.80	<0.69	<0.047	1.018	7.8	<0.05	<0.012
9LC12	2767	126937	0.07	0.39	380	9.98	5.64	2.29	<3.22	8.6	8532	191	9.11	3.20	<0.59	<0.079	1.238	19.8	<0.05	<0.015
9LC13	2771	132072	0.72	<0.22	188	46.4	2.11	<1.92	<3.75	6.4	8697	134	6.25	0.30	<0.60	<0.057	0.054	1.8	<0.06	<0.012
9LC14	2695	129473	0.91	<0.42	119	46.53	3.85	<1.48	3.98	6	8665	80	4.07	0.10	<0.97	<0.044	<0.025	0.4	<0.05	<0.014
LC19.1	4111	154203	0.6	0.05	197	12.05	3.78	36.43	2.15	6.3	8770	263	19.49	1.50	<0.14	<0.010	0.836	4.8	<0.01	0.014
LC19.2	3173	138954	1.13	<0.05	364	5.68	3.21	<0.37	2.49	6.2	8749	566	3.72	<0.01	<0.11	<0.009	0.006	0.4	0.01	0.002
LC19.3	3123	138823	1.21	0.03	164	6.11	4.32	<0.41	1.47	5.2	8807	236	4.04	0.20	<0.07	<0.010	0.125	1	0.01	<0.004
LC19.4	3558	144538	0.45	0.08	266	117.05	3.64	0.58	2.47	6.2	8306	252	38.11	0.90	<0.17	<0.008	0.484	2	0.01	0.387
LC19.5	3482	139883	0.24	<0.07	274	60.72	3.86	0.93	3.09	7.5	8947	262	2.81	1.20	<0.09	<0.008	0.125	2.4	<0.01	<0.003
LC19.6	3558	141388	0.37	<0.08	260	37.91	3.47	1.75	1.34	6	8909	262	6.41	0.20	<0.07	<0.010	0.020	0.9	0.01	<0.002
LC19.7	3525	139995	0.43	<0.04	275	59.09	3.45	<0.36	1.45	5.9	8915	254	5.76	0.10	<0.11	<0.008	<0.004	0.5	0.00	<0.002
LC19.8	3191	138973	0.18	0.07	205	30.83	3.63	<0.47	3.02	6.6	8745	250	2.23	0.50	<0.16	<0.009	0.262	1.4	0.02	<0.003
LC09-18.1	3266	124740	1.52	0.07	411	24.49	9.2	1.72	0.62	7.3	8519	117	5.85	1.00	<0.07	<0.004	0.670	14.7	0.01	<0.002
LC09-18.2	3287	128675	1.12	0.20	210	3.00	3.89	5.80	0.96	8.7	8901	231	8.34	2.90	<0.08	<0.004	0.760	54.1	0.01	0.002
LC09-18.3	3222	126822	0.44	1.66	2020	17.52	15.13	10.27	<0.54	7.6	9600	160	5.55	2.30	<0.08	<0.006	2.571	15.3	0.01	<0.002
LC09-18.4	3219	121861	2.24	0.09	143	24.19	2.71	0.43	1.32	7.1	8573	89	4.29	1.60	0.07	<0.004	0.309	5.1	0.01	0.001
LC09-18.5	3309	123927	3.06	0.10	227	21.88	4.06	2.28	1.01	9.7	8860	117	8.07	2.60	<0.10	<0.004	0.552	25.8	0.01	<0.001
LC09-18.6	3207	122400	4.41	0.08	128	22.34	2.89	<0.31	1.13	7.5	9070	122	4.22	0.50	<0.08	<0.003	0.132	5.7	0.01	<0.001
LC09-18.7	3172	122818	1.81	0.12	210	2.27	2.81	<0.29	1.02	5.8	8558	203	3.83	0.40	<0.06	-0.002	0.104	2.8	0.01	<0.001
LC09-18.8	3114	121694	1.68	0.15	137	24.44	2.76	0.33	0.62	10.1	8519	66	8.18	1.30	<0.07	<0.004	0.330	25.2	0.01	<0.001

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
9LC1	0.8683	13.0429	0.0379	0.2874	0.8345	0.112	1.3371	1.7386	4.3587	0.063	0.4668	0.0231	0.2407	0.0657	0.4752	0.0623	0.0284	0.0419	0.0489	0.0104
9LC2	0.5702	12.5514	0.0602	0.3054	0.8588	0.0843	1.5790	1.6457	3.3632	0.0605	0.2930	0.0155	0.2425	0.0672	0.5437	0.0718	0.0228	0.0382	0.0611	0.0158

9LC3	0.7220	11.8640	0.0440	0.1597	0.8780	0.0991	1.8266	1.8870	2.8293	0.0824	0.3428	0.0209	0.1889	0.0991	0.7879	0.0574	0.0353	0.0323	0.0620	0.0152
9LC4	0.6624	8.6809	0.0712	0.2542	0.6476	0.0610	1.3286	1.7021	3.3097	0.0735	0.2089	0.0164	0.2275	0.0693	0.5145	0.0837	0.0144	0.0305	0.0632	0.0137
9LC5	0.6364	9.9862	0.0579	0.2995	0.6629	0.0739	1.6606	1.4435	4.7125	0.0676	0.5516	0.0269	0.2176	0.0801	0.4990	0.0400	0.0305	0.0400	0.0346	0.0204
9LC6	0.7619	11.4064	0.0399	0.2279	0.7787	0.0761	1.8548	2.0558	4.7473	0.0784	0.4301	0.0280	0.2312	0.1056	0.6214	0.0559	0.0213	0.0353	0.0580	0.0172
9LC7	0.8233	12.5111	0.0393	0.2854	0.6971	0.0850	1.2783	1.7143	3.8626	0.0657	0.2301	0.0166	0.2928	0.0900	0.7522	0.0792	0.0253	0.0498	0.0662	0.0149
9LC8	0.8519	12.8585	0.0545	0.2535	0.9588	0.0614	1.7693	2.0936	4.0627	0.0753	0.3576	0.0251	0.2122	0.1049	0.7946	0.0640	0.0288	0.0380	0.0510	0.0203
9LC9	0.7444	14.4734	0.0618	0.4812	1.2598	0.1065	2.1344	2.2950	4.5706	0.1125	0.4381	0.0239	0.3207	0.0846	0.5391	0.1154	0.0321	0.0435	0.0836	0.0240
9LC10	0.7317	13.0020	0.0644	0.3092	1.2120	0.0882	1.9549	1.5500	4.5049	0.0540	0.3700	0.0162	0.2503	0.1161	0.7059	0.0685	0.0420	0.0373	0.0510	0.0133
9LC11	0.6975	9.5520	0.0454	0.2753	0.8450	0.0851	1.5203	1.6932	3.0412	0.0777	0.2561	0.0165	0.1883	0.0969	0.6899	0.0470	0.0244	0.0263	0.0515	0.0125
9LC12	0.6565	12.2798	0.0628	0.2369	0.7065	0.0785	1.4336	2.1311	3.2173	0.0527	0.4455	0.0191	0.2395	0.0594	0.5933	0.0791	0.0242	0.0375	0.0462	0.0146
9LC13	0.6069	9.2524	0.0787	0.2165	0.7387	0.0685	1.5529	1.9198	3.7491	0.0634	0.3053	0.0144	0.2166	0.0598	0.5977	0.0573	0.0277	0.0364	0.0556	0.0124
9LC14	0.6724	12.1333	0.0559	0.4179	0.6955	0.0934	1.1389	1.4843	2.3086	0.0456	0.5345	0.0102	0.2076	0.0631	0.9698	0.0441	0.0249	0.0343	0.0522	0.0144
LC19.1	0.1039	2.2682	0.0064	0.0186	0.1400	0.0110	0.2587	0.4028	0.4139	0.0075	0.0735	0.0029	0.0371	0.0173	0.1411	0.0103	0.0028	0.0065	0.0095	0.0035
LC19.2	0.1177	2.0848	0.0104	0.0490	0.1293	0.0141	0.2828	0.3723	0.4134	0.0106	0.0556	0.0024	0.0360	0.0136	0.1062	0.0088	0.0023	0.0049	0.0104	0.0016
LC19.3	0.1099	1.9879	0.0121	0.0262	0.1173	0.0144	0.2485	0.4108	0.4976	0.0076	0.0673	0.0033	0.0327	0.0196	0.0746	0.0102	0.0041	0.0069	0.0091	0.0037
LC19.4	0.1102	1.8100	0.0075	0.0495	0.1262	0.0154	0.2480	0.3963	0.4542	0.0079	0.0908	0.0022	0.0336	0.0147	0.1721	0.0083	0.0047	0.0057	0.0111	0.0029
LC19.5	0.1165	1.8601	0.0073	0.0695	0.1231	0.0128	0.2536	0.3082	0.4486	0.0086	0.0635	0.0031	0.0390	0.0120	0.0938	0.0084	0.0036	0.0061	0.0099	0.0026
LC19.6	0.0918	2.0160	0.0073	0.0819	0.1229	0.0168	0.3286	0.4346	0.4360	0.0063	0.0786	0.0024	0.0337	0.0096	0.0656	0.0103	0.0052	0.0052	0.0091	0.0024
LC19.7	0.1145	1.6188	0.0065	0.0405	0.1600	0.0093	0.2696	0.3626	0.4829	0.0125	0.0747	0.0039	0.0421	0.0160	0.1064	0.0080	0.0038	0.0059	0.0105	0.0022
LC19.8	0.1545	2.4040	0.0066	0.0235	0.2134	0.0176	0.4755	0.4746	0.6414	0.0079	0.0871	0.0041	0.0499	0.0176	0.1629	0.0093	0.0038	0.0086	0.0113	0.0028
LC09-18.1	0.0733	1.9683	0.0035	0.0260	0.0764	0.0058	0.1569	0.2968	0.4450	0.0075	0.0408	0.0016	0.0293	0.0087	0.0654	0.0038	0.0035	0.0054	0.0076	0.0015
LC09-18.2	0.0727	1.9204	0.0030	0.0170	0.0772	0.0044	0.1652	0.2434	0.4919	0.0058	0.0571	0.0018	0.0323	0.0102	0.0802	0.0036	0.0019	0.0050	0.0083	0.0012
LC09-18.3	0.0746	2.2072	0.0065	0.0181	0.0854	0.0045	0.2106	0.2642	0.5374	0.0081	0.0526	0.0019	0.0295	0.0092	0.0845	0.0055	0.0024	0.0049	0.0100	0.0017
LC09-18.4	0.0896	1.7118	0.0057	0.0211	0.0651	0.0052	0.1870	0.2413	0.4661	0.0055	0.0531	0.0018	0.0293	0.0055	0.0408	0.0045	0.0021	0.0050	0.0080	0.0012
LC09-18.5	0.0754	2.0180	0.0032	0.0315	0.0623	0.0043	0.1582	0.2577	0.4682	0.0043	0.0554	0.0019	0.0330	0.0072	0.0996	0.0039	0.0021	0.0042	0.0079	0.0014
LC09-18.6	0.0923	1.7896	0.0047	0.0160	0.0671	0.0044	0.1719	0.3137	0.3392	0.0052	0.0593	0.0019	0.0303	0.0080	0.0820	0.0035	0.0025	0.0044	0.0083	0.0015
LC09-18.7	0.0862	1.7640	0.0045	0.0252	0.0853	0.0062	0.1569	0.2880	0.3673	0.0079	0.0682	0.0015	0.0276	0.0073	0.0647	0.0076	0.0026	0.0047	0.0057	0.0013
LC09-18.8	0.0832	2.1106	0.0082	0.0167	0.0832	0.0058	0.1877	0.3200	0.4194	0.0076	0.0745	0.0024	0.0285	0.0110	0.0722	0.0043	0.0018	0.0060	0.0076	0.0023

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
9LC1	7	7	17	163	7	8	22	96	1134	8	6	7	9	49	67	121	176	40	52	62
9LC2	7	7	55	109	9	8	25	126	69	8	7	8	9	80	263	77	261	14	97	540
9LC3	7	7	23	48	7	8	25	127	151	7	6	7	9	83	249	143	89	8	187	328
9LC4	7	7	14	65	7	9	18	84	343	8	7	7	9	66	141	1063	52	20	1343	747
9LC5	7	7	13	186	7	8	15	22	162	7	6	7	7	8	71	72	8	15	43	233
9LC6	7	7	14	68	7	8	22	68	126	7	6	7	8	1005	206	207	82	10	204	101
9LC7	7	7	11	158	7	8	20	422	528	7	6	6	11	30	126	155	47	7	169	306
9LC8	7	7	16	77	7	8	21	120	126	7	6	7	9	101	97	126	463	15	113	358
9LC9	7	7	70	72	8	10	38	96	62	9	8	7	8	12	119	210	220	13	421	253
9LC10	7	7	14	103	7	9	25	497	779	7	6	7	8	104	217	136	272	10	294	70
9LC11	7	7	15	208	7	8	12	46	679	7	7	7	8	8	121	269	9	7	281	63
9LC12	7	7	61	49	7	8	13	51	267	7	6	7	13	9	100	85	11	10	67	114
9LC13	7	7	12	83	9	7	30	251	228	7	6	7	8	21	417	135	49	15	69	58
9LC14	7	7	10	123	7	8	15	889	45	7	6	7	8	33	102	116	276	10	52	148
LC19.1	10	10	11	36	10	12	11	17	19	10	10	10	11	13	151	83	11	12	178	21
LC19.2	10	10	11	75	10	11	11	81	18	10	9	10	10	41	217	298	39	13	115	50
LC19.3	10	10	11	77	10	11	10	81	28	10	9	10	10	15	164	131	13	12	94	237
LC19.4	10	10	11	44	10	11	11	39	18	10	10	10	29	11	138	331	12	13	62	16
LC19.5	10	10	13	151	10	12	11	27	17	10	9	10	11	11	137	494	17	10	302	84

LC19.6	10	10	12	370	11	11	11	30	29	10	9	10	13	16	56	332	32	11	58	82
LC19.7	10	10	11	414	10	11	11	61	31	10	9	10	10	19	213	283	107	17	215	214
LC19.8	10	10	17	49	10	11	12	90	27	10	9	10	12	14	56	122	13	11	46	325
LC09-18.1	5	5	5	31	8	5	6	11	56	5	5	5	5	5	77	343	5	13	53	234
LC09-18.2	5	5	5	12	5	6	6	6	38	5	5	5	5	5	243	62	5	5	38	33
LC09-18.3	5	5	6	13	6	5	8	7	80	5	5	5	6	6	92	155	7	8	41	221
LC09-18.4	5	5	5	22	6	5	6	32	26	5	5	5	5	6	30	210	6	7	53	63
LC09-18.5	5	5	5	26	5	5	6	10	34	5	5	5	5	6	146	147	7	6	74	354
LC09-18.6	5	5	5	25	5	5	6	74	27	5	5	5	5	8	503	62	10	6	74	132
LC09-18.7	5	5	5	20	9	6	6	7931	29	5	5	5	6	10	74	241	12	8	46	289
LC09-18.8	5	5	5	16	5	5	6	50	51	5	5	5	5	8	877	254	8	9	47	7318

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
9LC1	2	2	13	29	3	4	2	4	11	4	2	1	4	20	25	22	21	37	10	23
9LC2	2	2	18	23	6	3	2	4	12	4	1	4	4	22	29	25	21	9	6	23
9LC3	2	2	14	27	2	3	2	4	12	4	2	1	4	14	27	30	18	5	10	30
9LC4	2	2	9	24	2	6	3	4	14	5	2	2	4	21	30	25	25	16	7	20
9LC5	2	2	9	24	1	3	2	4	13	4	2	1	3	5	23	24	5	14	8	25
9LC6	2	2	11	26	2	4	2	3	12	4	1	2	3	23	36	29	22	7	9	24
9LC7	1	2	9	25	4	3	2	4	11	3	1	1	4	14	39	25	15	4	9	26
9LC8	3	2	11	22	3	3	2	4	13	3	2	2	4	23	36	28	24	11	9	21
9LC9	2	1	57	104	3	8	7	8	48	7	2	2	3	11	70	75	48	10	21	55
9LC10	2	2	10	23	3	5	2	4	13	3	2	2	3	21	25	26	23	6	9	21
9LC11	2	2	10	30	2	2	2	4	12	3	2	1	4	4	32	30	6	2	9	16
9LC12	2	2	21	22	2	4	2	4	12	3	2	1	10	6	37	34	9	8	8	36
9LC13	2	2	7	27	6	2	2	4	14	4	1	1	4	15	25	20	21	13	9	21
9LC14	2	2	7	28	3	3	2	4	12	3	1	1	4	18	28	25	24	6	10	21
LC19.1	2	2	3	25	1	5	2	12	7	2	2	1	4	9	28	27	5	7	8	14
LC19.2	1	1	3	21	1	2	2	3	7	2	1	1	2	15	25	24	19	8	8	22
LC19.3	1	1	3	33	1	3	2	3	9	2	1	1	2	9	28	27	9	6	7	21
LC19.4	2	1	4	19	2	1	1	3	7	2	2	1	28	5	30	32	6	9	9	13
LC19.5	2	1	7	22	3	4	2	5	8	2	1	1	4	4	23	23	14	2	11	28
LC19.6	2	1	5	27	5	2	2	10	9	2	1	1	7	12	25	22	15	5	9	20
LC19.7	2	1	5	31	2	1	2	3	10	2	1	1	2	10	27	28	18	13	9	27
LC19.8	1	1	13	41	2	2	3	6	16	2	1	2	5	10	28	41	8	4	13	41
LC09-18.1	2	1	2	16	6	1	3	2	6	1	1	2	3	3	20	33	3	12	5	29
LC09-18.2	2	2	3	10	1	3	2	2	6	2	1	1	2	3	20	26	3	2	6	17
LC09-18.3	1	1	4	12	4	1	6	4	8	2	1	1	3	3	20	44	5	7	6	19
LC09-18.4	2	2	2	14	4	1	1	2	6	2	1	1	2	4	17	26	5	5	6	21
LC09-18.5	2	2	2	14	2	1	2	3	7	1	1	1	2	4	21	24	6	4	6	27
LC09-18.6	1	1	2	19	2	1	2	2	8	2	1	1	1	7	25	25	8	3	6	21
LC09-18.7	1	1	2	13	7	2	2	3	8	2	1	1	3	9	21	23	10	7	7	31
LC09-18.8	2	1	2	14	2	1	1	2	9	1	1	1	1	6	25	32	7	8	7	22

MVT deposits

6. Huize

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Hui 1086.1	121	37553	0.04	0.12	1188	1.11	354	21	1.04	36.8	3637	<0.003	0.14	72.3	<0.06	<0.008	0.018	19.5	0.02	<0.002
Hui 1086.2	88	25183	0.04	0.04	357	6.18	98	11	1.64	22.1	3404	0.003	0.10	43.9	<0.10	<0.006	0.166	15.3	0.02	<0.002
Hui 1086.3	137	47248	0.05	0.2	926	19.75	146	90	1.04	76.8	4647	0.003	0.10	306.8	0.05	0.005	0.051	44.3	0.01	<0.002
Hui 1086.4	100	32666	0.04	0.21	809	8.06	221	23	<0.45	30.9	2817	0.002	0.11	65.7	<0.07	<0.009	0.013	10.6	0.01	<0.002
Hui 1086.5	105	32551	0.03	0.21	287	0.4	90	1.4	0.93	14.3	3104	<0.002	0.10	4.2	<0.10	<0.008	0.004	1.2	0.02	<0.001
Hui 1086.6	132	40305	0.05	0.24	263	3.96	80	0.23	1.12	13.3	2977	<0.002	0.08	7.5	<0.08	<0.008	0.026	7.1	0.01	<0.002
Hui 1086.7	118	30932	0.03	0.08	414	0.06	143	0.44	0.99	22.4	1728	<0.003	0.11	0.4	<0.07	<0.007	0.01	2.5	0.02	<0.002
Hui 1086.8	88	28080	0.04	0.15	575	0.34	186	1.56	0.75	13.7	2156	<0.003	0.11	11.4	<0.07	<0.007	0.047	3.5	0.01	<0.002
1062HZF1	7	4873	0.01	<0.04	7	0.05	3	<0.38	<0.31	9.6	1708	<0.003	0.07	0	<0.10	<0.008	0.003	1.1	0.01	<0.001
1062HZF2	43	8088	0.01	<0.06	18	0.88	5	2.16	<0.30	22.5	1266	0.456	1.07	1.6	<0.08	<0.007	0.034	3.3	0.02	0.001
1062HZF3	82	5139	0	<0.05	32	0.18	10	100	<0.31	15	894	0.457	1.27	0.6	<0.08	<0.007	0.12	6.4	0.01	0.007
1062HZF4	95	18254	0.01	<0.05	295	0.14	108	21	0.70	30.4	1632	0.355	1.50	2.1	<0.10	<0.008	0.184	6.9	0.01	0.016
1062HZF5	12	8544	0	<0.05	116	2.74	11	22	0.41	44.7	2392	0.019	0.33	130	<0.07	<0.007	0.013	14.7	0.01	<0.003
1062HZF6	98	16351	0.01	<0.04	246	1.17	81	109	0.69	50.7	1518	0.089	2.05	2.1	<0.09	<0.008	0.829	67.7	0.01	<0.002
1062HZF7	7	5166	0.01	0.03	10	1.14	3	<0.35	0.72	19.4	1626	<0.002	0.09	0.4	<0.09	<0.010	0	0.6	0.01	<0.002
1062HZF8	125	43664	0.04	<0.04	533	0.21	199	0.34	0.44	35.9	2474	0.002	0.11	3	<0.06	<0.012	0.086	4.1	0.01	<0.002
HZF1065.1	78	19732	0.02	0.06	119	0.18	40	<0.28	0.38	9	1714	0.392	0.50	0.8	<0.06	<0.008	0.025	0.8	0.01	<0.002
HZF1065.2	35	6482	0.01	0.03	16	7.82	3	385	0.76	10.9	1764	3.611	0.62	2.8	<0.10	<0.010	0.003	5.3	0.01	<0.002
HZF1065.3	45	16662	0.05	0.10	66	1.15	14	3.64	0.39	16.8	1423	0.34	1.21	27.4	<0.07	<0.007	0.196	12.4	0.01	<0.001
HZF1065.4	151	13771	0.02	0.03	23	8.1	5	1.64	0.69	12.7	1555	1.83	0.79	3	0.10	<0.006	0.021	5.7	0.01	0.001
HZF1065.5	58	17462	0.02	<0.07	51	1.49	17	0.43	0.12	8.4	1520	0.597	1.38	1.6	0.01	<0.011	0.054	3.1332	0.0068	<0.003
HZF1065.6	300	18822	0.06	<0.04	7	0.17	3	<0.32	0.81	6	1619	0.826	0.33	2.1	<0.07	<0.006	0.006	1.7	0.01	<0.002
HZF1065.7	11	7040	0	<0.03	14	7.95	3	<0.35	0.33	8.4	1597	5.611	0.16	0.1	<0.06	<0.006	0.001	0.4	0.01	<0.002
HZF1065.8	270	24444	0.01	<0.02	521	21.11	154	<0.32	<0.33	13.9	1707	2.29	27.42	0.2	<0.06	<0.005	-0.001	0.4	0.01	<0.002

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Hui 1086.1	0.08	1.35	0.00	0.04	0.10	0.01	0.1558	0.2425	0.3713	0.0103	0.0314	0.0032	0.0223	0.0111	0.0634	0.0076	0.0031	0.0042	0.0069	0.0016
Hui 1086.2	0.08	1.04	0.01	0.04	0.09	0.01	0.1650	0.2061	0.3830	0.0087	0.0307	0.0022	0.0199	0.0118	0.0960	0.0059	0.0026	0.0055	0.0063	0.0016
Hui 1086.3	0.07	1.09	0.01	0.02	0.06	0.01	0.1850	0.1605	0.3459	0.0075	0.0362	0.0019	0.0241	0.0114	0.0525	0.0048	0.0023	0.0036	0.0072	0.0021
Hui 1086.4	0.06	0.99	0.00	0.03	0.10	0.01	0.1748	0.2189	0.4498	0.0064	0.0399	0.0019	0.0254	0.0100	0.0679	0.0094	0.0032	0.0038	0.0062	0.0017
Hui 1086.5	0.10	1.20	0.01	0.02	0.10	0.01	0.1659	0.1493	0.3272	0.0059	0.0339	0.0021	0.0192	0.0152	0.1026	0.0082	0.0019	0.0033	0.0054	0.0012
Hui 1086.6	0.08	1.22	0.01	0.04	0.10	0.01	0.1976	0.2585	0.3072	0.0093	0.0435	0.0020	0.0245	0.0097	0.0834	0.0083	0.0031	0.0044	0.0061	0.0020
Hui 1086.7	0.07	0.99	0.01	0.03	0.09	0.01	0.1918	0.1818	0.3773	0.0105	0.0494	0.0028	0.0262	0.0096	0.0748	0.0065	0.0026	0.0045	0.0064	0.0017
Hui 1086.8	0.07	1.53	0.01	0.05	0.13	0.01	0.2020	0.2474	0.3846	0.0087	0.0441	0.0025	0.0280	0.0112	0.0746	0.0065	0.0023	0.0045	0.0091	0.0018
1062HZF1	0.07	1.40	0.01	0.04	0.07	0.01	0.1678	0.3823	0.3111	0.0069	0.0701	0.0029	0.0288	0.0111	0.1028	0.0085	0.0018	0.0046	0.0075	0.0015
1062HZF2	0.08	1.17	0.00	0.06	0.10	0.01	0.2480	0.3399	0.3024	0.0080	0.0505	0.0024	0.0278	0.0077	0.0757	0.0072	0.0031	0.0040	0.0059	0.0014
1062HZF3	0.09	1.49	0.01	0.05	0.09	0.01	0.1727	0.3390	0.3143	0.0060	0.0631	0.0019	0.0187	0.0077	0.0792	0.0074	0.0023	0.0047	0.0057	0.0014
1062HZF4	0.07	1.48	0.01	0.05	0.12	0.01	0.1984	0.3851	0.2383	0.0094	0.0740	0.0021	0.0253	0.0143	0.0967	0.0084	0.0029	0.0041	0.0074	0.0027
1062HZF5	0.10	1.70	0.01	0.05	0.12	0.01	0.2177	0.4298	0.3280	0.0089	0.0582	0.0026	0.0309	0.0100	0.0709	0.0073	0.0026	0.0062	0.0054	0.0026
1062HZF6	0.10	1.62	0.01	0.04	0.12	0.01	0.2383	0.3948	0.2932	0.0086	0.0579	0.0026	0.0366	0.0117	0.0861	0.0080	0.0028	0.0040	0.0071	0.0021

1062HZF7	0.10	1.50	0.01	0.01	0.12	0.01	0.2154	0.3513	0.3725	0.0065	0.0465	0.0023	0.0331	0.0144	0.0851	0.0100	0.0029	0.0050	0.0070	0.0021
1062HZF8	0.09	1.74	0.01	0.04	0.10	0.01	0.2309	0.3744	0.3023	0.0094	0.0426	0.0023	0.0388	0.0095	0.0583	0.0115	0.0029	0.0057	0.0066	0.0017
HZF1065.1	0.09	1.45	0.01	0.03	0.13	0.01	0.2245	0.2792	0.3119	0.0057	0.0521	0.0032	0.0257	0.0102	0.0625	0.0076	0.0013	0.0052	0.0064	0.0015
HZF1065.2	0.09	1.38	0.01	0.03	0.10	0.01	0.2226	0.2805	0.2998	0.0047	0.0582	0.0013	0.0277	0.0066	0.0955	0.0102	0.0030	0.0041	0.0103	0.0017
HZF1065.3	0.09	1.50	0.01	0.03	0.09	0.01	0.2101	0.3372	0.3450	0.0066	0.0504	0.0016	0.0339	0.0110	0.0681	0.0074	0.0024	0.0040	0.0066	0.0015
HZF1065.4	0.09	1.29	0.01	0.03	0.10	0.01	0.2205	0.4231	0.3690	0.0111	0.0488	0.0017	0.0197	0.0160	0.0422	0.0061	0.0027	0.0048	0.0065	0.0014
HZF1065.5	0.14	7.48	0.01	0.07	0.31	0.01	0.3158	0.4855	0.5473	0.1671	23.2401	0.0112	0.0422	0.0356	0.0805	0.0108	0.0032	0.1113	0.0126	0.0027
HZF1065.6	0.09	1.58	0.01	0.04	0.11	0.01	0.2285	0.3196	0.2900	0.0037	0.0354	0.0026	0.0368	0.0108	0.0669	0.0065	0.0014	0.0045	0.0066	0.0017
HZF1065.7	0.09	1.42	0.01	0.03	0.10	0.01	0.2611	0.3514	0.2956	0.0089	0.0480	0.0031	0.0307	0.0113	0.0625	0.0064	0.0027	0.0032	0.0063	0.0016
HZF1065.8	0.0848	1.4446	0.0083	0.0247	0.0993	0.0097	0.1827	0.3213	0.3268	0.0073	0.0437	0.0021	0.0299	0.0143	0.0626	0.0053	0.0027	0.0037	0.0056	0.0020

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Hui 1086.1	5	5	15	31	5	6	5	5	28	5	4	1227	13	5	119	720	19	5	20	292
Hui 1086.2	5	5	18	62	8	9	8	8	20	5	4	57	18	5	814	77	6	6	21	167
Hui 1086.3	5	5	14	16	5	6	5	5	27	5	4	45	18	4	52	61	10	5	43	156
Hui 1086.4	5	5	14	15	7	6	6	11	81	5	4	75	17	10	126	543	26	11	26	910
Hui 1086.5	5	5	25	13	5	7	5	9	29	5	4	521	15	5	209	102	43	6	20	55
Hui 1086.6	5	5	17	14	5	6	5	59	25	5	4	436	21	6	76	19492	14	7	26	4175
Hui 1086.7	5	5	23	29	5	17	5	24	31	5	4	413	18	9	114	244	27	7	25	64
Hui 1086.8	5	5	16	25	5	8	5	11	39	5	4	187	18	7	-	4867	11	5	47	155
1062HZF1	7	7	91	225	7	18	8	223	112	7	7	67	26	24	61	235	54	9	45	207
1062HZF2	7	7	46	432	7	11	8	25	112	7	7	10	10	7	422	69	15	7	21	77
1062HZF3	7	8	928	984	8	10	9	26	129	7	7	7	7	8	177	810	8	7	40	31
1062HZF4	7	7	34	81	7	13	8	27	30	7	7	7	7	8	297	19259	8	8	69	23
1062HZF5	7	7	118	235	7	9	7	7	63	7	7	17	11	7	102	315	25	7	33	357
1062HZF6	7	7	32	248	8	8	9	8	35	7	6	10	8	7	84	69	6	7	41	627
1062HZF7	7	7	36	43	7	9	8	298	39	7	7	462	24	11	116	129	1106	11	31	303
1062HZF8	7	7	18	329	8	13	8	59	52	7	7	64	24	9	119	86	12	10	39	58
HZF1065.1	10	9	31	42	11	12	11	65	62	9	8	9	10	9	75	64	17	9	33	64
HZF1065.2	9	9	68	61	9	10	9	14	31	9	8	9	10	10	229	154	106	11	57	236
HZF1065.3	9	9	17	27	9	10	10	10	67	8	8	9	9	8	74	319	9	9	32	1540
HZF1065.4	9	9	29	75	9	11	12	29	42	9	8	9	10	9	30	79	18	10	41	48
HZF1065.5	9	9	56	214	9	12	10	66	374	9	8	10	11	11	342	326	24	10	109	69
HZF1065.6	9	9	15	202	9	14	9	83	30	9	8	9	11	11	137	201	32	10	47	81
HZF1065.7	9	9	294	261	9	10	10	64	68	9	8	9	16	16	88	214	315	9	31	133
HZF1065.8	9	9	77	156	9	11	9	219	148	9	8	9	9	12	119	106	225	12	42	255

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Hui 1086.1	2	1	12	20	1	2	1	2	7	2	1	24	6	1	27	24	10	1	7	24
Hui 1086.2	2	1	12	20	6	6	6	5	8	1	1	23	7	3	21	20	4	4	7	29
Hui 1086.3	1	1	10	12	2	1	1	1	9	2	1	20	7	1	22	22	7	1	7	22
Hui 1086.4	1	1	12	12	5	2	4	10	11	3	1	22	6	9	22	23	12	10	6	22
Hui 1086.5	1	1	12	11	1	4	1	3	9	1	1	32	6	1	24	29	17	4	6	21
Hui 1086.6	1	1	11	9	1	2	1	4	10	1	1	30	6	5	28	23	9	5	6	20

Hui 1086.7	1	1	12	17	3	10	2	4	10	2	1	23	6	7	26	30	12	5	7	18
Hui 1086.8	1	1	12	15	2	5	2	4	10	1	1	24	6	5	28	24	9	3	7	26
1062HZF1	1	1	21	33	2	10	2	2	11	3	1	42	6	14	32	23	23	5	8	29
1062HZF2	2	2	24	33	3	7	3	9	11	1	1	8	6	2	25	20	11	2	7	20
1062HZF3	1	3	32	23	5	5	5	24	11	1	1	3	2	4	26	22	5	3	7	26
1062HZF4	1	1	19	30	3	8	3	23	11	2	1	3	2	5	24	22	5	4	8	20
1062HZF5	1	1	28	31	1	4	2	2	11	1	1	13	5	1	30	25	14	3	9	22
1062HZF6	2	3	20	32	5	3	5	4	9	1	0	7	4	2	25	22	2	1	7	25
1062HZF7	2	1	15	29	2	4	2	3	11	1	1	32	6	8	28	29	24	9	7	21
1062HZF8	2	1	12	28	4	8	4	3	10	2	3	24	7	6	36	24	9	7	8	20
HZF1065.1	4	3	15	19	6	6	6	3	11	1	1	3	4	4	21	29	14	4	7	19
HZF1065.2	2	1	19	24	2	2	2	11	8	2	2	2	4	5	22	24	18	8	8	27
HZF1065.3	1	1	10	14	3	3	5	2	10	1	1	3	3	2	21	30	5	1	7	34
HZF1065.4	2	1	16	21	4	4	6	9	10	2	1	2	4	3	21	24	11	4	9	21
HZF1065.5	3	2	37	71	4	7	4	7	28	2	1	5	6	6	71	71	21	5	19	103
HZF1065.6	1	1	10	21	3	8	1	3	10	2	1	3	4	7	25	33	22	5	9	24
HZF1065.7	1	2	29	36	2	2	2	3	11	1	1	2	5	10	25	27	32	3	8	25
HZF1065.8	1	2	19	36	1	3	1	3	13	2	1	1	2	8	27	29	33	8	9	25

7. Niujiaotang

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
B10.1	24	77235	1.440	6.22	83	32.53	25.32	7.09	1.17	16.7	9680	0.753	5.81	0.50	0.04	<0.003	0.769	140	0.040	0.019
B10.2	6	2842	0.080	0.02	32	6.6	24.37	<0.21	0.98	6.3	7086	0.02	0.21	<0.005	0.04	<0.003	0.277	163	0.037	0.013
B10.3	2	9394	0.010	0.02	137	5.19	127.88	<0.19	0.61	75.4	23400	0.001	0.14	<0.01	<0.04	<0.002	0.146	28	0.038	0.000
B10.4	13	18155	0.010	<0.02	80	6.59	72.67	<0.22	0.44	15.6	9077	0.327	2.68	<0.01	<0.04	0.002	0.762	120	0.025	0.004
B10.5	8	5221	<0.004	<0.02	3	0.68	16.95	<0.19	0.31	3.8	8244	0.004	0.36	<0.01	0.04	<0.004	0.797	150	0.041	<0.001
B10.6	3	3244	0.010	<0.02	169	11.27	9.53	<0.21	0.74	26.7	9960	0.153	1.62	<0.01	<0.04	<0.004	0.748	93	0.042	0.001
B10.7	8	11411	<0.005	<0.02	11	2.47	60.14	<0.21	0.55	6.2	4226	0.013	0.72	<0.01	0.04	<0.003	0.241	620	0.031	0.002
B10.8	4	985	0.220	1.51	<0.04	0.02	2.15	2.98	0.99	3.5	20621	0.011	0.32	<0.01	0.05	0.002	0.88	2427	0.223	0.449
B10.9	20	5419	0.140	<0.03	196	23.66	97.39	<0.38	0.66	43	20340	0.498	3.67	0.20	<0.09	<0.005	0.55	67	0.039	0.006
B10.10	3	3904	0.010	<0.02	39	8.65	6.71	<0.26	0.59	7.2	26998	0.015	0.36	<0.01	<0.08	<0.003	0.855	143	0.04	<0.001
B-6.1	9	16006	<0.003	<0.02	4	9.8	37.26	<0.25	0.53	4.1	13439	0.009	0.18	<0.01	<0.05	<0.004	0.771	145	0.017	0.004
B-6.2	10	10150	<0.004	<0.03	6	3.97	53.49	<0.25	0.42	4.2	7398	0.003	0.64	0.40	<0.06	<0.003	0.415	673	0.017	0.002
B-6.3	1	1033	0.020	<0.02	11	3.32	6.52	<0.20	0.26	4.8	6334	0.005	1.16	<0.01	<0.05	0.002	0.061	50	0.012	0.000
B-6.4	4	2349	<0.005	<0.02	17	7.28	22.81	<0.23	0.29	6.2	6607	0.086	1.05	<0.01	<0.07	<0.004	0.33	43	0.021	<0.001
B-6.5	2	2253	<0.005	<0.02	3	2.52	13.67	<0.29	0.16	3.8	10443	0.012	0.32	<0.01	<0.05	<0.003	0.402	61	0.012	<0.001
B-6.6	4	3167	0.100	<0.02	20	12.34	26.1	<0.32	0.43	5.7	9343	0.055	0.6	<0.01	<0.07	<0.005	0.271	174	0.023	0.001
B-6.7	1	1333	0.020	0.01	17	10.09	18.44	0.29	0.37	8.1	8301	0.01	0.83	<0.01	0.05	<0.005	0.172	108	0.027	<0.001
B-6.8	17	23399	0.350	0.48	38	12.85	59.44	0.97	0.37	7.5	10133	0.186	1.13	<0.01	<0.05	0.002	0.888	433	0.038	0.006
H-22.1	22	14018	0.010	<0.02	53	1.78	160	<0.28	0.56	4.4	9226	0	0.16	<0.01	<0.06	<0.003	7.9	238	0.029	0.001
H-22.2	7	2192	<0.006	<0.02	1	1.43	16.82	<0.24	0.40	4.5	15212	0	0.09	<0.01	<0.04	<0.003	1.6	179	0.026	<0.001
H-22.3	93	13068	2.070	0.01	194	48.32	187.45	3.27	0.40	5.5	8219	0.054	4.97	1.40	<0.05	<0.004	10.2	817	0.023	<0.001
H-22.4	214	29815	<0.005	0.02	302	2.76	546.7	3.52	0.50	8.3	956	0.005	0.98	0.10	0.04	<0.003	43.6	3493	0.021	0.001
H-22.5	225	36604	0.020	0.03	258	64.54	287.66	11.01	0.36	5.9	3697	0.193	12.3	0.80	0.05	<0.003	21.5	1316	0.02	<0.002
H-22.6	28	4696	<0.005	<0.02	90	0.87	120.36	<0.25	0.67	3.9	3527	0.001	0.14	<0.01	<0.08	<0.004	3.2	358	0.023	<0.001
H-22.7	4	2421	0.030	0.02	23	4.15	17.52	<0.24	0.41	3.7	10019	0.005	0.24	<0.01	<0.05	<0.005	2.1	151	0.026	<0.001
H-22.8	12	8043	<0.004	<0.02	69	5.05	124.81	<0.25	0.16	3.8	5369	0.01	0.4	<0.01	<0.07	<0.003	6.6	126	0.017	0.001

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
B10.1	0.0570	2.1473	0.0055	0.0246	0.0476	0.0032	0.1380	0.2735	0.2719	0.0053	0.0263	0.0023	0.0282	0.0087	0.0310	0.0030	0.0013	0.0038	0.0098	0.0010
B10.2	0.0615	1.9193	0.0039	0.0180	0.0465	0.0033	0.1377	0.2121	0.2037	0.0059	0.0367	0.0017	0.0260	0.0050	0.0305	0.0031	0.0015	0.0035	0.0079	0.0012
B10.3	0.0481	1.5094	0.0035	0.0093	0.0414	0.0023	0.1362	0.1937	0.2705	0.0032	0.0233	0.0013	0.0258	0.0061	0.0367	0.0021	0.0011	0.0044	0.0067	0.0011
B10.4	0.0564	2.0640	0.0026	0.0227	0.0486	0.0030	0.1497	0.2206	0.2347	0.0035	0.0363	0.0018	0.0238	0.0068	0.0416	0.0023	0.0018	0.0045	0.0084	0.0010
B10.5	0.0626	1.6291	0.0037	0.0160	0.0451	0.0024	0.1089	0.1926	0.2948	0.0069	0.0385	0.0015	0.0222	0.0072	0.0383	0.0036	0.0014	0.0043	0.0056	0.0008
B10.6	0.0546	1.6446	0.0021	0.0194	0.0470	0.0027	0.1298	0.2111	0.2162	0.0056	0.0466	0.0019	0.0198	0.0063	0.0375	0.0037	0.0016	0.0037	0.0063	0.0009
B10.7	0.0615	2.1980	0.0046	0.0158	0.0559	0.0035	0.1325	0.2080	0.2819	0.0062	0.0273	0.0009	0.0228	0.0075	0.0407	0.0030	0.0015	0.0043	0.0062	0.0007
B10.8	0.0542	1.4492	0.0030	0.0103	0.0441	0.0030	0.1272	0.1892	0.2525	0.0044	0.0320	0.0007	0.0172	0.0040	0.0190	0.0013	0.0010	0.0035	0.0044	0.0008
B10.9	0.1078	2.7989	0.0054	0.0274	0.0712	0.0069	0.1962	0.3792	0.4461	0.0082	0.0873	0.0024	0.0404	0.0106	0.0912	0.0047	0.0025	0.0082	0.0093	0.0016
B10.10	0.0500	1.8541	0.0034	0.0248	0.0636	0.0038	0.1483	0.2569	0.2832	0.0059	0.0444	0.0015	0.0217	0.0053	0.0815	0.0032	0.0016	0.0041	0.0065	0.0010
B-6.1	0.0755	1.7214	0.0032	0.0170	0.0455	0.0048	0.1572	0.2489	0.3053	0.0050	0.0586	0.0021	0.0198	0.0103	0.0466	0.0038	0.0016	0.0043	0.0057	0.0015
B-6.2	0.0779	1.9941	0.0041	0.0304	0.0397	0.0055	0.1371	0.2497	0.3633	0.0036	0.0511	0.0027	0.0294	0.0083	0.0625	0.0029	0.0019	0.0035	0.0062	0.0011
B-6.3	0.0699	1.8125	0.0024	0.0234	0.0565	0.0045	0.1310	0.2018	0.3147	0.0026	0.0353	0.0006	0.0229	0.0078	0.0482	0.0020	0.0014	0.0030	0.0084	0.0010
B-6.4	0.0784	1.6477	0.0047	0.0194	0.0499	0.0049	0.1325	0.2291	0.3080	0.0042	0.0546	0.0015	0.0252	0.0068	0.0654	0.0043	0.0019	0.0045	0.0047	0.0014
B-6.5	0.0668	2.0648	0.0053	0.0198	0.0599	0.0034	0.1563	0.2927	0.2464	0.0047	0.0579	0.0014	0.0269	0.0072	0.0534	0.0034	0.0010	0.0037	0.0061	0.0013
B-6.6	0.0730	1.6606	0.0059	0.0190	0.0725	0.0054	0.1364	0.3173	0.3544	0.0033	0.0440	0.0027	0.0336	0.0084	0.0719	0.0048	0.0007	0.0027	0.0059	0.0012
B-6.7	0.0721	1.5488	0.0039	0.0135	0.0553	0.0047	0.1355	0.2502	0.3600	0.0044	0.0471	0.0026	0.0272	0.0062	0.0391	0.0046	0.0014	0.0051	0.0058	0.0010
B-6.8	0.0705	1.7813	0.0054	0.0290	0.0682	0.0039	0.1501	0.2571	0.2969	0.0023	0.0518	0.0021	0.0246	0.0113	0.0536	0.0024	0.0022	0.0039	0.0052	0.0013
H-22.1	0.0589	1.6771	0.0021	0.0188	0.0654	0.0037	0.1695	0.2809	0.2878	0.0078	0.0420	0.0019	0.0237	0.0113	0.0576	0.0035	0.0022	0.0038	0.0052	0.0011
H-22.2	0.0672	1.4977	0.0057	0.0201	0.0559	0.0036	0.1407	0.2386	0.3128	0.0061	0.0435	0.0018	0.0294	0.0074	0.0418	0.0032	0.0019	0.0043	0.0055	0.0010
H-22.3	0.0758	2.0060	0.0042	0.0143	0.0570	0.0043	0.1455	0.2498	0.2553	0.0062	0.0561	0.0021	0.0294	0.0069	0.0486	0.0044	0.0018	0.0034	0.0051	0.0010
H-22.4	0.0785	2.0231	0.0052	0.0216	0.0733	0.0048	0.1421	0.3085	0.2985	0.0074	0.0582	0.0013	0.0238	0.0065	0.0446	0.0031	0.0016	0.0046	0.0069	0.0008
H-22.5	0.0708	1.8189	0.0052	0.0261	0.0611	0.0044	0.1779	0.2553	0.3593	0.0058	0.0634	0.0017	0.0295	0.0068	0.0487	0.0030	0.0016	0.0040	0.0058	0.0015
H-22.6	0.0734	1.5781	0.0046	0.0220	0.0505	0.0052	0.1262	0.2492	0.2764	0.0025	0.0420	0.0021	0.0310	0.0065	0.0791	0.0035	0.0025	0.0046	0.0058	0.0014
H-22.7	0.0710	1.6070	0.0031	0.0104	0.0528	0.0039	0.1712	0.2417	0.2825	0.0042	0.0704	0.0017	0.0272	0.0054	0.0487	0.0053	0.0023	0.0042	0.0058	0.0012
H-22.8	0.0844	1.6238	0.0040	0.0235	0.0568	0.0057	0.1386	0.2489	0.2947	0.0064	0.0496	0.0020	0.0255	0.0077	0.0651	0.0028	0.0022	0.0039	0.0060	0.0009

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
B10.1	4	14	17	17	4	4	4	13	19	4	3	4	4	6	43	193	5	11	15	11
B10.2	17	4	9	65	4	4	3	971	19	3	3	10	10	37	38	115	5	5	12	12
B10.3	4	4	25	49	3	4	3	144	33	3	3	68	13	290	68	188	4	3	10	3402
B10.4	4	4	36	239	3	5	3	1184	44	3	3	4	9	35	63	86	3	3	18	19
B10.5	4	4	192	254	12	8	4	65	71	3	6	26	14	59	47	20619	3	3	9	256
B10.6	5	4	33	570	3	4	4	104	23	3	3	7	7	31	97	125	3	4	9	51
B10.7	4	4	191	86	4	4	4	83	42	3	3	15	5	27	55	171	4	4	13	27
B10.8	4	7	6	5	13	14	5	5	21	4	4	11	8	12	25	58	3	4	4	5
B10.9	11	11	16	167	10	10	11	69	72	10	10	10	10	14	258	-	9	11	27	57
B10.10	4	4	29	6490	5	4	4	246	36	4	3	14	10	16	98	246	4	3	10	409
B-6.1	5	5	100	81	6	5	5	788	47	5	5	20	11	369	75	16671	4	5	21	21
B-6.2	5	5	1304	94	7	6	5	77	65	5	5	56	7	7	452	388	9	5	21	29
B-6.3	11	6	18	184	5	6	5	152	88	5	5	18	6	17	77	57	7	10	35	3029
B-6.4	5	6	152	388	5	6	5	150	79	5	4	11	10	34	132	227	5	5	15	89
B-6.5	11	8	205	402	8	10	8	115	124	5	5	15	14	968	82	120	6	5	29	210
B-6.6	6	5	9	89	6	6	5	90	60	5	5	13	12	35	198	213	7	5	16	86
B-6.7	8	6	21	131	5	6	5	47	71	5	5	19	7	25	39	50	7	8	14	140

B-6.8	6	6	11	18	6	6	5	15	59	5	5	16	13	22	267	82	5	7	10	17
H-22.1	5	5	27	169	5	6	5	102	40	5	5	255	12	384	217	262	4	5	12	55
H-22.2	5	5	169	1141	9	6	5	107	56	5	5	417	20	844	56	437	4	5	14	242
H-22.3	5	5	5	72	5	6	5	7	48	5	5	7	5	6	64	370	5	6	17	376
H-22.4	5	5	153	78	5	6	5	7	45	5	5	25	5	10	50	137	4	6	18	60
H-22.5	5	5	23	66	5	6	5	5	70	5	5	6	5	5	48	194	4	5	18	227
H-22.6	6	5	231	113	5	8	5	97	30	5	5	133	15	91	180	68	5	5	15	82
H-22.7	6	5	14	56	5	9	5	340	50	5	5	26	11	174	150	120	4	5	14	133
H-22.8	6	5	5777	677	5	6	5	263	158	5	4	17	9	638	107	94	4	5	22	49

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
B10.1	3	14	16	17	3	3	3	9	5	2	1	3	2	5	23	27	5	10	4	10
B10.2	14	3	7	24	2	1	1	2	6	1	1	8	4	17	19	43	4	3	3	10
B10.3	1	1	14	29	1	1	1	2	6	1	1	22	4	18	18	32	3	0	3	27
B10.4	1	2	21	25	1	3	1	2	7	1	1	3	8	16	19	23	2	1	4	13
B10.5	1	1	23	32	11	7	1	2	8	1	5	16	10	17	19	28	1	1	4	32
B10.6	3	2	23	29	1	2	2	3	7	1	1	6	5	13	22	38	2	3	4	23
B10.7	2	2	38	25	2	1	2	2	10	1	1	13	3	19	21	28	3	2	4	19
B10.8	2	6	5	4	6	8	2	2	6	2	1	10	5	10	19	32	1	1	2	3
B10.9	7	8	13	75	7	6	8	7	21	6	6	7	6	11	55	70	5	8	14	52
B10.10	1	1	17	28	4	1	1	3	7	2	1	12	7	13	22	32	3	1	4	22
B-6.1	1	1	31	25	3	1	1	2	10	2	1	13	5	18	19	23	2	0	5	12
B-6.2	2	2	36	38	4	2	1	3	9	2	1	16	3	5	23	38	8	3	6	16
B-6.3	3	3	15	31	1	1	1	3	7	1	1	16	3	10	19	26	5	8	5	25
B-6.4	2	3	22	38	2	2	1	3	7	1	1	9	7	15	17	22	3	2	5	30
B-6.5	7	6	24	28	6	8	6	3	9	1	2	12	8	22	21	34	5	3	6	22
B-6.6	2	2	7	27	4	3	1	3	8	2	2	11	8	15	30	28	6	2	6	21
B-6.7	3	4	16	37	2	2	2	2	9	1	2	11	4	15	21	44	5	6	5	27
B-6.8	3	4	9	16	3	3	2	2	9	3	3	15	11	12	21	27	3	5	4	13
H-22.1	1	1	22	31	1	3	1	3	9	1	0	46	4	21	25	24	1	1	4	20
H-22.2	2	2	32	36	5	2	2	3	8	2	1	25	5	26	22	32	2	1	5	27
H-22.3	2	2	2	30	1	1	2	3	8	2	1	5	2	3	22	34	3	3	7	34
H-22.4	1	1	29	24	1	2	1	2	9	1	1	17	2	8	19	25	1	4	5	25
H-22.5	2	2	15	20	1	1	1	2	8	1	1	3	1	3	24	44	1	2	6	27
H-22.6	3	2	42	24	3	6	2	2	7	2	1	22	5	21	24	22	3	1	5	33
H-22.7	2	1	12	36	1	7	1	3	8	2	1	14	5	26	26	27	2	1	6	25
H-22.8	3	2	49	39	3	1	2	3	15	2	1	11	6	30	27	35	2	2	8	26

8. Mengxing

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1M1	43	7227	0.11	<0.21	111	2.49	9.73	23.29	<3.76	4.3	8231	<0.015	0.31	83	1.12	<0.047	4.6	563	0.061	<0.012
1M2	14	11744	2.38	38	172	3.89	30.39	112.49	0.75	4.2	12594	0.014	0.23	85	<0.10	<0.008	9.2	775	0.061	0.046

1M3	7	7513	0.13	<0.35	201	4.38	53.89	38.13	<2.56	4.2	12745	<0.017	0.36	76	<0.33	<0.048	12.8	168	0.033	<0.014
1M4	7	6816	0.06	<0.03	143	7.09	24.77	16.62	0.87	4.5	10428	0.038	0.46	90	<0.06	<0.005	4.6	160	0.033	0.018
1M5	16	11407	0.44	2.06	184	2.24	4.27	34.76	0.65	4	10285	0.010	0.43	52	0.14	<0.006	7.2	714	0.274	<0.002
1M6	11	8692	1.08	6.29	169	1.79	23.59	181.71	0.96	4.3	9509	0.013	0.19	69	<0.06	<0.004	8.7	481	0.029	0.002
1M7	37	9060	0.37	1.17	130	4.93	14.89	94.65	0.30	5.1	9208	0.016	0.36	113	<0.08	<0.006	3.6	3031	0.097	0.002
1M8	88	6910	0.9	0.12	191	1.47	37.45	34.03	0.49	4	7522	0.002	0.1	45	<0.10	<0.010	18.1	400	0.013	0.012
1M9	10	6556	1.03	2.02	132	3.39	56.66	158.36	0.68	4.1	7078	0.004	0.11	158	<0.07	<0.007	14.4	530	0.039	0.002
1M10	168	14789	1.66	6.87	123	1.39	12.24	577.5	1.13	4.7	7048	0.004	0.16	108	<0.08	<0.008	4.9	2903	0.017	0.016
M-11.1	19	132	2.09	0.05	4	2.98	2.33	0.89	0.81	3.8	16409	<0.002	0.1	1	<0.05	<0.003	6.2	340	0.033	0.005
M-11.2	490	173	2.5	0.11	3	0.49	3	1.72	0.37	4.1	13875	0.002	0.11	2.6	0.08	0.003	11	346	0.068	0.245
M-11.3	13	79	2.33	0.04	4	0.36	2.67	1.1	0.75	3.9	16509	0.003	0.1	1.3	<0.09	<0.003	9.3	364	0.037	0.011
M-11.4	180	712	4.67	1.42	7	0.5	2.81	4.98	0.90	4.1	14191	0.002	0.13	1.4	<0.05	<0.003	6.5	326	0.049	0.117
M-11.5	24	3477	16.95	3.25	7	1.19	3.33	31.7	0.36	4.8	16560	0.005	0.24	3.4	<0.06	<0.003	6.8	400	0.069	0.338
M-11.6	1451	389	2.2	0.29	5	0.55	3.28	3.63	0.57	4.5	15617	0.004	0.09	3.3	<0.11	<0.006	12.4	382	0.122	0.374
M-11.7	60	186	1.9	0.07	4	0.37	2.83	2.64	0.44	4.3	15156	0.002	0.13	1.3	<0.07	<0.004	11.4	586	0.037	0.089
M-11.8	12	97	1.95	<0.02	2	0.22	2.28	0.15	0.71	3.9	15460	0.002	0.1	0.5	<0.08	<0.004	5.1	346	0.036	0.003

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1M1	0.6882	11.5670	0.0481	0.2132	0.9248	0.0805	1.3294	1.5606	3.7626	0.0410	0.4846	0.0146	0.1986	0.0715	0.5348	0.0469	0.0127	0.0295	0.0481	0.0117
1M2	0.0692	1.2213	0.0041	0.0325	0.1032	0.0098	0.1515	0.2043	0.2804	0.0074	0.0429	0.0016	0.0250	0.0127	0.0985	0.0081	0.0024	0.0029	0.0076	0.0018
1M3	0.5489	8.8968	0.0335	0.3507	0.6420	0.0652	1.3816	1.4031	2.5591	0.0420	0.4407	0.0174	0.1765	0.0665	0.3271	0.0480	0.0172	0.0230	0.0448	0.0138
1M4	0.0677	1.2005	0.0068	0.0306	0.0957	0.0089	0.1421	0.1960	0.3394	0.0081	0.0383	0.0019	0.0256	0.0095	0.0615	0.0048	0.0020	0.0048	0.0059	0.0016
1M5	0.0610	1.4863	0.0072	0.0350	0.0985	0.0072	0.1395	0.1591	0.2942	0.0068	0.0339	0.0029	0.0224	0.0107	0.0496	0.0061	0.0017	0.0036	0.0049	0.0021
1M6	0.0815	1.5237	0.0045	0.0276	0.0875	0.0091	0.1478	0.1868	0.3319	0.0026	0.0308	0.0022	0.0173	0.0098	0.0593	0.0042	0.0019	0.0033	0.0062	0.0014
1M7	0.0626	1.3415	0.0054	0.0118	0.1023	0.0094	0.1932	0.1854	0.2970	0.0038	0.0460	0.0019	0.0218	0.0098	0.0834	0.0065	0.0024	0.0033	0.0052	0.0015
1M8	0.0611	1.1934	0.0045	0.0284	0.0798	0.0073	0.1451	0.1701	0.3558	0.0045	0.0416	0.0017	0.0220	0.0098	0.0954	0.0096	0.0023	0.0045	0.0052	0.0018
1M9	0.0666	1.1116	0.0073	0.0216	0.0763	0.0090	0.1924	0.2188	0.2814	0.0050	0.0343	0.0012	0.0174	0.0087	0.0690	0.0070	0.0020	0.0048	0.0061	0.0013
1M10	0.0885	1.4772	0.0069	0.0244	0.0705	0.0076	0.2010	0.2083	0.3302	0.0049	0.0339	0.0024	0.0312	0.0139	0.0766	0.0078	0.0021	0.0034	0.0061	0.0015
M-11.1	0.0595	1.5850	0.0052	0.0221	0.0506	0.0026	0.1527	0.2558	0.2254	0.0038	0.0296	0.0019	0.0238	0.0078	0.0550	0.0028	0.0017	0.0046	0.0065	0.0007
M-11.2	0.0528	1.4773	0.0047	0.0208	0.0532	0.0046	0.1327	0.2994	0.2766	0.0023	0.0544	0.0015	0.0342	0.0090	0.0400	0.0020	0.0019	0.0062	0.0064	0.0009
M-11.3	0.0625	1.5467	0.0035	0.0185	0.0528	0.0026	0.1209	0.2206	0.2802	0.0039	0.0562	0.0007	0.0238	0.0070	0.0876	0.0032	0.0013	0.0061	0.0055	0.0010
M-11.4	0.0614	1.8151	0.0040	0.0188	0.0543	0.0035	0.1614	0.2175	0.3414	0.0049	0.0564	0.0021	0.0251	0.0071	0.0475	0.0030	0.0022	0.0046	0.0080	0.0016
M-11.5	0.0529	1.1743	0.0049	0.0189	0.0474	0.0043	0.1265	0.2287	0.2936	0.0049	0.0409	0.0022	0.0207	0.0095	0.0594	0.0026	0.0022	0.0053	0.0058	0.0012
M-11.6	0.0846	2.4761	0.0039	0.0311	0.0610	0.0066	0.2114	0.3722	0.3991	0.0110	0.0683	0.0023	0.0310	0.0104	0.1060	0.0064	0.0031	0.0068	0.0095	0.0016
M-11.7	0.0587	1.5735	0.0026	0.0242	0.0554	0.0069	0.1317	0.2826	0.2919	0.0053	0.0392	0.0010	0.0245	0.0066	0.0669	0.0038	0.0011	0.0048	0.0061	0.0015
M-11.8	0.0536	1.5557	0.0031	0.0208	0.0826	0.0029	0.1591	0.2535	0.3340	0.0034	0.0341	0.0009	0.0225	0.0043	0.0779	0.0041	0.0015	0.0039	0.0062	0.0011

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1M1	19	8	30	110	8	10	12	9	55	8	7	131	43	7	38	168	8	8	46	58
1M2	8	8	11	10	7	8	8	9	33	7	7	16	11	7	86	94	8	11	11	12
1M3	9	8	26	85	7	9	8	12	146	8	7	127	34	7	58	347	8	8	75	254
1M4	8	7	14	1313	8	8	8	8	33	7	7	11	9	7	106	249	10	8	15	36
1M5	8	10	20	21	8	9	8	12	35	7	7	22	10	7	25	169	7	8	20	81
1M6	8	8	17	33	8	9	9	13	28	7	7	15	12	8	74	175	8	14	15	42

1M7	13	8	13	16	7	9	8	12	75	7	7	13	10	7	111	1154	7	11	9	34
1M8	14	8	8	32	8	9	8	8	55	7	7	71	17	7	97	74	8	7	26	21
1M9	9	8	11	24	7	9	9	18	33	7	7	25	19	19	126	148	7	17	17	41
1M10	18	8	14	13	7	9	8	14	26	7	7	40	16	10	240	284	8	11	23	24
M-11.1	8	6	4	36	6	20	4	18	22	3	3	109	17	5	293	108	3	3	12	14
M-11.2	7	5	4	19	9	5	5	11	56	4	4	46	21	4	29	44	4	4	8	14
M-11.3	7	5	4	36	5	5	4	12	28	3	3	24	17	4	412	324	3	4	11	14
M-11.4	8	9	6	8	4	5	5	9	29	4	3	63	14	4	73	110	3	3	10	28
M-11.5	8	9	7	9	5	8	4	8	61	4	5	31	9	5	148	169	3	4	8	7
M-11.6	9	6	6	15	7	7	6	9	55	6	6	37	26	6	70	171	6	6	7	9
M-11.7	8	6	4	37	6	7	5	7	49	3	4	39	14	4	943	1160	3	4	12	30
M-11.8	9	5	4	158	7	6	5	87	36	3	3	39	16	4	167	293	3	3	11	42

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
1M1	15	2	14	24	3	6	4	2	10	4	1	26	8	2	27	23	3	2	8	21
1M2	2	3	8	7	2	2	4	5	9	2	1	12	4	1	18	28	3	9	4	9
1M3	2	1	17	28	2	4	3	7	11	3	1	23	8	1	27	26	4	3	7	25
1M4	3	1	10	36	3	1	3	4	10	2	1	7	4	2	24	29	7	3	7	33
1M5	1	6	18	19	5	2	1	10	9	2	1	12	5	1	17	20	1	2	18	18
1M6	3	3	15	32	3	4	4	11	9	2	1	9	6	3	21	34	3	12	6	21
1M7	10	3	11	14	1	2	2	9	9	2	1	9	4	1	18	27	1	8	5	17
1M8	12	1	3	21	3	4	4	4	10	2	1	23	5	3	21	27	4	1	7	16
1M9	4	3	8	23	2	3	5	16	9	1	1	17	10	17	28	25	2	15	10	19
1M10	17	4	12	11	1	4	3	12	10	2	1	15	6	6	29	27	4	9	6	20
M-11.1	7	5	2	20	5	19	1	3	7	1	1	23	5	4	21	25	1	0	4	12
M-11.2	5	3	2	14	8	2	2	3	7	2	2	22	5	2	18	26	2	1	4	14
M-11.3	5	2	3	22	4	3	2	2	7	1	0	20	5	3	23	30	1	1	5	12
M-11.4	7	8	5	7	2	3	2	6	8	2	1	17	4	3	22	40	1	1	4	27
M-11.5	7	8	6	8	3	7	1	7	8	2	3	15	5	4	21	31	1	2	4	6
M-11.6	7	4	3	13	5	4	2	3	10	4	3	20	6	3	17	23	4	4	3	7
M-11.7	7	4	2	24	5	5	2	2	9	1	2	28	5	3	20	27	2	1	5	29
M-11.8	8	3	2	25	5	3	2	3	9	1	1	23	6	3	24	22	1	1	4	29

9. Jinding

Measured concentrations (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Jind 0091-2.9	52	338	8.6	0.68	7	1.73	9.83	8.62	1.1	52.5	9683	0.004	0.19	3.0	<0.09	0.007	11.6	298	0.03	0.23
Jind 0091-2.10	774	714	19	0.62	8	0.77	8.12	34.45	1.6	17.4	7011	0.004	0.14	1.6	<0.08	<0.007	22.5	690	0.02	0.46
Jind 0091-2.11	638	661	21	0.58	4	0.75	6.91	16.89	0.6	20.3	5157	0.002	0.14	1.4	<0.06	<0.007	19.7	469	0.02	0.55
Jind 0091-2.12	1937	1120	20	1.26	4	1.15	7.39	11.84	3.7	21.1	6330	<0.016	0.30	1.4	<0.80	<0.073	12.8	340	<0.05	0.47
Jind 0091-2.13	97	541	26	0.50	5	0.58	7.84	25.79	<2.5	40	6287	<0.015	<0.18	1.5	<0.42	<0.037	14.5	492	<0.04	0.30
Jind 0091-2.14	554	445	20	0.65	5	1.05	9.22	12.33	1.2	34.3	7033	0.002	0.18	2.0	<0.06	<0.007	15.8	268	0.03	0.24
Jind 0091-2.15	72	300	17	0.46	6	1.03	8.72	9.21	<2.5	30.7	6882	<0.014	0.22	1.8	<0.38	<0.045	17.4	211	0.06	0.23

Jind 0091-2.16	184	529	11	0.37	6	0.61	12.13	29.38	<3.0	27.1	4106	<0.014	0.25	3.8	<0.53	<0.042	23.9	1099	<0.04	0.06
150Jind1	11	206	4.43	<0.36	1104	0.9	2.51	2.15	<3.4	43.6	21270	<0.013	<0.22	5.2	<0.43	<0.057	2.1	4002	<0.07	<0.01
150Jind2	178	1850	1.83	<0.21	31	3.94	3.3	13.08	<3.2	4.9	250	<0.013	<0.20	3.5	<0.45	<0.052	11.4	247	<0.06	<0.02
150Jind3	50	413	4.82	<0.37	2410	0.37	3.06	3.27	<2.5	136.2	23075	<0.013	<0.19	5.5	<0.52	<0.046	9.2	9064	<0.08	<0.01
150Jind4	196	2074	1.74	<0.17	525	2.92	2.96	21.88	<3.5	12.6	187	<0.021	0.28	5.4	<0.49	<0.064	18.5	577	<0.07	<0.01
150Jind5	141	3105	5.25	0.21	1268	0.47	7.17	84.66	3.17	28.6	374	<0.015	<0.19	10.3	<0.73	<0.047	22.1	553	<0.06	<0.02
150Jind6	129	1522	0.73	<0.19	2798	4.44	2.27	18.23	2.57	66.9	10349	0.161	12.3	2.6	<0.62	<0.049	15	1497	0.70	0.97
150Jind7	212	2692	6.77	5.73	1902	7.24	1.82	39.45	<7.3	56.6	10297	<0.054	5.91	2.7	<1.27	<0.107	12.5	4267	0.58	0.35
150Jind8	72	1999	3.01	<0.27	1206	7.05	4.06	25.28	0.39	49	6493	0.033	1.97	4.1	<0.53	<0.040	10	12955	<0.05	0.04
JD148.1	309	2624	3.6	2.24	2	0.59	75.11	<6.78	<9.0	3.8	1279	<0.057	1.65	0.5	<1.59	<0.171	12.9	249	<0.28	<0.05
JD148.2	41	910	1.38	0.44	<3	1.95	18.62	23.11	<9.2	3.8	18742	<0.045	<0.74	0.8	<2.37	0.146	11.1	238	<0.26	<0.06
JD148.4	6	66	0.07	<1.06	6	1.25	5.42	<7.10	<8.9	5.6	59666	0.097	<0.70	0.6	<1.58	<0.181	2	76	<0.23	<0.05
JD148.5	21	53	1.16	<0.61	4	1.23	10.02	<6.39	<9.3	4.1	44128	1.303	<0.72	1.5	<2.76	<0.176	4.8	92	<0.17	0.05
JD148.6	57	895	1.07	<1.05	1	1.89	27.33	30.39	8.5	3.4	19367	1.384	<0.90	0.9	<1.84	<0.115	10.9	338	<0.21	<0.05
JD148.7	1	56	1.09	<1.08	2	0.38	5.1	<7.54	<10.4	3.9	36541	0.19	<0.68	<0.3	1.52	<0.195	2.5	54	<0.21	<0.07
JD148.8	2	89	<0.26	0.81	<3	2.03	3.87	<6.67	<9.8	3.7	68552	<0.052	<0.97	<0.4	<2.56	<0.244	2.9	68	<0.21	<0.04
155-26.1	1	1296	0.18	0.02	33	3.17	6.69	32.29	0.4	3.9	17468	0.004	0.17	18.5	<0.06	<0.004	4.3	145	0.03	<0.001
155-26.2	5	2064	0.2	<0.03	85	0.41	5.72	20.18	0.4	3.9	17842	0.002	0.13	25.7	0.04	<0.004	12.8	719	0.03	<0.001
155-26.3	23	2381	0.46	0.08	94	5.79	3.76	20.56	0.7	3.8	35684	0.012	0.30	26.7	<0.07	<0.003	10.7	443	0.05	0.04
155-26.4	34	3283	0.31	0.02	113	10.87	10.35	37.63	0.3	4.6	16240	0.003	0.27	58.8	0.04	<0.003	23	767	0.03	0.01
155-26.5	6	1734	0.16	0.04	114	4.47	8.43	48.33	0.5	4.1	20461	0.005	0.13	35.5	0.06	<0.003	25	679	0.03	<0.001
155-26.6	1	1773	0.21	0.06	118	3.02	3.1	12.93	0.3	3.8	20631	0.002	0.13	15.3	<0.07	<0.002	6.2	257	0.03	<0.002
155-26.7	15	3625	0.02	0.03	122	1.97	56.28	257.86	0.8	6.3	6592	0.003	0.16	159.9	<0.09	<0.005	73.3	3931	0.04	<0.001
155-26.8	8	2316	1.11	0.33	104	5.74	4.75	57.07	0.5	5.1	30621	0.018	0.55	30.4	<0.06	<0.004	15.4	360	0.04	0.03

Detection limits (ppm)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Jind 0091-2.9	0.0737	1.5813	0.0086	0.0196	0.1028	0.0094	0.2072	0.2847	0.3886	0.0083	0.0464	0.0016	0.0318	0.0121	0.0922	0.0042	0.0030	0.0049	0.0052	0.0023
Jind 0091-2.10	0.0908	1.3249	0.0059	0.0341	0.0877	0.0096	0.1787	0.2270	0.3287	0.0073	0.0584	0.0024	0.0303	0.0059	0.0810	0.0069	0.0028	0.0040	0.0053	0.0025
Jind 0091-2.11	0.0928	1.5354	0.0061	0.0349	0.0901	0.0096	0.2145	0.2378	0.3598	0.0068	0.0330	0.0025	0.0247	0.0117	0.0647	0.0074	0.0033	0.0041	0.0065	0.0022
Jind 0091-2.12	0.8906	10.4772	0.0668	0.3626	0.9620	0.0899	1.7015	1.8069	3.5643	0.0746	0.3723	0.0159	0.2684	0.1244	0.7981	0.0728	0.0384	0.0364	0.0469	0.0130
Jind 0091-2.13	0.5380	9.7513	0.0501	0.1775	0.5500	0.0741	1.1872	1.5249	2.5143	0.0387	0.2885	0.0151	0.1770	0.0737	0.4151	0.0370	0.0228	0.0258	0.0372	0.0121
Jind 0091-2.14	0.0704	1.8012	0.0078	0.0242	0.1211	0.0131	0.2183	0.2287	0.3047	0.0087	0.0526	0.0018	0.0276	0.0075	0.0581	0.0067	0.0031	0.0049	0.0072	0.0021
Jind 0091-2.15	0.6333	10.4333	0.0212	0.3872	0.8494	0.0574	1.7126	1.9429	2.5037	0.0884	0.4368	0.0136	0.2168	0.0879	0.3750	0.0448	0.0305	0.0383	0.0427	0.0134
Jind 0091-2.16	0.6358	10.7287	0.0571	0.2706	0.6715	0.0623	1.2734	1.8413	3.0378	0.0640	0.3267	0.0135	0.1851	0.0701	0.5282	0.0417	0.0326	0.0345	0.0358	0.0156
150Jind1	0.5821	8.8154	0.0561	0.3552	0.7457	0.0629	1.1444	1.3603	3.3876	0.0587	0.4338	0.0131	0.2183	0.0869	0.4276	0.0567	0.0126	0.0339	0.0695	0.0114
150Jind2	0.6033	8.0979	0.0452	0.2106	0.7352	0.0582	1.1971	1.4985	3.1810	0.0361	0.2583	0.0134	0.2005	0.0821	0.4549	0.0521	0.0175	0.0443	0.0589	0.0157
150Jind3	0.6161	10.0176	0.0305	0.3652	0.5737	0.0730	1.4199	1.3985	2.5315	0.0502	0.3526	0.0132	0.1851	0.0695	0.5179	0.0457	0.0150	0.0425	0.0796	0.0116
150Jind4	0.7291	11.6643	0.0397	0.1736	0.7883	0.1071	1.4082	1.6026	3.5059	0.0707	0.3479	0.0209	0.1843	0.0363	0.4894	0.0637	0.0184	0.0385	0.0683	0.0142
150Jind5	0.5960	10.8082	0.0622	0.1292	0.9134	0.0578	1.2452	1.6155	2.7834	0.0603	0.3574	0.0146	0.1895	0.0785	0.7276	0.0470	0.0160	0.0295	0.0641	0.0150
150Jind6	0.6308	11.7690	0.0410	0.1890	0.7844	0.0755	1.7563	1.4728	2.3936	0.0526	0.2614	0.0140	0.1851	0.0635	0.6215	0.0492	0.0150	0.0271	0.0643	0.0108
150Jind7	1.5412	19.0281	0.0794	0.6006	1.9895	0.2183	3.3626	4.0927	7.3039	0.1457	0.5475	0.0541	0.4618	0.1739	1.2707	0.1074	0.0593	0.1102	0.1422	0.0311
150Jind8	0.5013	8.7015	0.0479	0.2748	0.8069	0.0566	1.1547	1.6115	2.5830	0.0659	0.3149	0.0135	0.2318	0.0809	0.5305	0.0400	0.0205	0.0406	0.0476	0.0096
JD148.1	2.4767	39.8853	0.1799	0.6918	2.5482	0.3083	6.0825	6.7776	8.9966	0.1432	1.1143	0.0570	0.8436	0.2505	1.5886	0.1712	0.0915	0.1270	0.2818	0.0472
JD148.2	2.6412	41.0356	0.1924	0.3845	2.9800	0.3285	6.0985	8.1418	9.2092	0.2181	0.8767	0.0448	0.7423	0.3272	2.3703	0.1021	0.0762	0.1427	0.2606	0.0627
JD148.4	2.3687	31.8174	0.3259	1.0563	2.1836	0.1738	5.3080	7.0972	8.8723	0.1436	1.4222	0.0474	0.6954	0.2712	1.5817	0.1810	0.0739	0.1277	0.2298	0.0489
JD148.5	2.2702	38.7825	0.2080	0.6079	2.5173	0.2059	4.9065	6.3891	9.2684	0.1444	0.8174	0.0345	0.7235	0.3110	2.7603	0.1756	0.0612	0.1508	0.1658	0.0351
JD148.6	2.8768	35.5253	0.1842	1.0471	2.9413	0.3234	4.4952	7.6173	7.7020	0.1694	1.4629	0.0684	0.9021	0.3614	1.8395	0.1146	0.0607	0.0831	0.2143	0.0532
JD148.7	2.5216	38.4937	0.1434	1.0836	2.1674	0.3417	4.9879	7.5449	10.4169	0.2131	1.3897	0.0481	0.6843	0.2535	1.2804	0.1950	0.0606	0.1068	0.2148	0.0724
JD148.8	3.0533	33.9606	0.2633	0.6642	3.3805	0.2750	6.5708	6.6669	9.8453	0.2418	1.3570	0.0516	0.9662	0.3938	2.5565	0.2438	0.0586	0.0880	0.2121	0.0412

155-26.1	0.0693	1.4923	0.0042	0.0127	0.0423	0.0038	0.1794	0.1894	0.3100	0.0046	0.0326	0.0020	0.0273	0.0088	0.0649	0.0041	0.0013	0.0048	0.0073	0.0013
155-26.2	0.0666	1.4077	0.0053	0.0257	0.0440	0.0040	0.1371	0.2275	0.2774	0.0056	0.0692	0.0014	0.0157	0.0092	0.0378	0.0040	0.0023	0.0047	0.0071	0.0012
155-26.3	0.0599	1.9954	0.0057	0.0201	0.0687	0.0051	0.1776	0.2855	0.2012	0.0074	0.0469	0.0016	0.0194	0.0052	0.0670	0.0034	0.0021	0.0055	0.0058	0.0013
155-26.4	0.0792	1.6995	0.0047	0.0161	0.0661	0.0038	0.1597	0.2189	0.3325	0.0048	0.0562	0.0021	0.0228	0.0063	0.0395	0.0035	0.0023	0.0048	0.0068	0.0012
155-26.5	0.0782	1.6037	0.0043	0.0218	0.0537	0.0042	0.1387	0.2450	0.3582	0.0043	0.0536	0.0012	0.0282	0.0063	0.0344	0.0027	0.0017	0.0039	0.0060	0.0014
155-26.6	0.0679	1.7567	0.0038	0.0130	0.0635	0.0036	0.1299	0.2354	0.2472	0.0042	0.0661	0.0023	0.0213	0.0087	0.0675	0.0023	0.0026	0.0059	0.0056	0.0016
155-26.7	0.0767	2.0662	0.0060	0.0110	0.0678	0.0043	0.1935	0.2495	0.3296	0.0059	0.0548	0.0021	0.0238	0.0068	0.0859	0.0046	0.0023	0.0055	0.0085	0.0015
155-26.8	0.0732	1.6451	0.0041	0.0140	0.0560	0.0063	0.1882	0.2120	0.3610	0.0050	0.0597	0.0011	0.0199	0.0101	0.0551	0.0044	0.0025	0.0080	0.0067	0.0016

Analytical precision (1 sigma, %)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Jind 0091-2.9	8	9	7	12	6	7	6	7	29	5	5	36	13	5	730	43	5	5	13	9
Jind 0091-2.10	10	6	5	14	7	7	6	5	18	6	6	43	16	6	284	270	5	5	18	9
Jind 0091-2.11	6	8	6	15	8	7	6	6	44	6	5	104	14	6	72	238	5	5	18	8
Jind 0091-2.12	8	8	7	30	19	11	11	13	70	9	7	237	54	11	5783	175	9	8	225	13
Jind 0091-2.13	8	6	5	33	10	12	9	7	85	6	5	153	135	8	59	93	5	6	228	15
Jind 0091-2.14	14	6	6	24	7	7	6	8	24	6	6	53	12	6	52	101	5	6	15	8
Jind 0091-2.15	6	9	6	55	15	10	9	14	100	5	5	109	60	8	85	2056	5	5	41	18
Jind 0091-2.16	8	7	5	53	12	12	7	7	169	5	4	391	48	6	57	417	5	5	110	23
150Jind1	10	8	8	202	7	10	21	35	78	7	7	154	69	8	174	324	7	20	1890	371
150Jind2	7	7	8	1658	14	9	17	10	610	8	8	119	157	9	254	66	6	7	87	153
150Jind3	14	8	8	22140	7	18	19	25	77	8	6	224	83	7	118	212	7	14	111	213
150Jind4	7	7	11	112	7	10	24	9	181	8	7	97	48	7	793	280	6	7	195	84
150Jind5	7	9	10	53	7	15	12	9	65	7	9	178	77	7	65	1733	6	7	165	454
150Jind6	7	8	12	256	7	9	29	9	70	8	7	12	11	8	413	353	7	7	10	13
150Jind7	14	13	15	34	15	13	75	15	182	15	15	97	15	16	499	192	15	14	20	16
150Jind8	10	13	8	184	7	9	15	13	470	7	7	35	11	9	271	269	9	8	172	19
JD148.1	15	12	24	32	83	42	12	83	691	13	21	67	36	33	166	89	11	12	92	325
JD148.2	12	13	20	75	2440	18	17	22	101	13	10	83	247	27	81	52	12	11	184	62
JD148.4	29	31	286	347	26	18	39	694	111	12	10	38	130	29	159	118	12	11	551	218
JD148.5	20	45	21	74	42	19	24	143	216	12	10	14	1615	21	66	206	13	11	65	37
JD148.6	11	12	24	95	257	19	13	18	68	13	11	13	1068	25	85	184	11	11	153	494
JD148.7	141	43	18	84	65	59	41	367	65	13	10	24	97	869	42	479	11	11	286	50
JD148.8	115	27	113	59	53	16	64	264	124	13	10	847	71	267	165	109	12	11	145	150
155-26.1	8	4	7	51	6	16	8	8	53	4	3	32	12	8	118	5869	7	7	16	68
155-26.2	5	4	6	456	4	7	4	4	55	4	3	65	11	7	49	80	4	3	14	143
155-26.3	9	4	5	21	4	5	4	4	29	3	3	14	7	4	73	543	3	3	8	17
155-26.4	4	4	5	72	4	7	4	4	68	3	3	44	8	4	43	123	3	4	14	41
155-26.5	8	4	7	46	4	6	4	4	49	3	3	24	15	4	34	391	3	4	13	630
155-26.6	7	4	6	23	5	6	4	4	66	4	3	64	12	4	54	114	5	4	12	445
155-26.7	5	4	31	57	4	6	4	6	34	3	3	58	15	12	287	130	5	9	13	187
155-26.8	4	4	5	19	3	6	6	3	54	3	3	11	8	4	69	302	3	3	10	11

SG Error (%)

Spot	Mn	Fe	Co	Ni	Cu	Ga	Ge	As	Se	Ag	Cd	In	Sn	Sb	Te	Au	Tl	Pb	Bi	U
Jind 0091-2.9	6	7	5	10	3	3	1	4	8	2	2	23	6	2	26	20	2	2	7	7

Jind 0091-2.10	9	2	1	12	4	4	2	1	8	3	3	20	5	3	25	30	2	1	7	7
Jind 0091-2.11	4	6	2	12	6	3	2	3	9	3	2	23	5	3	24	27	2	2	7	7
Jind 0091-2.12	6	5	4	19	7	7	2	4	11	7	4	33	7	8	23	34	7	5	9	12
Jind 0091-2.13	6	3	2	21	5	8	2	3	13	3	2	36	7	5	21	23	2	3	8	13
Jind 0091-2.14	13	4	3	23	4	3	3	5	10	3	3	23	6	4	22	22	2	4	6	6
Jind 0091-2.15	3	6	4	20	9	7	2	4	11	2	2	28	8	6	29	28	3	2	9	16
Jind 0091-2.16	6	4	2	18	6	9	2	3	14	2	1	32	9	4	21	28	2	2	10	17
150Jind1	4	3	4	27	2	5	2	3	9	2	2	34	6	4	26	23	3	19	6	22
150Jind2	1	1	4	34	11	4	2	3	11	4	4	31	7	6	32	37	2	1	7	25
150Jind3	10	3	4	20	2	10	2	3	10	5	1	37	8	3	29	24	3	12	6	23
150Jind4	1	1	8	51	3	6	4	4	18	4	3	71	10	4	60	34	2	1	14	71
150Jind5	2	5	7	30	1	10	3	5	11	2	6	34	7	3	47	34	2	1	8	19
150Jind6	2	3	9	32	1	5	2	3	10	4	3	9	8	4	23	28	4	2	5	11
150Jind7	7	5	9	29	9	5	3	5	13	10	10	19	7	9	27	23	9	8	7	10
150Jind8	7	11	5	31	3	4	3	8	11	1	2	20	5	5	24	30	6	5	8	13
JD148.1	9	6	21	20	8	18	3	4	17	7	18	101	8	16	37	49	6	5	8	39
JD148.2	2	6	14	42	7	9	2	3	11	7	4	27	7	14	28	26	7	3	7	22
JD148.4	2	4	21	26	7	11	2	3	11	6	2	21	9	13	40	23	6	3	9	24
JD148.5	6	6	13	27	7	10	3	3	11	7	2	10	9	14	31	34	8	5	7	19
JD148.6	2	5	16	25	9	11	2	3	11	8	4	8	9	12	27	33	4	5	8	24
JD148.7	2	6	12	32	6	18	3	3	13	8	2	15	10	23	21	20	6	2	9	32
JD148.8	2	5	27	24	9	9	2	3	15	7	3	37	8	19	27	29	7	2	8	26
155-26.1	3	2	5	26	5	15	6	7	8	2	0	17	4	7	21	25	7	7	5	19
155-26.2	3	1	5	24	1	5	1	1	9	1	1	28	5	6	22	40	2	1	5	23
155-26.3	8	2	3	13	1	2	1	1	11	1	1	11	4	2	19	36	1	1	4	16
155-26.4	2	1	4	26	1	6	2	1	8	1	1	18	4	2	21	38	1	2	5	36
155-26.5	6	1	6	21	2	5	2	2	8	1	1	17	5	2	22	32	1	2	5	25
155-26.6	3	1	5	17	4	3	1	2	11	2	1	20	5	2	18	33	5	3	5	31
155-26.7	4	1	21	45	1	4	3	5	10	1	1	25	8	12	37	33	4	8	6	42
155-26.8	2	1	3	18	1	4	3	1	11	1	1	10	6	3	16	25	1	1	4	10