



Technical Information and Typical Properties

MSC Two-Sided Cling Machine Film .80 mil



Product Description

Sigma Select is our most versatile and cost effective cast machine film. Designed to be a workhorse, Sigma Select is a robust 2 sided cling film with a broad range of gauges that make it an ideal choice for most applications.

General

Applications: High Volume, Lower speed wrapping, One-sided cling not required
Revision Date: 6/22/2015
Available in 20 and 30 inch widths

Film Properties	Typical Value (English)	Tolerance	Test Method
Tensile Strength at Yield MD	1300 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1200psi	± 15%	ASTM D882
Tensile Strength at Break MD	6900psi	± 15%	ASTM D882
Tensile Strength at Break TD	4000psi	± 15%	ASTM D882
Elongation at Break MD	480%	± 15%	ASTM D882
Elongation at Break TD	620%	± 15%	ASTM D882
Protrusion Puncture	10.0 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	23.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	330 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	540 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	20.3 micron	

Little & Co. Inc.

Phone: 8863-430-8861

Email: Adamm285@gmail.com

www.Littleandcompany.com