


Applications

- Automotive electronics
- Industrial electronics
- Home appliances

Features

- Glass-encapsulated, heat-resistive and highly stable
- For temperature measurement up to 300 °C
- Fast response
- Small dimensions
- Leads: dumet wires (copper-clad FeNi)



Dimensions
in mm

Options

Leads: nickel-plated wires

Delivery mode

Bulk

| | | | |
|--|------------------|-----------------------------|------|
| Climatic category (IEC 60068-1) | | 55/300/56 | |
| Max. power at 25 °C | P_{25} | 32 | mW |
| Resistance tolerance | $\Delta R_N/R_N$ | $\pm 1\%, \pm 3\%, \pm 5\%$ | |
| Rated temperature | T_N | 25 | °C |
| Dissipation factor (in air) | δ_{th} | approx. 0,75 | mW/K |
| Thermal cooling time constant (in air) | τ_c | approx. 7 | s |
| Heat capacity | C_{th} | approx. 5 | mJ/K |

| R_{25} | No. of R/T characteristic | $B_{25/85}$ | $B_{0/100}$ | $B_{25/100}$ | Ordering code |
|----------|-----------------------------|-------------|------------------------------|--------------|---------------|
| Ω | | K | K | K | |
| 2 k | 8401 | 3420 | $3390 \pm 1\%$ | 3436 | B57550G0202+ |
| 5 k | 8402 | 3480 | $3450 \pm 1\%$ | 3497 | B57550G0502+ |
| 10 k | 8407 | 3480 | $3450 \pm 1\%$ | 3497 | B57550G0103+ |
| 20 k | 8415 | 3992 | $3970 \pm 1\%$ | 4006 | B57550G0203+ |
| 30 k | 8415 | 3992 | $3970 \pm 1\%$ | 4006 | B57550G0303+ |
| 50 k | 8403 | 3992 | $3970 \pm 1\%$ | 4006 | B57550G0503+ |
| 100 k | 8404 | 4066 | $4036 \pm 1\%$ | 4085 | B57550G0104+ |
| 230 k | 8405 | 4240 | $4537 \pm 1\%$ ¹⁾ | 4264 | B57550G0234+ |
| 1400 k | 8406 | 4557 | $5133 \pm 2\%$ ²⁾ | 4581 | B57550G0145+ |

+: F000 for $\Delta R_N/R_N = \pm 1\%$; F002 for $\Delta R_N/R_N = \pm 1\%$ for nickel-plated wires
 H000 for $\Delta R_N/R_N = \pm 3\%$; H002 for $\Delta R_N/R_N = \pm 3\%$ for nickel-plated wires
 J000 for $\Delta R_N/R_N = \pm 5\%$; J002 for $\Delta R_N/R_N = \pm 5\%$ for nickel-plated wires

1) $B_{100/200}$

2) $B_{200/300}$

Reliability data

| Test | Standard | Test conditions | $\Delta R_{25}/R_{25}$ (typical) | Remarks |
|------------------------------------|----------------|---|-------------------------------------|-------------------|
| Storage in dry heat | IEC 60068-2-2 | Storage at upper category temperature T: 300 °C t: 1000 h | < 3 % | No visible damage |
| Storage in damp heat, steady state | IEC 60068-2-3 | Temperature of air: 85 °C Relative humidity of air: 85 % Duration: 56 days | < 2 % | No visible damage |
| Rapid temperature cycling | IEC 60068-2-14 | Lower test temperature: – 55 °C Upper test temperature: 200 °C Number of cycles: 1000 | < 2 % | No visible damage |

Herausgegeben von EPCOS AG**Unternehmenskommunikation, Postfach 80 17 09, 81617 München, DEUTSCHLAND****☎ ++49 89 636 09, FAX (0 89) 636-2 26 89**

© EPCOS AG 2002. Vervielfältigung, Veröffentlichung, Verbreitung und Verwertung dieser Broschüre und ihres Inhalts ohne ausdrückliche Genehmigung der EPCOS AG nicht gestattet.

Bestellungen unterliegen den vom ZVEI empfohlenen Allgemeinen Lieferbedingungen für Erzeugnisse und Leistungen der Elektroindustrie, soweit nichts anderes vereinbart wird.

Diese Broschüre ersetzt die vorige Ausgabe.

Fragen über Technik, Preise und Liefermöglichkeiten richten Sie bitte an den Ihnen nächstgelegenen Vertrieb der EPCOS AG oder an unsere Vertriebsgesellschaften im Ausland. Bauelemente können aufgrund technischer Erfordernisse Gefahrstoffe enthalten. Auskünfte darüber bitten wir unter Angabe des betreffenden Typs ebenfalls über die zuständige Vertriebsgesellschaft einzuholen.

Published by EPCOS AG**Corporate Communications, P.O. Box 80 17 09, 81617 Munich, GERMANY****☎ ++49 89 636 09, FAX (0 89) 636-2 26 89**

© EPCOS AG 2002. Reproduction, publication and dissemination of this brochure and the information contained therein without EPCOS' prior express consent is prohibited.

Purchase orders are subject to the General Conditions for the Supply of Products and Services of the Electrical and Electronics Industry recommended by the ZVEI (German Electrical and Electronic Manufacturers' Association), unless otherwise agreed.

This brochure replaces the previous edition.

For questions on technology, prices and delivery please contact the Sales Offices of EPCOS AG or the international Representatives.

Due to technical requirements components may contain dangerous substances. For information on the type in question please also contact one of our Sales Offices.