

Cellulose Casing

Description

Cellulose Casings made from regenerated cellulose.

Depending on the grade of film, it could also contain glycerol, white mineral oil. Coloured casings will contain various pigments and dye.

Ingredients

INGREDIENT
Cellulose
Glycerol
White mineral oil

Physical and Chemical Specification

Technical properties	Condition	Unit	Data	
			≤25US	> 25US
Thickness		um	26±10%	28±10%
Tensile Strength (MD)	23°C,50%RH	N/15mm	≥50	≥60
Elongation	23°C,50%RH	%	≥8	
Moisture	23°C,50%RH	%	>13	
Burst Strength	Wet	mm*mmHg	>11000	>12000
Overstuffing		%	10	

Recommendation Usage

1. Preparation

- The shirred casing is fully ready to use as shipped in the caddy.
- Do **not** immerse in water prior to use.

2. Applications

- Suitable for all types of sausage processing, including:
 - Liquid smoke
 - Acid showers
 - Natural smoke
 - Steam cooking
 - Water cooking
- Can be used for all sausage types.

This information comes from our research and testing and is thought to be reliable. Users must check and confirm that the product suits their purposes and meets legal requirements. No warranty is given, and we do not accept any responsibility for patent violations or other damages related to the product's use.

3. Stuffing Machine Setup

- Ensure the stuffing machine is correctly adjusted:
 - Casing stuffing to the recommended stuffing diameter.
 - Correct linker chains and stuffing tube must be used.
- Undersize stuffing tubes: may allow air entry and fat separation.
- Oversize stuffing tubes: may cause casing breakage (restricted rotation).

4. Smoking & Moisture Control

- The surface of the stuffed casing should be **moist** (not wet).
 - Water droplets: leave spots on sausage.
 - Very dry casing: prevents proper smoke penetration.
- Recommended relative humidity during processing: **25% – 40%**.
 - Higher humidity: better peeling but may cause surface fat and lighter col

5. Cooking

- Oven temperature must be set to:
 - Reach desired sausage internal temperature.
 - Enhance sausage skin color development.

6. Cooling & Peeling

- After processing and **before peeling**, sausages must be cooled rapidly:
 - Preferably with brine chill.
 - If not cooled properly: casing will not peel.
- For optimal peeling:
 - Sausage must be cold ($< 4^{\circ}\text{C}$).
 - Sausage surface must be extremely damp.
 - Preferably use steam peelers.

7. Customization

- Casings can be tailored to optimize sausage manufacturing (especially peeling):
 - Different mechanical properties.
 - Various end closures.
 - Specific compositions and additives.

This information comes from our research and testing and is thought to be reliable. Users must check and confirm that the product suits their purposes and meets legal requirements. No warranty is given, and we do not accept any responsibility for patent violations or other damages related to the product's use.

Allergens Information

No.	Indication presence or absence of listed allergens according Regulation (EU) 1169/2011 annex II	+ = present , - = absent x = cross contamination
1	Cereals containing Gluten	-
2	Crustaceans	-
3	Eggs	-
4	Fish	-
5	Peanuts	-
6	Soyabeans	-
7	Milk(including lactose)	-
8	Nuts	-
9	Celery	-
10	Mustard	-
11	Sesame Seeds	-
12	Sulphur dioxide and sulphites (>10mg/kg)	-
13	Lupin	-
14	Molluscs	-

Packaging

The top and bottom of the carton are fixed with adhesive tape, and each piece of goods is wrapped with plastic film, and four plastic belts are tied outside to avoid damage during transportation.

Shelf life

Best before 2 years after production date.

Storage Recommendations

- The casings should be stored in the cartons and caddy boxes between 4 deg C and 25 deg C, at room Relative Humidity of 50% to 70%.
- Keep the casing away from direct sunlight, both caddies and cartons.
- Unused casing should be returned to the caddy and covered completely in plastic so the casing will not dry out.
- If the casing does dry out due to exposure to air, put the casing in a refrigerated high humidity room to remoisturize.

This information comes from our research and testing and is thought to be reliable. Users must check and confirm that the product suits their purposes and meets legal requirements. No warranty is given, and we do not accept any responsibility for patent violations or other damages related to the product's use.