



PURE METTAL

Metallic microcement

Pure Mettal is a highly decorative two-component metallic microcement. Pure Mettal is suitable for use indoors and outdoors and can be applied to any surface. Pure Mettal is available in a wide range of colours and thanks to its exceptional properties allows the lines and contours of the design to be emphasised in a very significant way, thus achieving a greater intensity and texture, more typical of natural metal.


- Pure Mettal Bronze
- Pure Mettal Aluminium
- Pure Mettal Iridium
- **Pure Mettal Brass**
- **Pure Mettal Cooper**


Technical Data

First layer consumption: 305 g/m² Second layer consumption: 260 g/m²

Component B is the organic hybrid resin.


Application





Pure Mettal Component A is a powder with metallic properties, while Pure Mettal





The mixing ratio of the components will depend on the mode of application. The indicative rates for trowelling are:

Pure Mettal	COMPONENT A (Kg)	COMPONENT B (Kg)
Bronze	3	1
Aluminium	2	1
Iridium	3	1
Brass	3	1
Copper	1	0,5

Table 1.- Indicative rates for applying Pure Mettal with trowel.

1. Cleaning and preparation of the substrate

We must ensure that it is well consolidated, dry and, if necessary, bounded. Vacuum to clean the surface.

2. Primer

Apply one layer of the primer Primacem ABS and Primacem PLUS or Primacem ABS.

3. Decoration

We apply Pure Mettal (Bronze, Aluminium, Iridium, Brass, Copper) on the prepared substrate. It is recommended to apply 2 coats to obtain the best finishes. Mix the Pure Mettal Component A with the organic hybrid resin Component B. The indicative rate (Table 1) can be modified to reach the desired texture. Apply one coat and let it dry for 2h, then apply the next coat and let it dry for 12h, the drying time can be affected by the temperature and humidity of the environment. To get the metallic gloss effect, it must be sanded (with 180-220 grain) and finally polished (with 800 and 1000 grain at 2000-3000rpm). Clean surface to remove dust.

4. Sealing process

Once polished, it is recommended to immediately seal with two coats of Presealer to avoid oxidation.

Apply the first coat, leave to dry for 4 hours. Then apply the second coat, let it dry for 12h and sand with 400 grit.

5. Protection

It is recommended to apply two coats of TOPSEALER WT A+B to protect the surface. Proportion of TOPSEALER WT A catalysed with TOPSEALER WT B 5:1 (A:B) by weight. Apply the first coat and leave to dry for 24 hours. Sand with 400 grit and follow with the second coat, leave to dry for 24h.

Storage

The product should be stored in its original closed container and protected from the weather at temperatures between 10°C and 30°C, in a dry and well ventilated place, away from heat sources and direct sunlight. The time of use is 1 year from the date of manufacture, properly stored.

After mixing component A with component B of Pure Mettal, it can be stored in a closed container at temperatures between 10°C and 30°C in a dry place for one week.

Health and Safety

In case of contact with eyes, rinse with plenty of water for 15 minutes.

In case of skin contact wash with soap and water. Do not ingest. In case of ingestion do not provoke vomiting and seek medical attention immediately.

The following measures are recommended:

- Good ventilation
- Protective glasses to avoid splashes
- Rubber gloves

Empty containers must be disposed of in accordance with current legislation. To prevent the product from drying out or thickening, close the lid after each use. Keep out of the reach of children.

Tools used should be washed with soap and water immediately after use.



The product must not be used for purposes other than those specified, without first having written instructions for its use. It is always the responsibility of the user to take appropriate measures in order to comply with the requirements set out in the legislation. The Safety Data Sheets of the product are available for the professionals.

Last edition: January 2020