

Universal Packaging Company (Pvt) Ltd Certificate Of Analysis REC-QA-34-22 Effective Date 12.12.2022 Rev:0 Page 1 of 1

Customer Name: UNILEVER Job Name: REEL SFXL RS.50 CP 2L 10% EXTRA Job card #: 23070162 Structure: $PET (10\mu) + M.LDPE (50\mu)$ Dispatched Date: **Production Date:** 21-Sep-23 25/Aug/23 **Best Before:** 6 Months **Sampling Plan:** SOP-QA-11-19 JT-4426 **Dispatch Quantity:** 76,875.00 PCS **Vechile Number:**

S.NO	Parameters	Target	Min	Max	Test method	Unit	Results
1	Grammage	62.32	56.79	67.85	ISO 536	g/m²	63.8
2	Reel Width	720	719	721	Internal	mm	720
3	Coef of Fr. Dynamic face\face	0.25	0.22	0.28	ASTM D1894	Number	0.24
4	Coef of Fr. Dynamic Reverse\Reverse	0.23	0.2	0.26	ASTM D1894	Number	0.23
5	Coef of Fr. Static face\face	0.23	0.2	0.26	ASTM D1894	Number	0.24
6	Coef of Fr. Static Reverse\Face	0.25	0.22	0.28	ASTM D1894	Number	0.24
7	Lamination Strength	1.25	1.1	-	F 904-98	N/15mm	2.8
8	Dart Impact	400	360	440	ASTMD1709	g	465
9	Repeat Length	160	159	161	Internal	mm	160
10	Seal Strength	10	7.3	-	ASTM F88	N/15mm	11.5
11	Tensile Strength @ Break (CD)	48	44	-	ASTM D882	N/mm²	52
12	Tensile Strength @ Break - F max (CD)	45	37	-	ASTM D882	N/15mm	48
13	Tensile Strength @ Break (MD)	37	32	-	ASTM D882	N/mm²	39
14	Tensile Strength @ Break - F max (MD)	35	27	-	ASTM D882	N/15mm	53
15	Thickness	62.32	56.59	68.05	DIN 53370	μ	64

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.

Note: System generated document signature donot required.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi, Pakistan