

Universal Packaging Company (Pvt) Ltd	Effective Date 12.12.2022
Certificate Of Analysis	Rev:0
REC-QA-34-22	Page 1 of 1

Customer Name:		UNILEVER	Job Name:	9G TK SACHET SHUBHAM 12 LANE
Job card #:		23060213	Structure:	PET (12μ) + M.PET (12μ) + LDPE (40μ)
Dispatched Date: Best Before:		10-Jul-23 6 Months	Production Date: Sampling Plan:	26-Jun-23 SOP-QA-11-19
S.NO	Parameters	Test method	Unit	Results
1	Width	Interanl	mm±2	1152
2	Cut of length	Interanl	mm±2	80
3	Grammage	ASTM-D3776	g/m² ±5	78.4
4	Thickness	ASTM-F2251	μm±5	70
5	Coef of Fr. Dynamic	ASTM-D1894	Number	0.14
6	Coef of Fr. Static	ASTM-D1894	Number	0.15
7	Lamination Strength	ASTM F904-98	N\15mm	329
8	Lamination Strength	ASTM F904-98	N\15mm	418
9	Seal Strength	ASTM-F88	N\15mm	7147

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.

Note: System generated document signature donot required.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi,Pakistan