

Universal Packaging Company (Pvt) Ltd	Effective Date 12.12.2022
Certificate Of Analysis	Rev:0
REC-QA-34-22	Page 1 of 1

UNILEVER Job Name: NOODLE CHATPATTA 35G NACL **Customer Name:** Job card #: 23040010 Structure: PET (12 μ)+BOPP.COM (18 μ) Dispatched Date: 26-May-23 **Production Date:** 15-May-23 Best Before: 6 Months **Sampling Plan:** SOP-QA-11-19 Dispatch Quantity: 5008.22kg **Vechile Number:** JV-7964

S.NO	Parameters	Standard	Test method	Unit	Results
1	Grammage	35-41	ISO 536	g/m²	37.1
	-			6/111	
2	Width	244-246	Internal	mm	245
3	Coef of Fr. Dynamic Face/Face	0.229-0.232	ASTM-D1894	Number	0.231
4	Coef of Fr. Dynamic Reverse/Face	0.318-0.323	ASTM-D1894	Number	0.322
5	Coef of Fr. Dynamic Reverse/Metal	0.17-0.201	ASTM-D1894	Number	0.189
6	Coef of Fr. Dynamic Reverse/Reverse	0.337-0.358	ASTM-D1894	Number	0.349
7	Coef of Fr. Static Face/Face	0.238-0.244	ASTM-D1894	Number	0.237
8	Coef of Fr. Static Face/Metal	0.18-0.201	ASTM-D1894	Number	0.20
9	Coef of Fr. Static Reverse/Face	0.337-0.358	ASTM-D1894	Number	0.349
10	Coef of Fr. Static Reverse/Metal	0.18-0.212	ASTM-D1894	Number	0.182
11	Repeat Length	144-146	Internal	mm	145
12	Seal Strenght	4.5	ASTM F88	N/15mm	7.1
13	Thickness	32.5-37.5	DIN 53370	μm	34
14	Lamination Quality	N/A	ASTM-F904	N/A	OK
15	Print Quality	N/A	Visual Test	N/A	OK
16	Machineability	N/A	Undefined	N/A	OK
17	Odour in Laminates	N/A	ISO-13302	N/A	ОК

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.