	5

Universal Packaging Company (Pvt) Ltd Certificate Of Analysis REC-QA-34-22 Effective Date 12.12.2022 Rev:0 Page 1 of 1

Customer Name: UNILEVER Job Name: **REEL RIN WP RS 50** 23090064 Job card #: Structure: $PET (10\mu) + M.LDPE (50\mu)$ Dispatched Date: 13-Sep-23 **Production Date:** 11-Sep-23 **Best Before:** 6 Months SOP-QA-11-19 **Sampling Plan:** Vehicle Number: C-1391 **Dispatch Quantity:** 1,083,250.00

S.NO	Parameters	Target	Min	Max	Test method	Unit	Results		
1	Grammage	62.32	56.79	67.85	ISO 536	g/m²	63.6		
2	Reel Width	360	359	361	Internal	mm	360		
3	Coef of Fr. Dynamic face\face	0.25	0.22	0.28	ASTM D1894	Number	0.24		
4	Coef of Fr. Dynamic Reverse\Reverse	0.23	0.2	0.26	ASTM D1894	Number	0.26		
5	Coef of Fr. Static face\face	0.23	0.2	0.26	ASTM D1894	Number	0.25		
6	Coef of Fr. Static Reverse\Face	0.25	0.22	0.28	ASTM D1894	Number	0.28		
7	Lamination Strength	1.25	1.1	-	F 904-98	N/15mm	1.63		
8	Repeat Length	180	179	181	Internal	mm	180		
9	Seal Strength	40	32	-	ASTM F88	N/15mm	37		
10	Tensile Strength @ Break (CD)	48	44	-	ASTM D882	N/mm²	45		
11	Tensile Strength @ Break (MD)	37	32	-	ASTM D882	N/mm²	36		
12	Thickness	62.32	56.79	68.05	DIN 53370	μ	64		

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.

Note: System generated document signature donot required.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi, Pakistan