

Customer Name:	UNILEVER	Job Name:	LAMINATE TM CHASKA 100 MM
Job card #:	23050024	Structure:	PET (10μ)+MOPP (20μ)
Dispatched Date:	20-May-23	Production Date:	8-May-23
Best Before:	6 Months	Sampling Plan:	SOP-QA-11-19
Dispatch Quantity:	1505.02 Kg	Vehicle Number:	JV-7216

S.NO	Parameters	Standard	Test method	Unit	Results		
1	Width	100± 1	ISO-4592	mm	100		
2	Grammage	34.2± 1	ASTM-D3776	g/m²	34.9		
3	Thickness	32± 1	ASTM-F2251	μm	32		
4	Coef of Fr. Static Face\Metal	>0.2	ASTM-D1894	Number	0.204		
5	Lamination Quality	N/A	ASTM-F904	N/A	OK		
6	Print Quality	N/A	Visual Test	N/A	OK		
7	Machineability	N/A	Undefined	N/A	ОК		
8	Odour in Laminates	N/A	ISO-13302	N/A	ОК		

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.

Note: System generated document signature donot required.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi,Pakistan