

**Customer Name:** UNILEVER Job Name: KNORR TK 800G PET  $(10\mu)$  + FOIL  $(07\mu)$ + Job card #: 23030196 Structure: PET (10 $\mu$ ) + LDPE NYLON (152 $\mu$ ) Dispatched Date: 20-May-23 **Production Date:** 12-May-23 **Best Before:** 6 Months **Sampling Plan:** SOP-QA-11-19 **Dispatch Quantity: Vehicle Number:** JV-7216 423.61 Kg

S.NO	Parameters	Standard	Test method	Unit	Results
1	Width	537-539	ISO-4592	mm	538
2	Repeat length	164-166	Internal	mm	165
3	Grammage	175.5-214.5	ASTM-D3776	g/m²	200.2
4	Thickness	160-198	ASTM-F2251	μm	185
5	Lamination Strength A to B	N\A	ASTM F904-98	gf/25mm	N/Open
6	Lamination Strength B to C	N\A	ASTM F904-98	gf/25mm	N/Open
7	Lamination Strength C to D	N\A	ASTM F904-98	gf/15mm	665
8	Seal Strength	N\A	ASTM-F88	gf/15mm	8460
9	Coef of Fr. Dynamic Face/Metal	N\A	ASTM-D1894	Value	0.196
10	Coef of Fr. Static Face/Metal	N\A	ASTM-D1894	Value	0.246
11	Print Quality	N\A	Visual Test	N/A	Ok

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.

Note: System generated document signature donot required.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi,Pakistan