

**Customer Name:** UNILEVER Job Name: OW KNORR NOODLES CHSKA 31.5G Job card #: 23050023 Structure: PET (12 $\mu$ )+BOPP.COM (18 $\mu$ ) Dispatched Date: 20-May-23 **Production Date:** 8-May-23 **Best Before:** 6 Months Sampling Plan: SOP-QA-11-19 Dispatch Quantity: 7135.21 Kg Vehicle Number: JV-7216

S.NO	Parameters	Standard	Test method	Unit	Results
1	Grammage	35-41	ISO 536	g/m²	36.8
2	Width	244-246	Internal	mm	245
3	Coef of Fr. Dynamic Face/Face	0.229-0.232	ASTM-D1894	Number	0.231
4	Coef of Fr. Dynamic Reverse/Face	0.318-0.323	ASTM-D1894	Number	0.32
5	Coef of Fr. Dynamic Reverse/Metal	0.17-0.201	ASTM-D1894	Number	0.195
6	Coef of Fr. Dynamic Reverse/Reverse	0.337-0.358	ASTM-D1894	Number	0.341
7	Coef of Fr. Static Face/Face	0.238-0.244	ASTM-D1894	Number	0.24
8	Coef of Fr. Static Face/Metal	0.18-0.201	ASTM-D1894	Number	0.20
9	Coef of Fr. Static Reverse/Face	0.337-0.358	ASTM-D1894	Number	0.349
10	Coef of Fr. Static Reverse/Metal	0.18-0.212	ASTM-D1894	Number	0.201
11	Repeat Length	144-146	Internal	mm	145
12	Seal Strenght	4.5	ASTM F88	N/15mm	5.4
13	Thickness	32.5-37.5	DIN 53370	μm	35
14	Lamination Quality	N/A	ASTM-F904	N/A	ОК
15	Print Quality	N/A	Visual Test	N/A	ОК
16	Machineability	N/A	Undefined	N/A	ОК
17	Odour in Laminates	N/A	ISO-13302	N/A	ОК

**Remarks:** Storage condition, Temperature should be below 30°C & 50% humidity.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi,Pakistan