

Universal Packaging Company (Pvt) Ltd Certificate Of Analysis REC-QA-34-22 Effective Date 12.12.2022 Rev:0

LIFEBUOY HRBL DBLE PATTA 9 ML (6 UNILEVER Job Name: **Customer Name:** LANE) 23050102 Structure: PET (10 μ) + MILKY LDPE (63 μ) Job card #: Dispatched Date: 19-May-23 **Production Date:** 15-May-23 **Best Before:** 6 Months **Sampling Plan:** SOP-QA-11-19 **Dispatch Quantity: Vechile Number:** TMK-617 2639.08kg

| S.NO | Parameters | Min | Max | Test method | Unit | Results |
|------|-------------------------------------|-------|-------|-------------|--------|---------|
| | | | | | | |
| 1 | Grammage | 69.23 | 80.49 | ISO 536 | g/m² | 79.7 |
| 2 | Reel Width | 1055 | 1057 | Internal | mm | 1056 |
| 3 | Weight\Unit | 1.24 | 1.32 | UMA-1324 | g | 1.28 |
| 4 | Coef of Fr. Dynamic face\face | 0.19 | 0.25 | ASTM D1894 | Number | 0.24 |
| 5 | Coef of Fr. Dynamic Reverse\Reverse | 0.19 | 0.25 | ASTM D1894 | Number | 0.20 |
| 6 | Coef of Fr. Static Face\Face | 0.19 | 0.25 | ASTM D1894 | Number | 0.25 |
| 7 | Coef of Fr. Static Face\Metal | 0.19 | 0.25 | ASTM D1894 | Number | 0.25 |
| 8 | Repeat Length | 68 | 66 | UMA-5982 | mm | 68 |
| 9 | Thickness | 70.07 | 81.73 | Undefined | μm | 77 |
| 10 | Tensile Strength CD at break | 21 | 31 | Undefined | N\mm² | 62 |
| 11 | Tesnile Strength MD at break | 26 | 36 | Undefined | N\mm² | 85 |

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.

Note: System generated document signature donot required.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi,Pakistan