	<b>5</b>

## Universal Packaging Company (Pvt) Ltd Certificate Of Analysis REC-QA-34-22 Effective Date 12.12.2022 Rev:0 Page 1 of 1

**REEL SUNLIGHT GREEN RS. 50** UNILEVER Job Name: **Customer Name:** SINGLE LANE Q3 CP 23100121 PET  $(10\mu) + M.LDPE (50\mu)$ Job card #: Structure: 27-Oct-23 **Dispatched Date: Production Date:** 10/24/23 **Best Before:** 6 Months **Sampling Plan:** SOP-QA-11-19 Dispatched Qty: 1,380,924.00 PCS Vehicle Number: C-2715

S.NO	Parameters	Target	Min	Max	Test method	Unit	Results		
1	Grammage	62.32	56.79	67.85	ISO 536	g/m²	64.1		
2	Reel Width	360	359	361	Internal	mm	360		
3	Coef of Fr. Dynamic face\face	0.25	0.22	0.28	ASTM D1894	Number	0.26		
4	Coef of Fr. Dynamic Reverse\Reverse	0.23	0.2	0.26	ASTM D1894	Number	0.23		
5	Coef of Fr. Static face\face	0.23	0.2	0.26	ASTM D1894	Number	0.25		
6	Coef of Fr. Static Reverse\Face	0.25	0.22	0.28	ASTM D1894	Number	0.27		
7	Lamination Strength	1.25	1.1	-	F 904-98	N/15mm	3.1		
8	Repeat Length	180	179	181	Internal	mm	180		
9	Seal Strength	40	32	-	ASTM F88	N/15mm	38		
10	Tensile Strength @ Break (CD)	48	44	-	ASTM D882	N/mm²	46		
11	Tensile Strength @ Break (MD)	37	32	-	ASTM D882	N/mm²	36		
12	Thickness	62.32	56.59	68.05	DIN 53370	μ	65		

Remarks: Storage condition, Temperature should be below 30°C & 50% humidity.

Note: System generated document signature donot required.

Universal Packaging Company(pvt) Ltd. Plot No : GA-65-66-A4-A5, Korangi Creek National Industrial park, Korangi Town Karachi, Pakistan