

# TECHNICAL DATA

# Scapa 8705B

Polyester Adhesive Tape

#### DESCRIPTION

**Scapa 8705B** is a polyester film coated with a fully cured acrylic adhesive system, with 0.055 mm total thickness and recommended for a variety of coil winding protection and insulation applications (130°C thermal class B).

### **APPLICATIONS**

- Fixing and securing non-adhesive insulating materials between layers,
- Fixing output wires, copper sheets or wires harnesses,
- Layer and phases insulation,
- Outer protective insulating wraps for bobbins, transformers etc...
- Soldering protection and varied insulation uses for motors,
- Features identification (Printable),
- Cross-cut test of paints and varnishes (accordingly to EN ISO 2409).

#### PRODUCT BENEFITS

- 23 microns polyester films backing for improved moisture resistance, weight and space savings,
- Outstanding dielectric strength,
- Acrylic adhesive system specially designed for its resistance to solvents, freon and transformer oils,
- Service temperature: 130°C continuous Thermal Class B,
- Good peel strength to check paints and varnishes.

Issue: 1 Date: 01/03/03 Page 1 of 2 8705B.doc

www.scapa.com

The information supplied is accurate to the best of Scapa's knowledge and is based upon all current data available to it. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form part of any contract with a customer.

#### TECHNICAL PROPERTIES

	Unit	Nominal value	Test Method
Total Thickness	mm	0.055	AFERA 4006
Tensile Strength	N/cm	35	AFERA 4004
Elongation at Break	%	60 to 110	AFERA 4005
Adhesion to Steel	N/cm	4.3	AFERA 4001
Breakdown Voltage	kV	5	AFERA 4011
Insulation Resistance	MΩ	1x10 <sup>6</sup>	AFERA 4010
Service Temperature	°C	130	UL1446
Corrosion Factor		1	
Cross-linking Cycle		1h at 150°C – 2h at 130°C	

## STANDARD PRESENTATION

Roll length: 66 metres

Roll width:
9, 12, 15, 19, 25, 30, 38 and 50 mm
Core:
76 mm Scapa branded cardboard core

Packaging: 9 and 12 mm in plastic bag; other widths are cellowrapped with a Scapa label

Colours: Transparent

Note: Other dimensions are available upon request and may be subject to minimum order quantities.

### RECOMMENDATIONS

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and +30°C. Under these conditions, the storage life of the tape in a temperate climate will be at least one year.

Surfaces should be clean, dry and free of dust, grease, oil or other contaminants.

Issue: 1 Date: 01/03/03 Page 2 of 2 8705B.doc

www.scapa.com

The information supplied is accurate to the best of Scapa's knowledge and is based upon all current data available to it. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form part of any contract with a customer.