


	<h1>QC TEST REPORT</h1>	SCAPA Complaint n:	100489
		Customer Complaint n:	

date of test:
22/07/2011

Controlled by QC Coordinator: (Stefano Roncarolo)


2702

Adesion to seel

SAMPLE	Average values (SCAPA spec ≥ 1,8 N/cm)
1	2,84
2	2,38

Adesion to back

SAMPLE	Average values (SCAPA spec ≥ 1,8 N/cm)
1	2,44
2	2,25

Unwind force

SAMPLE	Average values (SCAPA spec ≥ 1,8 N/cm)
1	3,05
2	3,21