

# AS1179W-PR Test for Complaint Sample

## 1. Test Information

Test Date	2011.05.11~05.12	Test Surface	SUS
Tested by	SS Nam	Test Condition	25°C / 45 %

2. Result : The complaint sample has good adhesion value.

## 3. Summarization Test data

Test Item	Unit	Spec	Complaint sample		AS1179W (191282)	
			Liner side	Exposure side	Liner side	Exposure side
Thickness	mm	1.1±0.11	1.045		1.124	
90° Peel (20min)	N/19mm	INFO only	36.2	32.6	35.6	35.5
90° Peel (24hr)		>40	43.4	40.1	48	44.3
Release Force (300in/min)	g/19mm	INFO only	37.3		35.5	
Tensile Strength	N/19mm	>12	22.7		21	
Elongation	%	>600	976		1000	
Density	kg/m³	700~900	812		821	

## 4. Graph

