

Gd vs. Gd₅Si₂Ge₂ in the ASHRAE Range
(fixed-T_c Gd₅Si₂Ge₂ collapses to ~0; the same family re-tuned per span does not)

