

Nanocomposite Off-Design Robustness
Broad blend keeps $Q_c > 0$ where a sharply-tuned single phase collapses

