



Plot SYN-07, Kalpana Test Estate, Navarup Demo City, India 000000

quality@demo-07.invalid | Tel: +91 00000 00007 (demo only)

NABL-TC-SYN-002 | Internal reference SYN/2026/0007

LABORATORY TEST REPORT

Issue date: 2026-08-24 Reference: SYN/2026/0007
Lot / batch: SYN-LOT-26-007

Product / sample: Printed PE Pouch PP90, blue print
Client: Evratyn Export Assemblies | Nordelvia Components, EU demo buyer
Received: 2026-08-18 | Tested: 2026-08-20 to 2026-08-22


Method: XRF screening followed by CR 13695-1:2000 confirmation. Reported values below are confirmatory results; XRF alone is not the basis for the Cr(VI) result.

Analyte	Result	Detection limit	Unit
Pb	21.0	0.5	ppm
Cd	1.5	0.1	ppm
Hg	0.4	0.05	ppm
Cr(VI)	5.1	0.5	ppm
Pb+Cd+Hg+Cr(VI)	28.0		ppm

Units are ppm by mass (w/w). The sum refers to the tested component only.

Acceptance criterion: Pb + Cd + Hg + Cr(VI) <=100 mg/kg under Regulation (EU) 2025/40 Article 5(4). Assessment relates only to the submitted sample.

Report validity: no fixed expiry; applies only to the tested sample and lot.



Daren Kelvi
Authorised signatory - Trace Analysis

Issued electronically; signature is a fictional test specimen.





Plot SYN-07, Kalpana Test Estate, Navarup Demo City, India 000000

quality@demo-07.invalid | Tel: +91 00000 00007 (demo only)

NABL-TC-SYN-002 | Internal reference SYN/2026/0007

METHOD AND SAMPLE TRACEABILITY

Report SYN/2026/0007; sample Printed PE Pouch PP90, blue print; lot SYN-LOT-26-007. This page forms an integral part of the three-page report.

01 Sample receipt

Sealed sample pack received from the named client. Three pieces selected for the composite analytical preparation; the printed surface was included.

02 Screening

XRF used as preliminary elemental screening. Screening observations are not the final compliance values and are not substituted for species-specific Cr(VI) confirmation.

03 Confirmatory assessment

Confirmatory work and aggregation follow the fixture reference CR 13695-1:2000. Sample handling, blank checks and instrument records were reviewed before authorisation.

04 Unit convention

ppm in this report means parts per million by mass. Preserve the source unit and record the mass-basis conversion when normalising.

05 Document control

Page 1 contains the analytical table. Page 3 contains decision-rule and authorisation records. Reproduction must retain all three pages.

Daren Kelvi

Authorised signatory - Trace Analysis

Issued electronically; signature is a fictional test specimen.





Plot SYN-07, Kalpana Test Estate, Navarup Demo City, India 000000

quality@demo-07.invalid | Tel: +91 00000 00007 (demo only)

NABL-TC-SYN-002 | Internal reference SYN/2026/0007

RESULT REVIEW AND AUTHORISATION

Report SYN/2026/0007; same sample and lot as pages 1–2. Reviewer: Daren Kelvi.

Arithmetic check: $21.0 + 1.5 + 0.4 + 5.1 = 28.0$ ppm (mass basis). The aggregate, rather than four separate 100 mg/kg comparisons, is assessed against the criterion.

Decision statement: aggregate is below the 100 mg/kg reference threshold for the submitted sample. This report does not certify future batches or additional materials.

Decision rule for this synthetic fixture: direct comparison of the stated aggregate with the threshold; no uncertainty guard band has been applied. Any production decision needs the applicable decision rule.

Record status: authorised for issue on 2026-08-24. All sample data in this report are fictional. The synthetic NABL reference is not a real accreditation and must not be looked up as a live laboratory credential.

Daren Kelvi

Authorised signatory - Trace Analysis

Issued electronically; signature is a fictional test specimen.

