

**CHEMTECH****CHEMTECH COATING SOLUTION**

Fact. Add. : S.NO.182/2,Near MESB office,Village-Ware, Tal-Karjat, District-Raigad –410101. Mob:9834094310

E-mail : chemtechcoating@gmail.com**PRODUCT GUIDE****COATINGS**

SR.NO.	TRADE DESIGNATIONS & SYSTEM		PARTICULARS			
	Resin	Hardner	Type	Ratio	Pot life	Characterstics & application
2	CER 557	CEH 720	Modified Epoxy Resin / polyamine System	100 : 50 pbw	20 - 30 min.	Solventless rapid systems for primer and self- Levelling flooring and heavy duty floor coating for high humanity systems
3	CER 510 CER 552 CER 551	CEH 7035 - D CEH 7035 - DR	Modified Epoxy Resin / polyetheramine System	100:35 pbw 100:35 pbw	90-120 min. 60-90 min	Solventless, transparent high gloss systems for table top casting and clear coating /Imitation jewellery/ Meena works, Self- Levelling Flooring, Protective surface coating, colour retentive, Abrasion resistant.
4	CLF 559 Clear	CEH 7050 - DRN CEH 7050 - DN	Modified Epoxy Resin / polyetheramine System	100 : 50 pbw 100 : 50 pbw	60-90 min 90-120 min	Solventless, transparent high gloss systems for Imitation jewellery/ Coating, Self-Levelling, Flooring, Excellent Chemical resistant, protective surface coatings.
5	CER 552	CEH 735	Modified low viscosity /	100 : 35 pbw	30 - 40 min.	Solventless, transparent high gloss systems for Imitation jewellery/
6	CER 552 CLF 559 Pigmented	CEH 7963	Modified low viscosity / polyamine System	100 : 50 pbw	35 - 45 min.	Solventless high gloss & highly Chemical resistant coating, Self-levelling, Floor Topping & surface coating, Abrasion resirant, Transparent Imitation Jewellery, colour retentive.
7	CER 552 CLF 559 Pigmented	CEH 7618	Modified low viscosity / polyamine System	100 : 50 pbw	35 - 45 min.	Solventless high gloss & Chemical resistant coating, Self-levelling, Floor Topping & surface coating, Abrasion resirant, Transparent Imitation Jewellery, colour retentive.
8	Flex Dome A	Flex Dome B - 1	Modified / polyamine System	100 : 100 pbw	45 - 60 min.	Flexible, transparent high gloss Systems for doming in Imitation Jewellery & Label Coatings.
10	CER 557	CEH 740	Modified low viscosity Polyamide	100 : 50 pbw	35 - 45 min.	Solventless high solid ambient curing coating & Floorings mainly for Civil Engineering for Mortar, Screed & Anticorrosive coating .