

MFC TYPE	EFFECT	ANISOTROPIC ELASTICITY					
M-8557 P1	d33	D[* ,1] (Pa)	D[* ,2] (Pa)	D[* ,3] (Pa)	D[* ,4] (Pa)	D[* ,5] (Pa)	D[* ,6] (Pa)
DIMENSIONS		32000000000					
LENGTH	85	3510947130	14900000000				
BREADTH	57	4915670000	4620000000	14900000000			
LENGTH (OVERALL)	103	0	0	0	5150000000		
BREADTH (OVERALL)	64	0	0	0	0	5150000000	
THICKNESS	0.3	0	0	0	0	0	5150000000
DENSITY	5440 kg/m3						
TEMP	25C	PIEZOELECTRIC MATRIX					
YOUNGS MOD (XY)	15857000000	d[* ,1] (A s N^-1)	d[* ,2] (A s N^-1)	d[* ,3] (A s N^-1)			
YOUNGS MOD (YZ)	15857000000	0	0	0			
YOUNGS MOD (XZ)	30366000000	0	0	0			
POISSONS RATIO (XY)	0.31	-1.70E-10	-1.70E-10	4.00E-10			
POISSONS RATIO (YZ)	0.31	0	0	0			
POISSONS RATIO (XZ)	0.16	0	0	0			
SHEAR MOD (XY)	5150000000	0	0	0			
SHEAR MOD (YZ)	5150000000						
SHEAR MOD (XZ)	5150000000						