IPCON® PAHT GF

Glass Fiber Reinforced High Temperature Polyamide Filament

This is the filament's Technical Data Sheet (TDS). If you want the Material Safety Data Sheet (MSDS), please contact the customer service to download.

• Product Information

Item	Data
Filament Diameter	1.75 ± 0.05 mm
Net Filament Weight	1 kg ± 0.5%
Filament Length	340 m ± 2%
Spool Material	Cardboard (max heat resistance: 150 °C) or PC (max heat resistance: 130 °C)
Spool Size	Outer Cardboard's diameter: 200 mm; Inner roller's diameter: 90 mm
Recommendation for body protection during use	This material contains glass fiber, which may cause skin irritation. So it is recommended to wear gloves throughout the operation.

• Filament's Properties

Physical Properties	Testing Methods	Data
Density	ISO 1183-3	1.23 g/cm³
Shrinkage Rate*	Specially-defined	0.22% - 0.45%
Surface Hardness	Shore hardness	84D
Saturated Water Absorption Rate	25 °C, 55% RH, room air	1.03%
Melt Index	290 °C, 2.16 kg	17.8 g/10 min
Melting Temperature	DSC, 10 °C/min	238 °C
Vicar Softening Temperature	ISO 306, GB/T 1633	202 °C
Heat Deflection Temperature	ISO 75, 0.45 MPa	195 °C
Relative Thermal Index (RTI) Max Continuous Service Temperature	Actual working conditions simulation test	105 - 120 °C (dry state) (Related to load, size, shape, wall thickness, rate of water content, etc., and the value after annealing is higher than that before annealing in general)

Mechanical Properties*	Testing Methods	Data*
Tensile Strength XY	ISO 527, GB/T 1040	93 MPa
Tensile Strength Z	ISO 527, GB/T 1040	61 MPa
Young's Modulus XY	ISO 527, GB/T 1040	5368 MPa
Young's Modulus Z	ISO 527, GB/T 1040	3382 MPa
Breaking Elongation Rate XY	ISO 527, GB/T 1040	2.4%
Breaking Elongation Rate Z	ISO 527, GB/T 1040	1.7%

Flexural Strength XY	ISO 178, GB/T 9341	153 MPa
Flexural Strength Z	ISO 178, GB/T 9341	102 MPa
Flexural Modulus XY	ISO 178, GB/T 9341	5152 MPa
Flexural Modulus Z	ISO 178, GB/T 9341	3142 MPa
Impact Strength XY	ISO 179, GB/T 1043	35.5 kJ/m²
Impact Strength Z	ISO 179, GB/T 1043	10.5 kJ/m²

*The shrinkage rate and mechanical properties were tested on specimens printed by IPCON using a Bambu P1S printer (nozzle temperature: 290 °C, bed temperature: 100 °C, printing speed: printing speed: 100 mm/s) and IPCON PAHT GF (red) filament. The parameters of specimens of mechanical properties are as following: infill density—100%, infill pattern—concentric; and those of the 2 models of shrinkage (2 crosses that are vertical in the X and Y directions with designed lengths of 100.00 and 150.00 mm respectively) are as following: wall loop—2 and 6, infill density—15% and 25%, infill pattern—grid. The data is for user reference and comparison only. When using it, users are responsible for the safety, legal compliance and product performance.

• Main Features and Application Scenarios

1. Glass fiber reinforced, ultra low warping, strong, stiff and tough; highly accurate and wear-resistant; superb layer strength; outstanding heat resistance; compatible with AMS and CFS.
2. Applications with lightweight, insulating and high-performance needs such as automobiles, electrical tools and etc.

• Recommended Printing Settings

Drying Settings Before Printing	100 - 120 °C, 8 - 14 h (Blast drying oven)
Printing Temperature and Humidity	≤ 90 °C, ≤ 20% RH (Sealed with desiccant)
Storage Temperature and Humidity	≤ 35 °C, ≤ 20% RH (Sealed with desiccant)
Compatible Support Material	Itself or support filament for PA
Compatible Printer Type	Enclosed-frame (recommended), open-frame,
AMS or CFS	Compatible
Compatible Nozzle Material	Hardened steel, diamond, tungsten carbide, etc
Compatible Nozzle Size	0.4 / 0.6 / 0.8 mm
Compatible Plate Type	Smooth / Textured PEI Plate or other plate
Plate Surface Preparation	Apply liquid glue or PVP solid glue stick if the first layer bonding is not firm enough
Nozzle Temperature	270 - 300 °C
Bed Temperature	90 - 120 °C
Fan Speed	0% - 60%
Max Print Speed	250 mm/s

IPCON Polymer Material (Suzhou) Co., LTD

Address: Room 632, Building E, Dongchuang Science Park, No. 216, Jinfeng Road, Mudu Town,Wuzhong District, Suzhou City,China

Web Site:www.ipconpolymer.com

E-mail: sales@ipconpolymer.com

Tel: 400-139-1152

Innovative pragmatic Consistent