


# 1R6-72HPH 365~385M

High Efficiency
Low LID Mono PERC
with Half-cut Technology



## **Complete System and Product Certifications**

IEC 61215, IEC61730, UL1703

ISO 9001:2008: ISO Quality Management System

ISO 14001: 2004: ISO Environment Management System

TS62941: Guideline for module design qualification and type approval OHSAS 18001: 2007 Occupational Health and Safety







 Specifications subject to technical changes and tests. LONGi Solar reserves the right of interpretation. Positive power tolerance (0 ~ +5W) guaranteed

High module conversion efficiency (up to 19.3 %)

**Slower power degradation** enabled by Low LID Mono PERC technology: first year <2%, 0.55% year 2-25

**Solid PID resistance** ensured by solar cell process optimization and careful module BOM selection

Reduced resistive loss with lower operating current

Higher energy yield with lower operating temperature

Reduced hot spot risk with optimized electrical design and lower operating current



Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong District, Shanghai, 201203 Tel: + 86-21-61047332 Fax: +86-21-61047377 E-mail: module@longi-silicon.com Facebook: www.facebook.com/LONGi Solar

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.

## R6-72HPH**365~385M**

#### Design (mm) **Mechanical Parameters Operating Parameters**

Tolerance Length: ±2mm Width: ±2mm Height: ±1mm Pitch-row: ±1mm

Cell Orientation: 144 (6×24) Junction Box: IP67, three diodes

Output Cable: 4mm<sup>2</sup>, 300mm in length

Glass: Single glass

3.2mm coated tempered glass Frame: Anodized aluminum alloy frame

Weight: 23.0kg

Dimension: 2004×996×35mm

Packaging: 30pcs per pallet

150pcs per 20'GP

660pcc por 40'UC

Operational Temperature: -40 °C ~ +85 °C

Power Output Tolerance: 0 ~ +5 W

Voc and Isc Tolerance: ±3%

Maximum System Voltage: DC1500V (IEC/UL)

Maximum Series Fuse Rating: 20A

Nominal Operating Cell Temperature: 45±2 °C

Safety Class: Class II Fire Rating: UL type 4

		660pcs per 40°HC									
Electrical Characteristics Test uncertainty for Pmax											
Model Number	LR6-72H	LR6-72HPH-365M		LR6-72HPH-370M		LR6-72HPH-375M		LR6-72HPH-380M		LR6-72HPH-385M	
Testing Condition	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	
Maximum Power (Pmax/W)	365	270.4	370	274.1	375	277.8	380	281.5	385	285.2	
Open Circuit Voltage (Voc/V)	48.4	45.2	48.6	45.4	48.8	45.6	49.0	45.7	49.2	46.0	
Short Circuit Current (Isc/A)	9.71	7.82	9.79	7.89	9.87	7.95	9.96	8.02	10.03	8.09	
Voltage at Maximum Power (Vmp/V)	40.0	36.9	40.2	37.1	40.4	37.3	40.6	37.5	40.8	37.7	
Current at Maximum Power (Imp/A)	9.13	7.32	9.21	7.38	9.28	7.44	9.36	7.50	9.43	7.57	
Module Efficiency(%)	18	18.3		18.5		18.8		19.0		19.3	
CTC (Ctandard Testing Conditions), Irradiance	100014// 3 6 11	T	2F°C C		N 4 1 F						

Units: mm(inch)


STC (Standard Testing Conditions): Irradiance 1000W/m², Cell Temperature 25 °C, Spectra at AM1.5

NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20°C, Spectra at AM1.5, Wind at 1m/S


#### **Temperature Ratings (STC) Mechanical Loading** +0.057%/°C Front Side Maximum Static Loading 5400Pa Temperature Coefficient of Isc Rear Side Maximum Static Loading 2400Pa Temperature Coefficient of Voc -0.286%/°C **Hailstone Test** 25mm Hailstone at the speed of 23m/s Temperature Coefficient of Pmax -0.370%/°C

## **I-V Curve**


## Current-Voltage Curve (LR6-72HPH-375M)



## Power-Voltage Curve (LR6-72HPH-375M)



### Current-Voltage Curve (LR6-72HPH-375M)





Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong District, Shanghai, 201203 Tel: + 86-21-61047332 Fax: +86-21-61047377 E-mail: module@longi-silicon.com Facebook: www.facebook.com/LONGi Solar

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.