Universidade de Aveiro
2026

ALEXANDRE DE BRITO SALVADOR CAUVEL

Apollo 11 Mission Overview

Palavras Chave

texto livro, arquitetura, história, construção, materiais de construção, saber tradicional.

Resumo

Um resumo é um pequeno apanhado de um trabalho mais longo (como uma tese, dissertação ou trabalho de pesquisa). O resumo relata de forma concisa os objetivos e resultados da sua pesquisa, para que os leitores saibam exatamente o que se aborda no seu documento.
Embora a estrutura possa variar um pouco dependendo da sua área de estudo, o seu resumo deve descrever o propósito do seu trabalho, os métodos que você usou e as conclusões a que chegou.
Uma maneira comum de estruturar um resumo é usar a estrutura IMRaD. Isso significa:

- Introdução
- Métodos
- Resultados
- Discussão

Veja mais pormenores aqui:
`https://www.scribbr.com/dissertation/abstract/`

Keywords

textbook, architecture, history, construction, construction materials, traditional knowledge.

Abstract

An abstract is a short summary of a longer work (such as a thesis, dissertation or research paper).
The abstract concisely reports the aims and outcomes of your research, so that readers know exactly what your paper is about.
Although the structure may vary slightly depending on your discipline, your abstract should describe the purpose of your work, the methods you've used, and the conclusions you've drawn.
One common way to structure your abstract is to use the IMRaD structure. This stands for:

- Introduction
- Methods
- Results
- Discussion

Check for more details here:
`https://www.scribbr.com/dissertation/abstract/`

Contents

1 Introduction **6**
1.1 Background 6
1.2 Objectives 7
1.3 Scope 7
1.4 Work Breakdown Structure (WBS) 8

2 Literature Review **9**
2.1 Thermodynamic Basis for Corrosion 9
2.2 Notion of Potential and Passivity 9
2.3 Pourbaix Diagrams 10
2.4 Breakdown of Passivity by Chloride 11
2.5 Kinetics of Corrosion 12
2.6 Pitting Corrosion of Aluminium Alloys 13
2.7 Conventional Corrosion Protection Methods 14
2.8 Layered Double Hydroxides as a Chromate-Free Alternative . 15
2.8.1 Advantages of LDH 15
2.8.2 Synthesis of LDH 16
2.8.3 Rationale for ZnAl–LDH on Aluminium Substrates . . 17
2.8.4 Corrosion Inhibitors 18
2.9 Influence of IMPs on LDH growth 19
2.9.1 Pre-Treatment 20
2.10 Equivalent Circuit Models for EIS 21
2.10.1 Randles Equivalent Circuit (REC) 21
2.10.2 More advanced circuits 23
2.10.3 Inhibitor Efficiency from EIS Parameters 25

3 Methodology **26**
3.1 Pre-selection of inhibitors 26
3.2 Determine ECM for EIS 27
3.3 Pre-treatments 29
3.4 LDH Synthesis 30
3.5 Inhibitor incorporation 30

4 Results **31**

5 Discussion **32**

6 Conclusion & Future Work **33**

Bibliography **34**

List of Figures

List of Tables

1.1 Work Breakdown Structure (WBS) summary and project timeline. 8

3.1 Composition of the solutions for testing the effectiveness of the inhibitors and respective pH values 26

Chapter 1

Introduction

1.1 Background

Modern aerospace structures rely heavily on high-performance aluminium alloys, especially the 2xxx and 7xxx series, due to their exceptional strength-to-weight ratio and ease of manufacturability. However, under the harsh conditions of the aerospace environment, these materials are highly susceptible to localized corrosion [17, 34]. This degradation is accelerated by intermetallic particles dispersed within the alloy that form micro-galvanic sites, which can significantly shorten a component's lifespan [4, 17, 34].

Traditionally, this challenge has been managed using multilayer coatings based on hexavalent chromium (Cr(VI)) [6, 34]. These coatings offered strong adhesion, long-term durability, and, most importantly, a self-healing capability [4, 6, 34]. However, due to the carcinogenic nature of Cr(VI), strict regulatory restrictions have demanded an immediate ban, creating a need for safe, high-performance alternatives that can match the protection offered by chromium-based systems [4, 8, 34].

Recently, Layered Double Hydroxides (LDH) have emerged as a particularly promising alternative [4, 6, 8, 10, 24, 56]. Their layered structure allows them to store and release corrosion inhibitors in response to changes in the environment, providing a combination of barrier protection and active self-healing that aligns well with the industry's long-term needs.

Much of the recent research on LDH coatings has focused on common wrought alloys such as AA2024, usually tested on simple flat samples [8, 21, 49, 50]. While these studies have demonstrated excellent potential, there is a distinct lack of data on how LDH coatings perform on cast alloys like AC46000. Cast alloys make it possible to manufacture complex, highly detailed geometries that are becoming more common in modern aerospace assemblies. But these components also introduce new challenges such as an

uneven surface roughness, restricted accessibility, distinct microstructural features, and higher silicon content. All of these factors can significantly influence LDH growth, inhibitor incorporation, and overall coating uniformity, integrity and performance.

By successfully applying and testing the optimized environmentally-friendly LDH system on geometrically complex components, this work validates the limited existing research. More importantly, it draws a path for future work, especially in complex geometry which continues to grow rapidly in aerospace industry, while complying with safety and health regulations.

1.2 Objectives

This work follows four central objectives defined in the project plan:

- **O1. Synthesis and Optimization:** Synthesize a, Layered Double Hydroxide (LDH) conversion pre-treatment capable of forming a uniform coating layer on both flat and geometrically complex aluminium alloy substrates.
- **O2. Inhibitor Integration:** Intercalate established and novel corrosion inhibitors into the optimized LDH structure.
- **O3. Performance Benchmarking:** Compare LDH performance against established reference systems, such as anodizing and Cr(III)/Ce(IV) conversion coatings.
- **O4. Applicability to complex shapes:** Validate the protective system on complex geometric shapes, including application of an organic top-coating.

1.3 Scope

- **Coating System:** Hydrothermal synthesis and optimization of ZnAl-LDH conversion layers on AC46000 alloy via immersion in a metal-containing solution at high temperatures.
- **Inhibitor chemistry:** A targeted screening of environmentally friendly candidates, including vanadates, molybdates and MBT, will be performed at a standard concentration of 0.005 M.
- **Characterization Techniques:** Physical Characterization will use XRD to evaluate inhibition intercalation efficiency, FTIR/Raman to confirm chemical presence of inhibitor molecules within the LDH galleries, and SEM/EDS to analyse coating and substrate morphology.

- **Electrochemical Assessment:** Corrosion performance is evaluated through long-term EIS (up to 168 hours of immersion in 0.05 M NaCl) and localized SVET for self-healing monitoring.
- **Multilayer Configuration:** The final validation phase employs an anaphoretic polyurethane-based organic coating applied over the optimized LDH pre-treatment.

1.4 Work Breakdown Structure (WBS)

To achieve the defined objectives, the research project is organized into seven distinct Work Packages (WPs) that provide a chronological and technical framework for execution. This structure ensures a systematic progression from theoretical review and material characterization to the synthesis and final validation of the LDH-based protective system on complex geometries. Table 1.1 summarizes the project phases, their respective timelines, and the key deliverables associated with each stage of the research.

Table 1.1: Work Breakdown Structure (WBS) summary and project timeline.

WP	Title	Timeline	Key Tasks & Deliverables
1	State-of-the-Art	Sep – Oct 25	Literature review on Al corrosion and LDH systems.
2	Inhibitor Selection	Oct – Dec 25	EIS screening of organic/inorganic inhibitors in NaCl.
3	Substrate Charact.	Nov – Jan 26	Preparation and characterization of AC46000 substrate.
4	LDH Synthesis	Dec – Feb 26	Growth of LDH on Al and intercalation of inhibitors (XRD/FTIR).
5	Corrosion Eval.	Mar – May 26	EIS/SVET benchmarking against reference systems.
6	Multilayer Coatings	May – Jun 26	Organic coating on complex parts and adhesion validation.
7	Final Report	Jan – Jun 26	Data compilation and feasibility assessment.

Chapter 2

Literature Review

2.1 Thermodynamic Basis for Corrosion

Corrosion is fundamentally a spontaneous thermodynamic process driven by the tendency of metals to revert to their most stable, lower-energy states, such as oxides (M_nO_p) or sulfides (M_nS_p) [43, 45, 51]. This transition is quantified by a negative change in Gibbs free energy (ΔG), indicating that the oxidation reaction is energetically favoured over the retention of the metallic state [43, 45]. Mathematically, this thermodynamic driving force is related to the electrochemical potential E through the relation:

$$\Delta G = -nFE \tag{2.1}$$

where n is the number of electrons transferred per mole of reaction and F is the Faraday constant [18, 43, 45]. A negative ΔG corresponds to a positive E, confirming that the reaction proceeds spontaneously in the direction of corrosion for most metals.

2.2 Notion of Potential and Passivity

In practice, the thermodynamic behaviour of a metal is governed by its electrochemical potential in a given environment. While standard electrode potentials (E°) provide a useful thermodynamic reference, they are defined under idealised conditions and therefore have limited direct applicability to real corrosion environments [18, 51]. Corrosion studies consequently rely on the open-circuit potential (OCP), defined as the potential difference between the metal and a reference electrode measured in the absence of any externally applied current [44, 51]. Since absolute electrode potentials cannot be determined experimentally, OCP values are always reported relative to a specified reference electrode in a given electrolyte [43, 45, 51].

The OCP must be carefully distinguished from E°, the latter representing the ideal thermodynamic driving force for a given

half-reaction under standard conditions. For aluminium, $E^\circ = -1.66$ V versus the standard hydrogen electrode (SHE), which serves as the universal 0 V reference [51]. In contrast, the OCP reflects the steady-state potential established in a specific environment, at which the rates of anodic and cathodic partial reactions are equal and no net current flows [33, 43, 45]. In aqueous environments, aluminium typically exhibits an OCP in the range of -0.5 V to -0.7 V versus SHE [43, 51]. This substantial positive shift relative to E° arises from the rapid and spontaneous formation of a thin, adherent alumina film upon exposure to air or aqueous media:

$$2\,\mathrm{Al} + \frac{3}{2}\,\mathrm{O_2} \rightarrow \mathrm{Al_2O_3} \tag{2.2}$$

This native passive oxide layer acts as a physical barrier between the metal and the electrolyte, significantly retarding further oxidation and shifting the OCP in the noble direction. The stability of this passive film, however, is strongly dependent on environmental conditions, particularly pH, temperature, and the presence of aggressive anions such as chloride [18, 43, 45, 51].

2.3 Pourbaix Diagrams

A powerful tool for visualising the thermodynamic stability of a metal as a function of both electrochemical potential and pH is the Pourbaix diagram, also known as the E–pH diagram. For a given metal–electrolyte system, the diagram delineates three distinct thermodynamic domains [18, 43]:

- **Corrosion**, where the stable species are soluble ionic products (e.g. $\mathrm{Al^{3+}}$, $\mathrm{AlO_2^-}$), indicating active dissolution of the metal;
- **Passivation**, where the stable species are insoluble oxides or hydroxides (e.g. $\mathrm{Al_2O_3}$, $\mathrm{Al(OH)_3}$) that form a protective layer on the metal surface;
- **Immunity**, where the metal itself is the thermodynamically stable phase and dissolution is thermodynamically unfavourable.

The E–pH diagram for aluminium, shown in [REFERENCIAR FIGURE], illustrates the amphoteric nature of the metal: aluminium is susceptible to corrosion in both strongly acidic and strongly alkaline media, with only a relatively narrow intermediate pH range (approximately pH 4 to pH 8.5) corresponding to the passivation domain [18, 43, 51]. This behaviour is consistent with the dissolution reactions at either extreme:

$$\mathrm{Al} + 3\,\mathrm{H^+} \rightarrow \mathrm{Al^{3+}} + \frac{3}{2}\,\mathrm{H_2} \quad \text{(acidic dissolution)} \tag{2.3}$$

$$\mathrm{Al} + \mathrm{OH}^- + \mathrm{H_2O} \rightarrow \mathrm{AlO_2^-} + \frac{3}{2}\,\mathrm{H_2} \quad \text{(alkaline dissolution)} \tag{2.4}$$

It must be emphasised, however, that Pourbaix diagrams are strictly equilibrium constructs: they identify thermodynamically stable phases and the direction of spontaneous reactions, but provide no information on the kinetics of corrosion or the rate at which these reactions proceed [43, 45, 51]. A metal situated within the passivation domain may still corrode if the passive film is mechanically damaged or chemically disrupted [18, 43]. An example of this is when aluminium is exposed to chloride-containing environments, where localised breakdown of the passive film can initiate pitting corrosion despite nominally passive conditions [45, 51].

2.4 Breakdown of Passivity by Chloride

Although the native alumina film confers effective passivation across a broad pH range, as established in Sections 2.2 and 2.3, it is particularly vulnerable to localised breakdown in the presence of chloride ions [45, 51]. This vulnerability stems from the specific physicochemical properties of the chloride anion: its small ionic radius and relatively low hydration energy allow it to shed its hydration shell readily and adsorb directly onto the oxide surface, in contrast to larger or more strongly hydrated anions that remain solvated and interact only weakly with the film [45, 51].

The mechanism of passive film breakdown by chloride is most widely described by competitive adsorption at the oxide surface [43]. Chloride ions compete with hydroxyl ions and water molecules for adsorption sites on the passive film, and their preferential adsorption at surface defects, grain boundaries, or IMP/matrix interfaces locally disrupts the continuity and stoichiometry of the oxide [36, 51, 53]. This competitive displacement can be expressed as:

$$\mathrm{Al(OH)_{ads}} + \mathrm{Cl}^- \rightarrow \mathrm{AlCl_{ads}} + \mathrm{OH}^- \tag{2.5}$$

where the adsorbed hydroxide species that stabilise the passive film are progressively replaced by chloride [18, 51]. Once a critical local chloride concentration is reached, the thinned oxide layer ruptures, exposing the bare metal directly to the electrolyte [43, 51]. The exposed aluminium then undergoes accelerated anodic dissolution, forming soluble aluminium chloride according to [51]:

$$\mathrm{Al} + \mathrm{n\,Cl}^- \rightarrow \mathrm{AlCl_n} + 3e^- \tag{2.6}$$

The $\mathrm{AlCl_n}$ produced is highly soluble and readily hydrolyses in the presence of water, generating a locally acidic environment that further accelerates dissolution and inhibits repassivation [18, 51]:

$$AlCl_3 + 3\,H_2O \rightarrow Al(OH)_3 + 3\,HCl \tag{2.7}$$

This transition from passive to active dissolution is characterised electrochemically by the pitting potential (E_{pit}): below this threshold the passive film remains intact, whereas above it localised attack proceeds spontaneously [18, 43]. Increasing bulk chloride concentration shifts E_{pit} in the active direction, reducing the electrochemical window over which passive protection is maintained [51].

The consequences of chloride-induced depassivation are severe in the context of aluminium alloys: once the film ruptures, the autocatalytic pit growth mechanism described in Section 2.6 is activated, and repassivation becomes increasingly difficult as the local chemistry evolves [18, 51]. This underscores the inadequacy of purely barrier-based protection strategies and motivates the use of active corrosion protection systems, such as inhibitor-loaded LDH coatings, capable of suppressing film breakdown and restoring passivity at localised defects [6, 34].

2.5 Kinetics of Corrosion

The kinetics of corrosion are fundamentally governed by the rate of charge transfer at the interface between a metal and its surrounding aqueous environment [51]. During corrosion, metal atoms are oxidised at anodic sites, releasing electrons into the metal lattice, while electroactive species in solution simultaneously capture these electrons at cathodic sites [51]. These two partial reactions, the anodic oxidation and the cathodic reduction, are spatially and electrically coupled, and their relative rates determine the overall corrosion rate.

This charge exchange is confined to a highly structured interfacial region, approximately 10 nm in thickness, known as the electrical double layer [51]. Upon immersion of a metal in an electrolyte, the perturbation of the local molecular and ionic arrangement gives rise to a charge separation at the interface, which is sustained to maintain overall electroneutrality [45, 51]. The resulting double layer is structurally described by a combination of the Helmholtz, Stern, and Gouy–Chapman models, which together delineate three regions of decreasing order moving away from the surface [45, 51].

The innermost compact Stern layer contains oriented water molecules and specifically adsorbed species; of particular relevance is the adsorption of chloride ions, which, owing to their small ionic radius and low hydration energy, readily shed their hydration shell to adsorb directly onto the metal surface, locally disrupting the passive oxide film and rendering it the primary initiator of pitting corrosion [45, 51]. Beyond this lies the outer Helmholtz plane, marking the closest approach of solvated ionic species that retain their hydration shell and therefore cannot interact directly with the surface

[45, 51]. Further out, the diffuse Gouy–Chapman layer extends into the bulk electrolyte, consisting of a loosely organised ionic distribution whose thickness decreases with increasing electrolyte concentration [45, 51].

The architecture of the double layer directly controls corrosion kinetics by imposing physical and electrostatic barriers to ionic transport and charge transfer [45].

2.6 Pitting Corrosion of Aluminium Alloys

While the passive oxide film that forms spontaneously on aluminium provides effective protection across a broad range of conditions, it is susceptible to localised breakdown in the presence of aggressive anions, most notably chloride [43, 51]. This breakdown initiates pitting corrosion, a highly localised form of attack in which small, discrete cavities propagate into the metal while the surrounding surface remains nominally passive [45, 51].

Pit initiation is strongly associated with the presence of IMPs at the alloy surface. As described in Section 2.5, chloride ions preferentially adsorb at defect sites or at boundaries between IMPs and the aluminium matrix, where they locally displace oxygen and hydroxide ions from the passive film [18, 36, 51, 53]. Once a critical chloride concentration is reached at these sites, the passive film ruptures and active dissolution of the underlying metal commences [43, 51]. This breakdown is characterised by a transition from passive to active behaviour at a potential known as the pitting potential (E_{pit}), below which the passive film is stable [18, 43].

Following initiation, pit growth is sustained by an autocatalytic mechanism [18, 45]. Metal dissolution within the pit generates a local excess of cations, which attracts additional chloride ions to maintain charge balance [18, 45, 51]. The resulting accumulation of metal chloride salts undergoes hydrolysis, acidifying the pit interior and further accelerating dissolution [18, 43, 45, 51]. The surrounding cathodic regions support the oxygen reduction reaction, maintaining the electrochemical driving force for continued pit growth [18, 43, 45, 51]. Prior to reaching a stable propagating state, pits may repeatedly initiate and repassivate, a phenomenon known as metastable pitting, which is observable electrochemically as transient current fluctuations at potentials below E_{pit} [18, 45].

From a protective coating perspective, the critical objective is therefore not only to provide a barrier against electrolyte ingress, but also to supply active inhibition that can suppress these autocatalytic processes should the barrier be locally breached [6, 34].

2.7 Conventional Corrosion Protection Methods

Conventional corrosion protection systems for aluminium alloys, particularly in aerospace applications, typically consist of a multilayer structure comprising an anodic oxide or conversion coating, followed by a corrosion-inhibited primer and an organic topcoat [34]. These systems are designed to provide both passive barrier protection and active corrosion inhibition, and their general architecture is illustrated in [REFERENCIAR FIGURE].

Passive protection is provided by the coating layers themselves, which act as a physical barrier against electrolyte ingress, while active protection is achieved through corrosion inhibitors incorporated into the primer that become mobilised when coating defects allow electrolyte contact with the substrate [34]. Although anodised aluminium alloys generally exhibit superior corrosion and wear resistance, conversion coatings (CCs) are often preferred in industrial practice due to their lower cost, simpler processing, and greater application flexibility [4].

Historically, hexavalent chromium has played a central role in these protection systems, both as the basis of chromate conversion coatings (CCCs) and as a leachable inhibitor within primers, owing to its well-documented self-healing capability [5, 6]. However, Cr(VI) compounds are classified as highly toxic and carcinogenic, and their use is now subject to severe regulatory restrictions, creating an urgent need for environmentally benign alternatives [6, 34].

Among the most industrially advanced replacements, trivalent chromium process (TCP) coatings have gained considerable acceptance due to their good corrosion protection performance on aluminium alloys [4, 6, 42]. Nevertheless, TCP systems exhibit reduced effectiveness when combined with non-chromium primers, and the trace formation of Cr(VI) during processing remains an unresolved concern [4]. These limitations preclude TCP coatings from serving as a universal chromate replacement and motivate the continued development of alternative strategies [4].

Rare earth conversion coatings (RECCs), particularly cerium-based systems, have also been investigated as chromate-free alternatives owing to their lower toxicity and reported corrosion protection performance comparable to CCCs [4, 12, 23, 30]. The protection mechanism of cerium-based coatings relies primarily on the precipitation of insoluble cerium oxide and hydroxide species at cathodic sites, which suppresses the oxygen reduction reaction and thereby retards the overall corrosion process [23]. Although cerium-based systems can demonstrate active self-healing capabilities, their inferior stability in acidic environments and dependence on substrate surface chemistry, combined with the complexities of scaling up technically integrated solutions, have so far hindered their widespread industrial adoption [4].

2.8 Layered Double Hydroxides as a Chromate-Free Alternative

More recently, layered double hydroxides (LDHs) have emerged as a promising chromate-free alternative for corrosion protection. LDHs belong to a class of lamellar materials with brucite-like structures, consisting of positively charged metal hydroxide host layers with exchangeable anions located in the interlayer galleries to maintain charge balance [8, 10, 21, 24, 56]. Their general chemical formula is:

$$[\mathrm{M}^{2+}_{1-x}\mathrm{M}^{3+}_{x}(\mathrm{OH})_2]^{x+}(\mathrm{A}^{n-})_{x/n} \cdot m\mathrm{H_2O} \tag{2.8}$$

where M^{2+} and M^{3+} represent the divalent and trivalent metal cations that constitute the brucite-like layers, A^{n-} denotes the n-valent interlayer anions that compensate the positive layer charge, x is the molar ratio $\mathrm{M}^{3+}/(\mathrm{M}^{2+} + \mathrm{M}^{3+})$, typically in the range 0.2–0.33, and m is the number of moles of interlayer water [10, 21].

The composition of LDHs is highly tuneable: the cations M^{2+} and M^{3+} can be substituted by a wide range of metal ions, provided their ionic radii are compatible with octahedral coordination in the hydroxide layer [21]. The interaction between the hydroxide layers and the interlayer anions is relatively weak, relying primarily on electrostatic forces and hydrogen bonding [21]. This weak interlayer coupling confers LDHs with their most technologically relevant property: the ability to exchange interlayer anions readily with species present in the surrounding environment, a phenomenon known as anion exchange.

This anion exchange capability, combined with the tuneable chemical composition, has led to LDHs being widely investigated for applications including adsorption, catalysis, drug delivery, and flame retardancy [21]. In the context of corrosion protection, the interlayer space can be pre-loaded with corrosion inhibiting anions which are released in exchange for aggressive anions, most notably chloride, upon electrolyte ingress [6, 8]. This ion-exchange mechanism confers LDHs with an active, self-healing corrosion inhibition capability that is conceptually analogous to that of chromate-based systems, but without the associated toxicity. Following the pioneering work of Buchheit et al. [9], numerous studies have demonstrated enhanced corrosion resistance when LDH coatings are applied to aluminium, zinc, and magnesium alloys, as well as to anodised surfaces and galvanised steels [24].

2.8.1 Advantages of LDH

The anion exchange capability of LDHs is their most technologically relevant property for corrosion protection, and can be exploited in two complementary ways [8, 10, 21, 24, 56]:

1. **Controlled release of corrosion inhibitors:** LDHs can serve as hosts for anionic corrosion inhibitors pre-loaded into their interlayer galleries, releasing them on demand in response to environmental triggers such as local pH changes or the ingress of aggressive anions (e.g. Cl^-, SO_4^{2-}). This stimuli-responsive behaviour endows LDH-based systems with a self-healing capability: when appropriate inhibitors are intercalated, corrosion protection performance comparable to that of traditional Cr(VI)-based systems can be achieved [6, 8];

2. **Trapping of aggressive species:** Simultaneously, LDHs can selectively capture harmful anions, most notably chloride, within their interlayer galleries through anion exchange mechanism. This mean that they effectively function as nanotraps that reduce the local concentration of corrosive species at the metal surface [21, 24].

Beyond anion exchange, LDHs offer several additional protective mechanisms that further enhance their appeal as corrosion protection materials [10]. LDHs are capable of local dissolution and recrystallisation at coating defects, generating new crystals that fill damaged areas and restore barrier integrity reinforcing the self-healing behaviour described above [10]. When incorporated as fillers within organic coatings, LDH particles additionally provide a passive barrier contribution by occupying micro- and nanopores and increasing the tortuosity of ionic diffusion pathways, thereby impeding water and electrolyte permeation [10]. This so-called labyrinth effect can be further enhanced by combining LDHs with graphene, which introduces additional impermeable platelets into the diffusion path [10].

At the crystal level, LDHs can also contribute a structural barrier effect. As demonstrated by Bouali et al. [8], the exchange of nitrate ions for smaller anions such as chloride in ZnAl–LDH reduces the interlayer *d*-spacing, yielding a denser crystal structure that restricts the diffusion of species through the lattice. Finally, LDH-based systems can benefit from synergistic effects, whereby the simultaneous action of multiple inhibitors or protection mechanisms (ion exchange, barrier reinforcement, and recrystallisation) produces a combined protective performance that exceeds the sum of the individual contributions [10].

2.8.2 Synthesis of LDH

LDHs can be fabricated either ex situ as powders or in situ as films grown directly on metal substrates. Ex situ LDH powders are most commonly synthesised by co-precipitation, which can be carried out under variable or constant pH conditions [6]. Constant pH synthesis is generally preferred, as it yields purer and more crystalline products [6]. In this

approach, the pH is maintained by the simultaneous addition of an alkaline solution and a mixed-metal salt precursor solution containing the cations that will constitute the LDH structure [6]. Once synthesised, LDH powders can be dispersed within single-layer coating systems, such as sol–gel hybrid coatings [52, 58], or distributed across multilayer coating architectures, which is a common approach in industrial applications such as the automotive sector [6].

Despite this versatility, in situ LDH growth is generally considered more advantageous for corrosion protection, as it promotes the formation of chemical bonds between the LDH film and the substrate, resulting in stronger interfacial adhesion [6, 10, 20]. Furthermore, in situ film formation is a single-step process that is largely independent of substrate geometry, making it well suited for large-area and complex-geometry applications [6, 20].

The most widely adopted in situ method is hydrothermal treatment, also referred to as in situ co-precipitation by some authors [6], which can be regarded as an extension of the ex situ co-precipitation approach. In this work, the approach described by Bouali et al. [6] is adopted, in which the substrate itself serves as one of the metal precursors. For aluminium substrates, LDH films are grown by immersing the substrate in a solution containing divalent or monovalent metal cations (such as Zn^{2+}, Mg^{2+}, or Li^{+}) under controlled pH, temperature, and concentration conditions, while Al^{3+} ions are supplied through partial dissolution of the substrate. This approach produces strong interfacial bonding between the LDH film and the substrate [10, 20], and has been employed in numerous corrosion protection studies [24, 49, 50].

Beyond hydrothermal treatment, several alternative in situ fabrication routes have been explored. Electrodeposition offers significantly shorter processing times, approximately 300 s as reported by He et al. [21], and can be readily applied to substrates with complex geometries [10]. However, it generally yields weaker film adhesion and involves higher energy consumption [10]. Steam coating represents another promising alternative, combining good interfacial bonding with an environmentally benign process [10, 41]. Although previously limited to magnesium alloys, Matsui et al. [35] recently demonstrated its successful application to a die-cast aluminium alloy (ADC-12) for the formation of Mg–Al LDH films, extending the applicability of this technique to aluminium substrates.

2.8.3 Rationale for ZnAl–LDH on Aluminium Substrates

Among the many possible LDH compositions, ZnAl–LDH has emerged as one of the most studied systems for in situ corrosion protection of aluminium alloys. This preference is grounded in both chemical compatibility and processing considerations. As describedin Section 2.8.2,

in situ hydrothermal synthesis on aluminium substrates relies on the partial dissolution of the substrate to supply the trivalentAl^{3+} cation, while the divalent cation is provided externally through the synthesis solution [6, 10]. Among the candidate divalent cations, Zn^{2+} is particularly well suited: its ionic radius is compatible with octahedral coordination in the brucite-like layer, and zinc-based LDH systems have consistently demonstrated effective anion exchange kinetics and strong inhibitor release behaviour in chloride-containing environments [6, 8, 10, 49].

In comparison, MgAl–LDH requires higher synthesis temperatures and pH values to achieve crystalline film formation on aluminium substrates and has been more widely applied to magnesium alloys [6, 10]. LiAl–LDH, which incorporates monovalent lithium in place of a divalent cation, exhibits a distinct crystal structure and has been less extensively investigated for corrosion protection applications [4, 6]. The combination of established synthesis protocols, well-documented inhibitor intercalation behaviour, and demonstrated performance on aluminium alloys therefore makes ZnAl–LDH the most appropriate system for the present study.

2.8.4 Corrosion Inhibitors

LDHs are typically synthesised with nitrate ions as the initial interlayer anions, owing to their weak affinity for the LDH structure and consequently high exchangeability. Carbonate anions, by contrast, exhibit a significantly stronger affinity and therefore resist subsequent exchange, making them unsuitable as precursor anions [10]. Once synthesised, the LDH undergoes an anion-exchange step to intercalate the desired corrosion inhibiting species.

A wide range of inhibitor anions has been investigated for LDH-based corrosion protection systems. Vanadates are among the most extensively studied, with active corrosion protection of AA2024 demonstrated by Tedim et al. [49] and Yasakau et al. [52]. Zhang et al. [55] further showed that vanadate-intercalated ZnAl–LDH provides superior corrosion resistance relative to nitrate-intercalated LDH on the same alloy, while Zhou et al. [56] reported analogous protective behaviour for AZ91 magnesium alloy using ZnAl–LDH. Other inhibitors, including 2-mercaptobenzothiazole (MBT) and molybdate, have also been investigated [10, 48, 55]; however, for AA2024 these were found to offer inferior corrosion protection relative to vanadates [48, 55].

The relative performance of inhibitors is not universal, however, and is strongly dependent on both the LDH composition and the substrate chemistry. Matsui et al. [35] reported that molybdate-intercalated Mg–Al LDH provided superior corrosion resistance compared to vanadate-based systems when applied to ADC-12, an Al–Si–Cu die-cast alloy, underscoring the importance of tailoring inhibitor selection to the specific alloy system

under investigation.

Synergistic effects between inhibitor combinations have also been reported, further expanding the design space for LDH-based protection systems. Zhang et al. [55] demonstrated enhanced corrosion protection through the combination of cerium salts and vanadates, while Tedim et al. [48] showed that LDH nanocontainers co-loaded with vanadate and MBT anions yielded a synergistic anticorrosion effect exceeding that of either inhibitor alone. Beyond inorganic inhibitors, Lamaka et al. [28] reported that organic species — including 8-hydroxyquinoline (8-HQ), salicylaldoxime, and quinaldic acid — can suppress corrosion of AA2024 as effectively as, or in some cases more effectively than, MBT and cerium salts, highlighting the potential of organic inhibitors as complementary or alternative active species in LDH interlayer systems.

2.9 Influence of IMPs on LDH growth

AC46000 contains a diverse range of intermetallic particles (IMPs), including copper-rich phases such as Al_2Cu and Al_7Cu_2Fe, iron-rich phases such as Al_5FeSi and $Al_{15}(Fe, Mn)_3Si_2$, and eutectic silicon particles. To assess the influence of these IMPs on LDH growth and corrosion behavior, it is important to consider their electrochemical potential relative to the aluminium matrix [19, 26].

The copper-rich phases are strongly cathodic relative to the Al matrix, with Al_2Cu exhibiting a potential difference of approximately +400 mV [19]. This drives intense localized micro-galvanic coupling, promoting rapid oxygen reduction and a sharp rise in local pH. In the context of LDH growth, these conditions trigger the preferential and rapid precipitation of thick, "flower-like" LDH islands directly over the cathodic sites [11]. This localized growth is sustained by the anodic dissolution of the surrounding aluminium matrix, commonly referred to as trenching [7]. The trenching process generates voids at the periphery of the intermetallic particles where LDH flakes fail to nucleate [7]. These uncoated gaps compromise the corrosion resistance of the substrate, as chloride ions and other aggressive species can readily penetrate the exposed defects and initiate pitting corrosion [7]. The resulting inhomogeneous LDH film also reduces the adhesion of subsequently applied polymer coatings or paints [7], and in severe cases extensive trenching can render the intermetallic particles prone to detachment, further undermining the integrity of overlying layers [7].

The iron-rich phases are also strongly cathodic, approximately +300 mV above the aluminium matrix [19], and the galvanic coupling they generate similarly leads to inhomogeneous LDH growth and increased susceptibility to corrosion.

Although eutectic silicon particles are likewise cathodic, with a potential difference of approximately +250 mV relative to the Al matrix, they are electrochemically inert and do not act as nucleation sites for LDH. Since they provide no source of the metal cations (Al^{2+}/Al^{3+}, Mg^{2+}) required for LDH formation, as explain in section 2.8.2, no coating growth is triggered at these sites [15, 19].

2.9.1 Pre-Treatment

Given the detrimental influence of these IMPs on LDH growth homogeneity and overall coating quality, their removal from the alloy surface prior to conversion coating is essential. To this end, various pre-treatment strategies have been developed, but the most widely adopted approach consists of a multistep procedure comprising degreasing, alkaline etching, and acid pickling, applied sequentially [34].

Degreasing constitutes the first pre-treatment step, with the primary objective of removing surface contamination, most notably oils and lubricants introduced during the manufacturing process. This step is critical to ensure full surface wettability, thereby guaranteeing that subsequent processing stages act uniformly across the substrate [34].

The second step, alkaline etching, is aimed at dissolving the native oxide layer that forms spontaneously on aluminium surfaces, as well as removing surface-exposed intermetallic particles. The cathodic IMPs act as highly active sites for oxygen reduction, generating a localised rise in pH at their immediate vicinity. This accelerates the anodic dissolution of the surrounding aluminium matrix, progressively undermining the mechanical support of the particles [39]. As the matrix recedes, scallop-shaped voids form at the particle periphery, eventually causing the IMPs to detach from the surface, a process known as selective dealloying [25, 39]. Since many of the constituent alloying elements released during this process are insoluble in alkaline media, they accumulate on the surface as a loosely adherent residue known as smut, the removal of which necessitates a subsequent acid pickling step [25, 34, 39].

Nitric acid (HNO_3) is widely used for desmutting because it naturally passivates the aluminum matrix while acting as a powerful oxidant [25]. It successfully targets and dissolves the dealloyed metallic smut, including copper, iron, and manganese residues. Despite this, Nitric acid alone is ineffective against silicon-rich intermetallic residues [13]. To remove these, fluorides (such as hydrofluoric acid or ammonium bifluoride) must be added to the pickling bath [2, 31]. The fluoride ions dissolve the silica and complex the remaining silicon remnants so they can be washed away [2, 31].

2.10 Equivalent Circuit Models for EIS

2.10.1 Randles Equivalent Circuit (REC)

Determining an appropriate equivalent circuit model (ECM) for electrochemical impedance spectroscopy (EIS) spectra is among the most critical steps in impedance analysis, as it enables the deconvolution of overlapping electrochemical processes and their quantification through physically meaningful parameters. One of the most widely used models is the Randles equivalent circuit, which consists of a solution resistance (R_s) in series with a parallel combination of a charge-transfer resistance (R_ct) and a double-layer capacitance (C_dl), as represented in [REFERENCIAR FIGURE] [14, 29].

Time constants

Before discussing each circuit element individually, it is necessary to introduce the concept of the time constant, as it underpins the physical interpretation of the impedance response. A time constant (τ) defines the characteristic duration required for a given electrochemical process to relax from a transient state towards a new equilibrium [14]. In an electrical equivalent circuit, it is defined as the product of a resistance and a capacitance ($\tau = RC$), and governs the rate at which the system responds to an applied perturbation [29]. Because an electrochemical interface involves multiple concurrent processes (such as charge transfer, ionic diffusion, and intermediate adsorption) each process is characterised by its own distinct time constant [14]. For instance, the kinetic time constant of an interface is given by $\tau_k = R_\mathrm{ct}C_\mathrm{dl}$ [29]. In the frequency domain, each time constant manifests as a characteristic angular frequency ($\omega_c = \frac{1}{RC}$), which marks the transition between different impedance regimes — for example, from a capacitively controlled response to a diffusion-dominated one [14, 29]. Their resolution in the impedance spectrum is therefore a prerequisite for the unambiguous assignment of ECM elements to specific interfacial processes.

Solution Resistance

R_s, also referred to as the ohmic or solution resistance, quantifies the resistive potential drop occurring between the working electrode and the reference electrode [29, 37]. Its magnitude is governed by the specific conductivity of the bulk electrolyte and the cell geometry [37]. In a Nyquist representation, R_s is readily identified as the high-frequency intercept of the impedance data with the real axis, corresponding to the condition under which the reactive elements of the circuit are effectively

short-circuited and the purely resistive contribution dominates the response.

Charge-Transfer Resistance

R_{ct} is the real component of the Faradaic impedance governing the transfer of electrons across the electrode/electrolyte interface to or from electroactive species in solution [29]. As a strictly kinetic parameter, its value is inversely proportional to the heterogeneous rate constants of the electrode reactions, and it is sometimes referred to as polarisation resistance in the context of Faradaic processes [14, 29]. This inverse relationship extends directly to the corrosion rate: according to the Stern–Geary relationship, the instantaneous corrosion current density i_{corr} is obtained by dividing a proportionality constant B by R_{ct} [27]:

$$i_{\mathrm{corr}} = \frac{B}{R_{\mathrm{ct}}} \tag{2.9}$$

Consequently, a higher R_{ct} reflects slower interfacial kinetics, a lower corrosion current density, and therefore improved corrosion protection [27]. In the Nyquist plot, R_{ct} manifests as the diameter of the semicircle observed in the high-frequency to mid-frequency range, a feature arising directly from its coupling with C_{dl} to form the kinetic time constant $\tau_k = R_{\mathrm{ct}} C_{\mathrm{dl}}$ [14, 29].

Double Layer Capacitance

C_{dl} is the capacitance that inherently forms at the electrode/electrolyte interface as a consequence of the charge separation between ionic species in solution and charges within the electrode, as described in section 2.5 [27, 37]. While liquid electrodes can behave as nearly ideal capacitors, solid electrodes invariably exhibit frequency dispersion due to surface heterogeneities, roughness, porosity, and non-uniform current distributions [14, 29]. To account for this non-ideal behaviour, the double layer at solid electrodes is most accurately represented by a constant phase element (CPE) rather than an ideal capacitor [14, 29, 37].

From a corrosion monitoring perspective, C_{dl} is a particularly sensitive indicator of coating degradation and the onset of localised pitting, often preceding any macroscopic visual evidence of corrosion [27]. As a protective coating degrades or delaminates, the electrolyte gains direct access to the underlying metal substrate, initiating underfilm corrosion [27]. The measured capacitance at defect sites scales directly with the delaminated area. Consequently, progressive coating breakdown exposes an increasingly large area of bare metal, driving C_{dl} proportionally higher [27]. This area dependence is readily understood through the expression for a planar capacitor:

$$C = \frac{\epsilon \epsilon_0 A}{d} \tag{2.10}$$

where ϵ is the relative permittivity of the interfacial medium, ϵ_0 is the permittivity of free space, A is the effective interfacial area, and d is the charge separation distance. Additionally, as localised corrosion progresses, for instance through pitting, the electrode surface becomes increasingly rough and geometrically complex, further enlarging the effective interfacial area and driving C_{dl} to higher values [27, 29].

2.10.2 More advanced circuits

While the simple Randles circuit provides an adequate description of a bare metal undergoing a single-step charge transfer reaction, real-world systems exhibit multiple time constants that cannot be captured by a single RC network. To model these more complex responses, advanced equivalent circuits are constructed by combining multiple resistor–capacitor (RC) or resistor–constant phase element (R-CPE) sub-networks.

When a system displays two distinct time constants, which typically manifest as two partially or fully resolved semicircles in the Nyquist plot, the two most common topologies are the series (Voigt-type) configuration [FIGURE X] and the nested (ladder) configuration [FIGURE Y]. In the series configuration, each RC sub-network represents a physically distinct and sequential process that operates independently of the others [27, 29]. The nested configuration, by contrast, is generally preferred in corrosion science for the description of defective or porous protective coatings, where simultaneous and spatially overlapping processes occur [27]. In this topology, the outer RC network represents the macroscopic response of the coating itself which can be characterised by the film capacitance and the film resistance. The inner nested RC network on the other hand describes the actively corroding metal/electrolyte interface at the base of the pores, represented by the double-layer capacitance and the charge-transfer resistance [27].

It is important to note, however, that despite their distinct physical interpretations, a series Voigt circuit and a nested ladder circuit can be mathematically equivalent, producing identical impedance values and indistinguishable complex plane plots [29]. The selection of the nested topology must therefore be justified by the physical reality of the system under investigation rather than by mathematical preference alone [29].

In this nested configuration, the outer time constant is associated with the response of the protective film such as an externally applied organic coating, a native oxide layer, or a conversion coating like an LDH film.

Film or Oxide Resistance

The film resistance, R_{film} plays an analogous role to R_{ct} in the sense that both manifest as semicircle diameters in the Nyquist plot and both inversely reflect the degree of protection afforded at their respective interface. However, while R_{ct} is a kinetic parameter governing the rate of electron transfer across the electrode/electrolyte interface, R_{film} is an ionic transport parameter [27]. It represents the resistance to ionic current flow both through the bulk of the film itself and through any microscopic pores and defects connecting the bulk electrolyte to the metal/film interface [27]. Just as a high R_{ct} indicates sluggish interfacial reaction kinetics, a high R_{film} restricts ionic transport across the film and is therefore directly associated with superior corrosion protection [27, 29].

Film or Oxide Capacitance

The film capacitance, C_{film}, is equally informative and serves as a sensitive early indicator of coating degradation, often responding before any macroscopic evidence of corrosion becomes apparent. Its evolution is most directly governed by water uptake: upon immersion in an electrolyte, water progressively penetrates the pores of the coating [29]. Since water possesses a substantially higher dielectric constant (approximately 80) relative to that of a typical coating, its ingress causes a measurable increase in C_{film} [29, 37]. Monitoring this increase is of practical importance, as water uptake is frequently a precursor to active substrate corrosion [27]. More generally, a progressive increase in C_{film} over time is indicative of ongoing coating degradation and a reduction in protective performance.

Warburg Element and Diffusion-Controlled Processes

In electrochemical systems where mass transport becomes a rate-limiting step, the impedance response cannot be fully described by purely kinetic elements such as resistors and capacitors. This situation arises when the rate of an electrochemical reaction at the electrode surface exceeds the rate at which reactants can be supplied or products removed by diffusion through the electrolyte or a surface layer [3, 40]. Under these conditions, a concentration gradient develops near the electrode surface, and the resulting diffusion impedance manifests in the Nyquist plot as a characteristic 45° linear tail at low frequencies, known as the Warburg impedance [40].

In the context of aluminium alloy corrosion in chloride-containing electrolytes, Warburg-type behaviour may arise at extended immersion times, when diffusion of aggressive ionic species through a thickening corrosion product layer or a defective coating becomes the rate-limiting

transport mechanism [40]. In bounded systems of this kind, where diffusion is confined to a layer of finite thickness, this contribution is formally represented by a finite-length Warburg element [3, 22]. As a practical simplification, the finite-length Warburg element can be approximated by an additional RC sub-circuit, in which the resistance captures the steady-state diffusion resistance and the capacitance reflects the charge storage associated with concentration polarisation [3, 22]. This approximation is particularly convenient when automated fitting procedures are employed, as it avoids the introduction of fractional impedance elements while preserving the essential low-frequency behaviour of the system.

2.10.3 Inhibitor Efficiency from EIS Parameters

Electrochemical impedance spectroscopy provides a non-destructive means of quantifying the protective performance of corrosion inhibitors through the analysis of equivalent circuit parameters extracted from the impedance response [28, 40]. The most direct indicator of inhibitor efficiency is the charge transfer resistance R_{ct}. Since it is inversely proportional to the corrosion current density through the Stern–Geary relation (Equation 2.9), an increase in R_ct upon addition of an inhibitor directly reflects a reduction in the rate of anodic dissolution or cathodic reduction at active sites [40, 43]. The inhibitor efficiency η can therefore be expressed as:

$$\eta = \left(1 - \frac{R_{ct,0}}{R_{ct,i}}\right) \times 100\,\% \tag{2.11}$$

where $R_{ct,0}$ and $R_{ct,i}$ are the polarisation resistances measured in the absence and presence of the inhibitor, respectively [28, 40]. Beyond R_p, the double layer capacitance C_{dl} provides complementary information: a decrease in C_{dl} upon inhibitor addition is indicative of adsorption of inhibitor molecules at the electrode surface, which displaces the water molecules and ions previously occupying the double layer and reduces its effective dielectric permittivity [40, 45]. In systems where inhibitors are released from a reservoir such as an LDH coating, the evolution of both R_{film} and R_{ct} over immersion time provides a particularly informative picture: an initial decrease in R_{film} due to electrolyte uptake followed by a recovery or stabilisation of R_{ct} is the electrochemical signature of active inhibitor release compensating for barrier degradation [6, 34, 48].

Chapter 3

Methodology

3.1 Pre-selection of inhibitors

As discussed in WP2, the first task of the project was to do a pre-selection of the inhibitors using electrochemical impedance spectroscopy (EIS). For this purpose bare metal substrates were sequentially polished using 120, 600, 1200 and 2500 grit sandpaper under water. After polishing, the samples were rinsed with deionized water and subsequently air-dried.

The selected corrosion inhibitors are listed in Table 3.1, with a standard concentration of 0.005 M, except for those with lower saturation limits. Sodium chloride (NaCl) at 0.05 M was used as the electrolyte. This concentration is commonly chosen because it provides high conductivity, resulting in low solution impedance, and allows easy comparison with existing studies. The pH of each solution was also measured prior to experimentation.

Table 3.1: Composition of the solutions for testing the effectiveness of the inhibitors and respective pH values

No.	Solution Composition	Concentration of the reagent	pH
1	NaCl 0.05 M	—	7.38
2	NaCl 0.05 M + $NaVO_3$	0.005 M	7.41
3	NaCl 0.05 M + Na_2MoO_4	0.005 M	6.70
4	NaCl 0.05 M + 2-mercaptobenzothiazole	Saturated	5.67
5	NaCl 0.05 M + benzotriazole	0.005 M	5.75
6	NaCl 0.05 M + 8-hydroxyquinoline	Saturated	6.42
7	NaCl 0.05 M + L-cysteine	0.005 M	6.54

EIS measurements were then performed inside a Faraday cage using a Gamry Interface 1000 potentiostat linked to a computer and Gamry Framework v.6.33 and Echem Analyst v.6.33 software packages for data

acquisition and analysis. Measurements were conducted at open circuit potential with a 10 mV sinusoidal perturbation over a frequency range of 100 kHz to 10 mHz, using 10 points per decade. For the initial measurement, the lower frequency limit was set to 100 mHz due to insufficient sample stability.

A conventional three-electrode configuration was used, comprising a saturated calomel electrode (SCE) as the RE, a platinum foil as the CE, and the exposed AC46000 substrate as the WE. The samples were immersed for a total duration of seven days, with EIS measurements collected at 0 h, 1 h, 4 h, 8 h, 24 h, 48 h, 72 h, 120 h, and 168 h.

3.2 Determine ECM for EIS

Determining an appropriate equivalent circuit model (ECM) for electrochemical impedance spectroscopy (EIS) spectra is among the most important steps in impedance analysis, as it enables the deconvolution of overlapping electrochemical processes and their quantification through physically meaningful parameters, such as charge transfer resistance (R_{ct}), film resistance (R_{film}), and double-layer capacitance (C_{dl}).

Despite its centrality to the analysis, ECM identification remains a laborious task. Commercial software packages such as ZView and Gamry Echem Analyst rely on nonlinear least-squares (NLLS) fitting routines, most commonly the Levenberg-Marquardt algorithm, which are inherently sensitive to the choice of initial parameter estimates [16, 57]. While heuristic approaches exist to guide these estimates, such as reading characteristic resistances from the diameters of semicircular arcs in the Nyquist representation or extracting time constants from Bode phase plots, the process remains largely manual and iterative, demanding considerable operator experience to avoid convergence to local minima or physically unreasonable solutions.

In response to these limitations, a number of open-source, programmatic alternatives have been developed, predominantly in Python. Among these, `impedance.py` provides a flexible framework for ECM fitting and validation [38]. More recently, tools such as `AutoECM` and `AutoEIS` have incorporated machine learning methodologies into the workflow. AutoECM employs supervised classification models such as Random Forest, XGBoost (XGB), and convolutional neural network (CNN) architectures [46]. These are trained on libraries of previously validated circuit-spectrum pairs to predict candidate ECMs for new datasets [46]. AutoEIS, by contrast, adopts a probabilistic framework grounded in Bayesian inference, enabling uncertainty quantification in both circuit structure selection and parameter estimation [54]. A notable limitation shared by both tools, however, is the apparent discontinuation of active

maintenance by their respective developers. As a consequence, dependency incompatibilities with more recent versions of core scientific Python libraries have rendered them largely non-functional in current environments.

Given this landscape, `impedance.py` emerges as the most viable open-source option. In its standard implementation, it operates analogously to commercial software: the user must supply the impedance dataset, an *a priori* circuit string, and initial parameter guesses. Two optional fitting configurations are available. The first, `weight_by_modulus`, applies the modulus of the complex impedance as a frequency-dependent weighting factor which ensures that data points spanning several decades of impedance magnitude contribute proportionally to the objective function. The second, `global_opt`, invokes a basin-hopping algorithm, which combines stochastic perturbation of parameter coordinates with local minimization and a Metropolis-type acceptance criterion to escape local minima. Importantly, `global_opt` is incompatible with `weight_by_modulus` and given that EIS datasets span several decades in frequency, commonly from 10 mHz to 100 kHz, and correspondingly large ranges in impedance magnitude, modulus weighting is generally considered essential to prevent low-frequency, high-impedance data from disproportionately dominating the fit residuals.

To overcome the dependence on user-supplied initial guesses while retaining the precision of local optimization, a hybrid fitting framework was developed building upon impedance.py and the Differential Evolution (DE) algorithm. DE is a stochastic, population-based global optimization metaheuristic well-suited to high-dimensional, non-differentiable, and multimodal objective functions [1, 47]. The algorithm evolves a population of candidate solutions across successive generations through three operators: mutation, which generates trial vectors via linear combinations of population members; crossover, which probabilistically exchanges parameter values between candidate and trial vectors; and selection, which retains whichever vector yields a lower objective function value [1, 47]. Crucially, DE requires no gradient information making it less likely to be stuck at local minima [32] and therefore particularly appropriate for the complex, rugged parameter landscapes characteristic of multi-element ECM fitting.

In the proposed workflow, the user supplies only physically motivated bounds for each circuit element rather than precise initial estimates. The DE algorithm then explores this parameter space to identify the order of magnitude and approximate value of each component. To accelerate convergence, given that circuit element values typically span many orders of magnitude, the optimization is performed in logarithmic space, transforming the search domain such that each decade is treated uniformly. This logarithmic reparameterization substantially improves the efficiency of

the population-based search and reduces sensitivity to the scale disparity between, for example, charge-transfer resistances on the order of kilohms and double-layer capacitances on the order of microfarads. Once the DE stage yields a sufficiently accurate global estimate, the resulting parameter vector is passed as the initial condition to the Levenberg-Marquardt local optimizer within `impedance.py`, with `weight_by_modulus` activated, to refine the solution and obtain statistically meaningful parameter estimates together with their associated uncertainties.

3.3 Pre-treatments

As previously discussed, the presence of intermetallic particles (IMPs) on the surface of the aluminium alloy can negatively affect LDH growth homogeneity and must therefore be removed prior to coating deposition. Two pre-treatment procedures were evaluated: a simplified chemical treatment and anindustrial multistep treatment.

The first procedure consisted of alkaline cleaning in a 0.1 M NaOH solution at room temperature for 120 s, followed by acid pickling in a 0.1 M HNO_3 solution for 480 s. Each step was followed by rinsing with deionised water, and the specimenswere finally dried in air.

The second procedure followed an industrial multistep protocol. Degreasing was performed in Metaclean T2001 (an alkaline cleaner based on metalsilicates with complexing and surface-active agents) at a concentration of $48\,\mathrm{g\,L^{-1}}$ and a temperature of approximately 65 °C for 10 min. Although the recommended immersion time is 25 min, a shorter duration was deemed sufficient given that no oils or lubricants were employed during specimen preparation. Following rinsing with deionised water, the specimens were alkaline etched in Turco Liquid Aluminetch N2 (a sodium hydroxide and phosphate-based solution) at $38\,\mathrm{g\,L^{-1}}$ and 65 °C for 45 s, and subsequently rinsed again with deionised water. Desmutting was then carried out in Turco Liquid Smutgo NC (a formulation based on ferric sulfate, nitric acid, sodium hydrogendifluoride, and sulfuric acid) at a concentration of $180\,\mathrm{mL\,L^{-1}}$ and 30 °C for approximately 5 min, before a final rinse with deionised water and drying in air.

To assess the effectiveness of each pre-treatment, scanning electron microscopy (SEM) and energy dispersive X-ray spectroscopy (EDS) analyses were conducted on the treated surfaces. The objective was to identify which IMPs remained on the surface following each procedure and thereby determine which pre-treatment was most conducive to homogeneous LDH growth.

3.4 LDH Synthesis

To assess the influence of the pre-treatment on LDH growth, films were grown on three sets of specimens: those subjected to the chemical pre-treatment, those subjected to the industrial pre-treatment, and mechanically polished reference specimens. In all cases, the same in situ hydrothermal synthesis procedure was employed to ensure comparability.

The synthesis solution was prepared by first dissolving NH_4NO_3 at a concentration of 0.6 M in 600 mL of deionised water (resistivity 18 MΩ cm) under magnetic stirring. The pH of this solution was measured and found to be below 5. $Zn(NO_3)_2 \cdot 6\,H_2O$ was then added at a concentration of 0.1 M, together with an additional 300 mL of deionised water. The pH was subsequently adjusted to 6.5 ± 0.1 using a 5% ammonia solution. Deionised water was then added to bring the total volume to 1 L, and the pH was measured and corrected to 6.5 ± 0.1 if required.

For LDH film growth, 300 mL of the synthesis solution was transferred to a vessel and pre-heated to 95 °C, sufficient for the simultaneous immersion of three specimens. The specimens were suspended vertically and fully immersed in the solution for 1 h under magnetic stirring. Upon completion, the specimens were removed, rinsed with deionised water, and dried with compressed air.

To characterise the LDH films and compare growth across the different substrate conditions, X-ray diffraction (XRD) analysis was conducted. From the diffraction patterns, the basal spacing (d_{003}) was determined using Bragg's law, providing structural confirmation of LDH formation and enabling comparison of film crystallinity across the different pre-treatment conditions.

3.5 Inhibitor incorporation

To incorporate corrosion inhibiting anions into the LDH interlayer galleries, anion exchange was performed by immersing the as-grown LDH films in a 0.1 M inhibitor solution at 25 °C for 3 h. Following this, the specimens were rinsed with deionised water and dried with compressed air.

Chapter 4

Results

Present the results of your project clearly and concisely, using tables and figures where necessary.

Chapter 5

Discussion

Interpret the results and discuss their implications. Compare your findings with previous research. Discuss any limitations of your study.

Chapter 6

Conclusion & Future Work

Sum up the main findings and their importance, and discuss how they have the WBS going forward.

Bibliography

[1] Mohamad Faiz Ahmad, Nor Ashidi Mat Isa, Wei Hong Lim, and Koon Meng Ang. Differential evolution: A recent review based on state-of-the-art works. *Alexandria Engineering Journal*, 61(5):3831–3872, 2022. doi: 10.1016/j.aej.2021.09.013.

[2] Albert L. Askin and Paul B. Schultz. Method for desmutting aluminum alloys having a highly reflective surface. US Patent 5,417,819, May 1995. Assigned to Aluminum Company of America.

[3] Evgenij Barsoukov and J. Ross Macdonald. *Impedance Spectroscopy: Theory, Experiment, and Applications*. John Wiley & Sons, Hoboken, New Jersey, 2 edition, 2005. ISBN 9780471647492. doi: 10.1002/0471716243.

[4] Markus Becker. Chromate-free chemical conversion coatings for aluminum alloys. *Corrosion Reviews*, 37(4):321–342, 2019. doi: 10.1515/corrrev-2019-0032.

[5] Martin Beneke and Sonja Nixon. Chromate free surface pre-treatments for aluminium alloys. Technical report, AIRBUS, ASETSDefense, dec 2016. Technical Presentation.

[6] A. C. Bouali, M. Serdechnova, C. Blawert, J. Tedim, M. G. S. Ferreira, and M. L. Zheludkevich. Layered double hydroxides (LDHs) as functional materials for the corrosion protection of aluminum alloys: A review. *Applied Materials Today*, 21:100857, 2020. doi: 10.1016/j.apmt.2020.100857.

[7] A. C. Bouali, M. Serdechnova, K. A. Yasakau, A. Lutz, G. Wiese, H. Terryn, M. G. S. Ferreira, and M. L. Zheludkevich. The Role of Cu-Based Intermetallic on the Direct Growth of a ZnAl LDH Film on AA2024. *Journal of The Electrochemical Society*, 169(8):081501, 2022. doi: 10.1149/1945-7111/ac83f5.

[8] Anissa C. Bouali, Mariia H. Iuzviuk, Maria Serdechnova, Kiryl A. Yasakau, D. C. Florian Wieland, Gleb Dovzhenko, Hanna Maltanava,

Igor A. Zobkalo, Mario G. S. Ferreira, and Mikhail L. Zheludkevich. Zn-Al LDH growth on AA2024 and zinc and their intercalation with chloride: Comparison of crystal structure and kinetics. *Applied Surface Science*, 501:144027, 2020. doi: 10.1016/j.apsusc.2019.144027.

[9] Rudolph G. Buchheit, Hong Guan, Suhakar Mahajanam, and Fariaty Wong. Active corrosion protection and corrosion sensing in chromate-free organic coatings. *Progress in Organic Coatings*, 47(3-4):174–182, 2003. doi: 10.1016/S0300-9440(03)00130-3.

[10] Yanhui Cao, Dajiang Zheng, Fan Zhang, Jinshan Pan, and Changjian Lin. Layered double hydroxide (LDH) for multi-functionalized corrosion protection of metals: A review. *Journal of Materials Science & Technology*, 102:232–263, 2022. doi: 10.1016/j.jmst.2021.05.078.

[11] Yanhui Cao, Shenao Wang, Congshu Huang, Jingjing Wang, Haixia Qi, Lieji Yang, Hui Li, Dajiang Zheng, and Changjian Lin. Study on the influence mechanism of intermetallic compounds (IMCs) in aluminum alloy AA7075 on the growth behavior and corrosion resistance of layered double hydroxide films. *Corrosion Science*, 265:113809, 2026. doi: 10.1016/j.corsci.2026.113809.

[12] S. M. Cohen. Replacements for Chromium Pretreatments on Aluminum. *Corrosion*, 51(1):71–78, 1995. doi: 10.5006/1.3333898.

[13] C. M. Cotell, J. A. Sprague, and F. A. Smidt. *Surface Engineering of Aluminum and Aluminum Alloys*, pages 784–804. ASM International, 1994. doi: 10.1361/asmhba0001308.

[14] Sutanu Das, Ankita Banerjee, Upendranath Nandi, and Aswini Ghosh. Critical review on the analysis of electrochemical impedance spectroscopy data. *Journal of Applied Physics*, 138(12):125002, 2025. doi: 10.1063/5.0275205.

[15] Rubén del Olmo, Reynier I. Revilla, Francesco Andreatta, and Iris De Graeve. Layered double hydroxides on additively manufactured Al-Si alloy: Growth mechanism, microstructure and corrosion performance. *Applied Surface Science*, 710:163891, 2025. doi: 10.1016/j.apsusc.2024.163891.

[16] Gamry Instruments. Equivalent Circuit Modeling Using the Gamry Electrochemical Impedance Spectroscopy Software. Application note, Gamry Instruments, 2023. URL `https://www.gamry.com/application-notes/EIS/equivalent-circuit-modeling-using-the-gamry-electrochemical-impedance-spectroscopy-software/`.

[17] Vishant Garg, Maxime Magnan, Sandrine Zanna, Antoine Seyeux, Frédéric Wiame, Vincent Maurice, and Philippe Marcus. Corrosion inhibition mechanisms of 2-mercaptobenzothiazole on aa2024 t3 aluminium alloy. *npj Materials Degradation*, 2025. doi: 10.1038/s41529-025-00653-z.

[18] Edward Ghali. *Corrosion Resistance of Aluminum and Magnesium Alloys: Understanding, Performance, and Testing*. John Wiley & Sons, Inc., Hoboken, New Jersey, 2010. ISBN 978-0-471-71576-4.

[19] Senka Gudić, Ladislav Vrsalović, Jure Krolo, Aleš Nagode, Ivana Dumanić Labetić, and Branimir Lela. Corrosion Behaviour of Recycled Aluminium AlSi9Cu3(Fe) Machining Chips by Hot Extrusion and Thixoforming. *Sustainability*, 16(4):1358, 2024. doi: 10.3390/su16041358.

[20] Xiaoxiao Guo, Sailong Xu, Lili Zhao, Wei Lu, Fazhi Zhang, David G. Evans, and Xue Duan. One-Step Hydrothermal Crystallization of a Layered Double Hydroxide/Alumina Bilayer Film on Aluminum and Its Corrosion Resistance Properties. *Langmuir*, 25(17):9895–9902, 2009. doi: 10.1021/la901032q.

[21] Qing-Qing He, Ming-Jie Zhou, and Ji-Ming Hu. Electrodeposited Zn-Al layered double hydroxide films for corrosion protection of aluminum alloys. *Electrochimica Acta*, 355:136796, 2020. doi: 10.1016/j.electacta.2020.136796.

[22] Jun Huang. Diffusion impedance of electroactive materials, electrolytic solutions and porous electrodes: Warburg impedance and beyond. *Electrochimica Acta*, 281:170–188, 2018. doi: 10.1016/j.electacta.2018.05.136.

[23] A. E. Hughes, F. H. Scholes, A. M. Glenn, D. Lau, T. H. Muster, and S. G. Hardin. Factors influencing the deposition of Ce-based conversion coatings, part I: The role of Al^{3+} ions. *Surface and Coatings Technology*, 203:2927–2936, 2009. doi: 10.1016/j.surfcoat.2009.03.012.

[24] Mariia H. Iuzviuk, Anissa C. Bouali, Maria Serdechnova, Kiryl A. Yasakau, D. C. Florian Wieland, Gleb Dovzhenko, Aliaksandr Mikhailau, Carsten Blawert, Igor A. Zobkalo, Mario G. S. Ferreira, and Mikhail L. Zheludkevich. In situ kinetics studies of Zn–Al LDH intercalation with corrosion related species. *Physical Chemistry Chemical Physics*, 22:17574–17585, 2020. doi: 10.1039/d0cp01765e.

[25] Zelong Jin, Changrun Cai, Yudie Yuan, DaeHoon Kang, John Hunter, and Xiaorong Zhou. The behaviour of AA5754 and AA5052 aluminium alloys in alkaline etching solution: Similarity and difference. *Materials*

Characterization, 168:110534, 2020. doi: 10.1016/j.matchar.2020.110534.

[26] Justyna Kasińska, Dana Bolibruchová, and Marek Matejka. The Influence of Remelting on the Properties of AlSi9Cu3 Alloy with Higher Iron Content. *Materials (Basel)*, 13(3):575, 2020. doi: 10.3390/ma13030575.

[27] Robert G. Kelly, John R. Scully, David W. Shoesmith, and Rudolph G. Buchheit. *Electrochemical Techniques in Corrosion Science and Engineering*. Marcel Dekker, Inc., New York, NY, 2002. ISBN 0-8247-9917-8.

[28] S. V. Lamaka, M. L. Zheludkevich, K. A. Yasakau, M. F. Montemor, and M. G. S. Ferreira. High effective organic corrosion inhibitors for 2024 aluminium alloy. *Electrochimica Acta*, 52(25):7231–7247, 2007. doi: 10.1016/j.electacta.2007.05.037.

[29] Andrzej Lasia. *Electrochemical Impedance Spectroscopy and its Applications*. Springer New York, New York, NY, 2014. ISBN 978-1-4614-8932-0. doi: 10.1007/978-1-4614-8933-7.

[30] D. Lau, A. M. Glenn, A. E. Hughes, F. H. Scholes, T. H. Muster, and S. G. Hardin. Factors influencing the deposition of Ce-based conversion coatings, Part II: The role of localised reactions. *Surface and Coatings Technology*, 203:2937–2945, 2009. doi: 10.1016/j.surfcoat.2009.03.011.

[31] Eul-Kyu Lee. Surface treatment composition and method for removing Si component and reduced metal salt produced on the aluminum die cast material in etching process. US Patent 7,405,189, Jul 2008. Assigned to Cheon Young Chemical Co., Ltd.

[32] Bruno Scalia C. F. Leite. Differential Evolution: An alternative to nonlinear convex optimization. Medium (Towards Data Science), Apr 2022. URL `https://medium.com/data-science/differential-evolution-an-alternative-to-nonlinear-convex-optimization-690a123f3413`.

[33] Philippe Marcus, editor. *Corrosion Mechanisms in Theory and Practice*. CRC Press, Taylor & Francis Group, Boca Raton, FL, 3rd edition, 2011. ISBN 978-1-4200-9462-6.

[34] Mariana Paz Martínez-Viademonte, Shoshan T. Abrahami, Theodor Hack, Malte Burchardt, and Herman Terryn. A Review on Anodizing of Aerospace Aluminum Alloys for Corrosion Protection. *Coatings*, 10(11):1106, 2020. doi: 10.3390/coatings10111106.

[35] Io Matsui, Hikari Ouchi, Yuki Atsuumi, Kota Fukuhara, and Takahiro Ishizaki. Steam Coating-Based Synthesis and Corrosion Inhibition Performance of Mg-Al-Layered Double Hydroxide Films with Different Interlayer Anions on Al-Si-Cu Alloys. *Materials*, 18(23):5405, 2025. doi: 10.3390/ma18235405.

[36] Edward McCafferty. *Introduction to Corrosion Science*. Springer New York, New York, NY, 2010. ISBN 978-1-4419-0454-6. doi: 10.1007/978-1-4419-0455-3.

[37] Metrohm Autolab. Electrochemical Impedance Spectroscopy Part 3 - Data Analysis. EC Application Note AN-EIS-003, Metrohm AG, 2021. URL `https://www.metrohm.com/en/applications/AN-EIS-003`.

[38] Matthew D. Murbach, Brian Gerwe, Neal Dawson-Elli, and Lok kun Tsui. impedance.py: A Python package for electrochemical impedance analysis. *Journal of Open Source Software*, 5(52):2349, 2020. doi: 10.21105/joss.02349.

[39] K. J. H. Nelson, A. E. Hughes, R. J. Taylor, B. R. W. Hinton, L. Wilson, and M. Henderson. Characterisation of aluminium alloys after $HNO_3/HF - NaOH - HNO_3/HF$ pretreatment. *Materials Science and Technology*, 17(10):1211, 2001. doi: 10.1179/026708301101509125.

[40] Mark E. Orazem and Bernard Tribollet. *Electrochemical Impedance Spectroscopy*. John Wiley & Sons, Hoboken, New Jersey, 2008. ISBN 9780470041406. doi: 10.1002/9780470381588.

[41] Shi-Qi Pan, Fen Zhang, Cuie Wen, and Rong-Chang Zeng. Advances in Mg-Al-layered double hydroxide steam coatings on Mg alloys: A review. *Journal of Magnesium and Alloys*, 2023. doi: 10.1016/j.jma.2023.05.002. Available online 10 June 2023.

[42] J.-T. Qi, T. Hashimoto, J. R. Walton, X. Zhou, P. Skeldon, and G. E. Thompson. Trivalent chromium conversion coating formation on aluminium. *Surface and Coatings Technology*, 280:203–214, 2015. doi: 10.1016/j.surfcoat.2015.09.024.

[43] R. Winston Revie and Herbert H. Uhlig. *Corrosion and Corrosion Control: An Introduction to Corrosion Science and Engineering*. John Wiley & Sons, Inc., Hoboken, New Jersey, 4th edition, 2008. ISBN 978-0-471-73279-2.

[44] Pierre R. Roberge. *Handbook of Corrosion Engineering*. McGraw-Hill, New York, 2000. ISBN 0-07-076516-2.

[45] V. S. Sastri, Edward Ghali, and Mimoun Elboujdaini. *Corrosion Prevention and Protection: Practical Solutions*. John Wiley & Sons, Ltd, Chichester, West Sussex, England, 2007. ISBN 978-0-470-02402-7.

[46] Joachim Schaeffer, Paul Gasper, Esteban Garcia-Tamayo, Raymond Gasper, Masaki Adachi, Juan Pablo Gaviria-Cardona, Simon Montoya-Bedoya, Anoushka Bhutani, Andrew Schiek, Rhys Goodall, Rolf Findeisen, Richard D. Braatz, and Simon Engelke. Machine Learning Benchmarks for the Classification of Equivalent Circuit Models from Electrochemical Impedance Spectra. *arXiv preprint arXiv:2302.03362*, 2023. doi: 10.48550/arXiv.2302.03362.

[47] Rainer Storn and Kenneth Price. Differential Evolution - A Simple and Efficient Heuristic for Global Optimization over Continuous Spaces. *Journal of Global Optimization*, 11(4):341–359, 1997. doi: 10.1023/A:1008202821328.

[48] J. Tedim, S. K. Poznyak, A. Kuznetsova, D. Raps, T. Hack, M. L. Zheludkevich, and M. G. S. Ferreira. Enhancement of active corrosion protection via combination of inhibitor-loaded nanocontainers. *ACS Applied Materials & Interfaces*, 2(5):1528–1535, 2010. doi: 10.1021/am100174t.

[49] J. Tedim, M. L. Zheludkevich, A. N. Salak, A. Lisenkov, and M. G. S. Ferreira. Nanostructured LDH-container layer with active protection functionality. *Journal of Materials Chemistry*, 21:15464–15470, 2011. doi: 10.1039/c1jm12463c.

[50] J. Tedim, M. L. Zheludkevich, A. C. Bastos, A. N. Salak, A. D. Lisenkov, and M. G. S. Ferreira. Influence of preparation conditions of Layered Double Hydroxide conversion films on corrosion protection. *Electrochimica Acta*, 117:164–171, 2014. doi: 10.1016/j.electacta.2013.11.102.

[51] Christian Vargel. *Corrosion of Aluminium*. Elsevier, Amsterdam, 2nd edition, 2020. ISBN 978-0-08-099925-8.

[52] K. A. Yasakau, J. Tedim, M. L. Zheludkevich, and M. G. S. Ferreira. Active Corrosion Protection by Nanoparticles and Conversion Films of Layered Double Hydroxides. *Corrosion*, 70(5):436–445, 2014. doi: 10.5006/0979.

[53] B. Zhang, J. Wang, B. Wu, X. W. Guo, Y. J. Wang, D. Chen, Y. C. Zhang, K. Du, E. E. Oguzie, and X. L. Ma. Unmasking chloride attack on the passive film of metals. *Nature Communications*, 9:2559, 2018. doi: 10.1038/s41467-018-04942-x.

[54] Runze Zhang, Robert Black, Debashish Sur, Parisa Karimi, Kangming Li, Brian DeCost, John Scully, and Jason Hattrick-Simpers. AutoEIS: automated Bayesian model selection and analysis for electrochemical impedance spectroscopy. *arXiv preprint arXiv:2305.04841*, 2023. doi: 10.48550/arXiv.2305.04841.

[55] You Zhang, Jianhua Liu, Yingdong Li, Mei Yu, SongMei Li, and Bing Xue. Fabrication of inhibitor anion-intercalated layered double hydroxide host films on aluminum alloy 2024 and their anticorrosion properties. *Journal of Coatings Technology and Research*, 12(2):293–302, 2015. doi: 10.1007/s11998-014-9644-1.

[56] Meng Zhou, Luchun Yan, Hao Ling, Yupeng Diao, Xiaolu Pang, Yanlin Wang, and Kewei Gao. Design and fabrication of enhanced corrosion resistance Zn-Al layered double hydroxides films based anion-exchange mechanism on magnesium alloys. *Applied Surface Science*, 404:246–253, 2017. doi: 10.1016/j.apsusc.2017.01.157.

[57] Bin Zou, Songpei Hu, Yang Wu, Bo Sun, Hang Tian, Kai Liu, Jiafeng Yao, and Minhong Pan. Bioimpedance spectroscopy for lung cancer diagnosis based on Hippopotamus algorithm with Enhanced exploitation capability (EEC-HA). *Measurement*, 221:113519, 2023. doi: 10.1016/j.measurement.2023.113519.

[58] D. Álvarez, A. Collazo, M. Hernández, X. R. Nóvoa, and C. Pérez. Characterization of hybrid sol-gel coatings doped with hydrotalcite-like compounds to improve corrosion resistance of AA2024-T3 alloys. *Progress in Organic Coatings*, 68(1-2):91–99, 2010. doi: 10.1016/j.porgcoat.2009.10.019.