

Corrosion protection of complex shapes aluminium alloys via conversion coatings

Alexandre de Brito Salvador Cauvel

alexandre.cauvel@ua.pt

Advisors: Kiryl Yasakau, João Tedim

Abstract

This work investigates the development of a ZnAl-LDH conversion coating system loaded with corrosion inhibitors on the AC46000 die-cast aluminium alloy as a chromate-free alternative for aerospace applications. Electrochemical pre-selection identified MBT, NaVO_3 , and L-cysteine as the most effective inhibitors. While NaVO_3 was successfully intercalated into the LDH galleries, demonstrating active chloride-triggered release, the thiol-containing inhibitors caused the destruction of the LDH crystalline structure due to aggressive zinc chelation. Notably, MBT remained on the surface in an adsorbed state, contributing to the initial barrier properties. Corrosion evaluation highlighted the critical influence of the substrate microstructure: an aggressive industrial pre-treatment proved detrimental by exposing subsurface intermetallics during LDH synthesis. A milder chemical pre-treatment yielded significant improvements, with MBT providing excellent initial barrier protection and NaVO_3 providing sustained active protection. Potentiodynamic polarisation confirmed both act primarily as anodic inhibitors, though neither effectively suppressed cathodic activity at Fe-Mn intermetallic sites. Finally, the successful application of a polyurethane topcoat via anodic electrodeposition on complex geometries validated the practical feasibility of the complete multilayer system.

1 Introduction

Modern aerospace structures rely heavily on high-performance aluminium alloys, particularly the 2xxx and 7xxx series, due to their exceptional strength-to-weight ratio. However, in harsh aerospace environments, these materials are highly susceptible to localised corrosion, accelerated by dispersed intermetallic particles (IMPs) that form micro-galvanic sites [1, 2]. Traditionally, this challenge has been managed using multilayer coatings based on hexavalent chromium (Cr(VI)), which offer exceptional self-healing capabilities. However, the carcinogenic nature of Cr(VI) has led to strict regulatory restrictions, creating an urgent need for high-performance, environmentally benign alternatives [3, 4].

Layered Double Hydroxides (LDH) have emerged as a highly promising chromate-free alternative. Their unique layered structure allows for the storage and stimuli-responsive release of corrosion inhibitors via anion exchange, providing a combination of barrier protection and active self-healing [5, 6, 7]. While recent LDH research has demonstrated excellent potential on wrought alloys (e.g., AA2024) tested on simple flat specimens [8, 9, 10], there is a distinct lack of data regarding their performance on cast alloys like AC46000. Cast alloys enable the manufacturing of complex, highly detailed geometries increasingly common in modern aerospace assemblies. However, they introduce significant challenges, including heterogeneous mi-

crostructures, higher silicon content, and complex surface topographies, all of which critically influence LDH growth and coating integrity.

The primary objective of this work is to synthesise and optimise a ZnAl-LDH conversion pre-treatment capable of forming a uniform coating on both flat and complex-geometry AC46000 substrates. This involves the intercalation of selected corrosion inhibitors, rigorous electrochemical evaluation, and the ultimate validation of the complete multilayer protective system, including an organic polyurethane topcoat, on industrially representative complex geometries.

2 Methodology

The experimental methodology was structured to systematically address the challenges posed by the AC46000 die-cast alloy microstructure.

2.1 Inhibitor Pre-selection

Seven candidate inhibitors (NaVO_3 , Na_2MoO_4 , MBT, BTA, 8-HQ, L-cysteine, and a blank NaCl control) were evaluated via Electrochemical Impedance Spectroscopy (EIS) over 168 h of immersion in 0.05 M NaCl. The charge-transfer resistance (R_{ct}) and double-layer capacitance (C_{dl}) were extracted using a custom automated fitting framework based on the Differential Evolution algorithm.

2.2 Surface Pre-treatments and LDH Synthesis

To mitigate the heterogeneous distribution of IMPs, three surface preparation routes were evaluated: mechanical polishing (reference), a simplified chemical pre-treatment, and an aggressive industrial pre-treatment. Following pre-treatment, ZnAl-LDH films were synthesised *in situ* via a hot aqueous solution method at 95 °C for either 1 h (LDH-1) or 3 h (LDH-2). The films were characterised using X-ray Diffraction (XRD) and Scanning Electron Microscopy with Energy-Dispersive X-ray Spectroscopy (SEM-EDS).

2.3 Inhibitor Intercalation

The top-performing inhibitors from the pre-selection phase were incorporated into the LDH galleries via anion exchange. NaVO_3 was intercalated from a 0.1 M solution. For the MBT, the solution pH was carefully adjusted with NaOH to deprotonate the thiol groups, imparting the net negative charge required for electrostatic uptake [11].

2.4 Corrosion Performance and Topcoat Application

The active corrosion protection of the intercalated LDH coatings was evaluated via long-term EIS and Potentiodynamic Polarisation (PDP) in 0.05 M NaCl [12]. Finally, a water-based polyurethane colloidal formulation was applied over the optimised LDH pre-treatments via anodic electrodeposition (80 V for 1 min, followed by curing at 120 °C) on both planar and complex-geometry specimens to form a complete multilayer system.

The resulting multilayer architecture was characterised using cross-sectional SEM-EDS to evaluate local coating thickness, interfacial adhesion, and elemental distribution, complemented by macroscopic dry film thickness measurements using an Elcometer gauge.

3 Results and Discussion

3.1 Inhibitor Pre-selection

The EIS pre-selection identified MBT, NaVO_3 , and L-cysteine as the most effective inhibitors, demonstrating R_{ct} values in excess of $100 \text{ k}\Omega \text{ cm}^2$ and stable C_{dl} values on the order of $10 \mu\text{F cm}^{-2}$, indicative of active and durable surface film formation. Conversely, the poorly protected systems exhibited exceptionally high C_{dl} values. As these represent an effective capacitance derived from a 2RC model over a restricted frequency window, they reflect both extensive water uptake and the lumped contributions of unresolved low-frequency mass transport processes. Sodium molybdate provided negligible protection, while BTA and 8-HQ exhibited intermediate and transient protection, failing to maintain stable surface films over extended immersion.




Figure 1: Evolution of R_{ct} and C_{dl} over the 168 h immersion period for the pre-selected inhibitors.

3.2 Pre-treatments and LDH Synthesis

SEM-EDS characterisation revealed that the industrial pre-treatment achieved near-complete removal of Fe-Mn and Cu-rich IMPs, leaving primarily electrochemically inert Si particles exposed. The chemical pre-treatment achieved only partial removal of Fe-Mn particles. XRD analysis confirmed successful ZnAl-LDH formation on all substrate conditions, with comparable film density and basal spacing consistent with NO_3^- intercalation. EDS analysis further confirmed uniform Zn deposition across both the aluminium matrix and the Si phase, demonstrating that the LDH grows conformally over the heterogeneous microstructure.

3.3 Inhibitor Intercalation

XRD analysis of the intercalated systems confirmed the successful incorporation of NaVO_3 , evidenced by a systematic shift in the (003) basal reflection from $2\theta = 9.86^\circ$ to 9.51° , corresponding to an expansion of the interlayer gallery height from 4.20 Å to 4.53 Å. Following immersion in NaCl, a further shift to $2\theta = 10.35^\circ$ confirmed the exchange of vanadate for chloride anions, definitively demonstrating active inhibitor release [7].

In stark contrast, the attempted intercalation of MBT resulted in the destruction of the LDH crystalline structure. This structural degradation is fundamentally attributed to the deprotonated, negatively charged thiolate anions ($-\text{S}^-$) present in the alkaline intercalation solutions. These thiolate

groups exhibit an exceptionally strong coordination affinity for Zn^{2+} ions, acting as powerful chelating agents that actively extract zinc from the host brucite layers, forming soluble zinc-thiolate complexes and collapsing the LDH crystal lattice [11]. Consequently, this system lacks a structured crystalline reservoir for controlled release. Instead, the

protective mechanism relies on the passive barrier properties of the amorphous remnants, comprising zinc and aluminium hydroxides, combined with the direct chemisorption of MBT molecules onto both the exposed alloy surface and these residual hydroxide sites.




Figure 2: XRD patterns of LDH films in the nitrate form (control), following NaVO_3 intercalation, and following the MBT intercalation attempt, each presented before and after immersion in 0.05 M NaCl.

3.4 Corrosion Performance Analysis

The corrosion performance was evaluated in two iterative batches. The first batch (LDH-1), based on the industrial pre-treatment with a 1 h LDH growth time, yielded unsatisfactory protection. The uncoated control specimen outperformed all vanadate-intercalated LDH specimens. This counterintuitive result is attributed to the synergistic effect of the aggressive industrial etching and subsequent matrix dissolution: the etching digs deep trenches into the aluminium matrix, and even minor matrix dissolution during LDH synthesis fully exposes subsurface intermetallic particles that were previously undermined. These newly exposed, highly cathodic sites initiate severe localised pitting that the inhibitor loading is insufficient to suppress.

Driven by these limitations, the second batch (LDH-2) employed the milder chemical pre-treatment with an extended 3 h LDH growth time. MBT-intercalated specimens exhibited the best corrosion protection, with a low-frequency impedance modulus approximately one order of magnitude higher than the control at 1 h and substantially elevated R_{ct} values at early immersion times. However, after 24 h, their R_{ct} values decreased sharply, confirming that the unstructured remnant film causes rapid inhibitor exhaustion via uncontrolled desorption and reprecipitation. NaVO_3 -intercalated specimens showed intermediate performance, with localised vanadate ox-

ide deposits confirming active inhibitor release and repassivation attempts.




Figure 3: Evolution of R_{ct} and C_{dl} over the 168 h immersion period for the LDH-2 specimens.

PDP analysis revealed that neither inhibitor sup-

pressed cathodic activity at Fe–Mn sites, with cathodic branches virtually superimposed. However, both significantly reduced anodic dissolution, shifting E_{corr} nobly and acting primarily as anodic inhibitors. The long-term performance remains below target due to persistent Fe–Mn particles on the chemically pre-treated surface. Unlike Cu-rich IMPs in wrought alloys like AA2024, the Fe–Mn IMPs characteristic of AC46000 are not effectively passivated by NaVO_3 or MBT.

3.5 Polyurethane Topcoat Application

Finally, a polyurethane topcoat was applied to planar and complex-geometry (CG) specimens via anodic electrodeposition. The complex-shaped specimens were manufactured via investment casting, and the author gratefully acknowledges Prof. Georgina Miranda and Pedro Araújo for their assistance in producing these components. A photograph of the complex geometry is presented in Figure 4.




Figure 4: Optical macrographs of polyurethane-coated complex-shaped specimens.

Cross-sectional SEM-EDS confirmed robust interfacial adhesion and resolved the multilayer architecture, identifying the LDH layer (Zn, O) and specific intercalated species (S for MBT, V for NaVO_3). Local thickness measurements from these cross-sections revealed a thinner coating for MBT ($16.5\text{ }\mu\text{m}$) compared to NaVO_3 ($26.5\text{ }\mu\text{m}$), attributed to the amorphous remnant film versus the intact crystalline LDH. Complementing this localised analysis, macroscopic dry film thickness evaluations performed using an Elcometer gauge revealed average topcoat thicknesses of $31.7(57)\text{ }\mu\text{m}$ for the NaVO_3 -intercalated specimens and $28.8(55)\text{ }\mu\text{m}$ for the MBT-intercalated specimens. Both systems exhibited substantial standard deviations (approximately 18–19% relative variation), demonstrating the heterogeneous nature of the coating thickness across the macroscopic surface. Crucially, cross-sections visually confirmed the persistence of large Fe–Mn intermetallic particles at the alloy surface, highlighting the challenge of protecting these active micro-galvanic sites. Despite these thickness variations, conformal coverage was achieved on the complex geometries, validating the system’s practical feasibility.

4 Conclusions

This work investigated ZnAl–LDH conversion coatings on the AC46000 die-cast alloy as a chromate-free aerospace alternative. While NaVO_3 was successfully intercalated and demonstrated active chloride-triggered release, MBT destroyed the LDH crystalline structure via aggressive zinc chelation, yet remained adsorbed on the surface, actively inhibiting corrosion. Corrosion evaluation revealed that aggressive industrial pre-treatments detrimentally exposed subsurface IMPs, whereas a milder chemical pre-treatment yielded significant improvements: MBT provided excellent initial barrier protection and NaVO_3 offered sustained active protection. However, long-term performance remains limited by the inability of these inhibitors to passivate the highly prevalent Fe–Mn intermetallic particles. Ultimately, the successful conformal deposition of a polyurethane topcoat via anodic electrodeposition validated the practical feasibility of protecting complex aerospace geometries.

References

- [1] M. P. Martínez-Viademonte, S. T. Abrahami, T. Hack, M. Burchardt, and H. Terryn, “A Review on Anodizing of Aerospace Aluminum Alloys for Corrosion Protection,” *Coatings*, vol. 10, no. 11, p. 1106, 2020.
- [2] V. Garg, M. Magnan, S. Zanna, A. Seyeux, F. Wiame, V. Maurice, and P. Marcus, “Corrosion inhibition mechanisms of 2-mercaptobenzothiazole on aa2024 t3 aluminium alloy,” *npj Materials Degradation*, 2025.
- [3] M. Becker, “Chromate-free chemical conversion coatings for aluminum alloys,” *Corrosion Reviews*, vol. 37, no. 4, pp. 321–342, 2019.
- [4] A. C. Bouali, M. Serdechnova, C. Blawert, J. Tedim, M. G. S. Ferreira, and M. L. Zheludkevich, “Layered double hydroxides (LDHs) as functional materials for the corrosion protection of aluminum alloys: A review,” *Applied Materials Today*, vol. 21, p. 100857, 2020.
- [5] Y. Cao, D. Zheng, F. Zhang, J. Pan, and C. Lin, “Layered double hydroxide (LDH) for multi-functionalized corrosion protection of metals: A review,” *Journal of Materials Science & Technology*, vol. 102, pp. 232–263, 2022.
- [6] K. A. Yasakau, A. Kuznetsova, S. Kallip, M. Starykevich, J. Tedim, M. G. S. Ferreira, and M. L. Zheludkevich, “A novel bilayer system comprising LDH conversion layer and sol-gel coating for active corrosion protection of AA2024,” *Corrosion Science*, vol. 143, pp. 299–313, 2018.
- [7] M. Zhou, L. Yan, H. Ling, Y. Diao, X. Pang, Y. Wang, and K. Gao, “Design and fabrication of enhanced corrosion resistance Zn–Al layered double hydroxides films based anion-exchange mechanism on magnesium alloys,” *Applied Surface Science*, vol. 404, pp. 246–253, 2017.
- [8] J. Tedim, M. L. Zheludkevich, A. C. Bastos, A. N. Salak, A. D. Lisenkov, and M. G. S. Ferreira, “Influence of preparation conditions of Layered Double Hydroxide conversion films on corrosion protection,” *Electrochimica Acta*, vol. 117, pp. 164–171, 2014.
- [9] J. Tedim, M. L. Zheludkevich, A. N. Salak, A. Lisenkov, and M. G. S. Ferreira, “Nanostructured LDH-container layer with active protection functionality,” *Journal of Materials Chemistry*, vol. 21, pp. 15464–15470, 2011.
- [10] Q.-Q. He, M.-J. Zhou, and J.-M. Hu, “Electrodeposited Zn–Al layered double hydroxide films for corrosion protection of aluminum alloys,” *Electrochimica Acta*, vol. 355, p. 136796, 2020.
- [11] J. Tedim, S. K. Poznyak, A. Kuznetsova, D. Raps, T. Hack, M. L. Zheludkevich, and M. G. S. Ferreira, “Enhancement

of active corrosion protection via combination of inhibitor-loaded nanocontainers,” *ACS Applied Materials & Interfaces*, vol. 2, no. 5, pp. 1528–1535, 2010.

[12] M. E. Orazem and B. Tribollet, *Electrochemical Impedance Spectroscopy*. Hoboken, New Jersey: John Wiley & Sons, 2008.