

Table C.2 — Austenitic-ferritic grade

Steel designation		Typically available tensile strength levels for diameters in mm								
Name	Number	+C500	+C600	+C700	+C800	+C900	+C1000	+C1100	+C1200	+C1400
X2CrNiMoN22-5-3	1.4462	-	-	-	< 20	< 20	< 15	< 15	< 15	< 6

Table C.3 — Ferritic grades

Steel designation		Typically available tensile strength levels for diameters in mm				
Name	Number	+C500	+C600	+C700	+C800	+C900
X6Cr17	1.4016	all diam.	< 20	< 20	< 15	< 10
X3CrNb17	1.4511	1 to 25	< 20	< 20	< 15	< 10
X6CrMoS17	1.4105	all diam.	< 20	< 20	< 15	< 10
X6CrMo17-1	1.4113	< 25	< 20	< 20	< 15	< 10