

Annex A (informative)

List of all stainless steel grades that appear in the document

Table A.1 — List of stainless steel grades that appear in the present standard (by ascending Number)

Number	Name	Grade Group ^a	Table ^b	Number	Name	Grade Group ^a	Table ^b	Number	Name	Grade Group ^a	Table ^b
1.4000	X6Cr13	fP std	4,10	1.4110	X55CrMo14	mM std	5,11	1.4362	X2CrNi23-4	dP std	3,9,14,18,19
1.4003	X2CrNi12	fP std	4,10	1.4112	X90CrMoV18	mM sp	5,11	1.4369	X11CrNiMnN19-8-6	aP sp	2,8
1.4005	X12CrS13	mP std	5,11,16,18	1.4113	X6CrMo17-1	fM std	4,10,15,18,19	1.4372	X12CrMnNiN17-7-5	aP sp	2,8
1.4006	X12Cr13	mP std	5,11,16,18	1.4114	X6CrMoSi19-2	fM sp	4,10,15	1.4374	X8CrMnNiN18-9-5	aP sp	2,8,18,19
1.4016	X6Cr17	fP std	4,10,15,18,19	1.4116	X50CrMoV15	mM std	5,11	1.4378	X6CrMnNiN18-13-3	aP sp	2,8,13,18,19
1.4020	X13MnNiN18-13-2	aP sp	2,8,13,18,19	1.4122	X39CrMo17-1	mM std	5,11,16	1.4391	X3CrMnNiN20-9-6	aP sp	2,8,13
1.4021	X20Cr13	mP std	5,11,16,18	1.4123	X40CrMoVN16-2	mM sp	5,11	1.4401	X5CrNiMo17-12-2	aM std	2,8,13,18,19
1.4024	X15Cr13	mP std	5,11	1.4125	X105CrMo17	mM sp	5,11	1.4404	X2CrNiMo17-12-2	aM std	2,8,13,18,19
1.4028	X30Cr13	mP std	5,11,16,18	1.4150	X53CrSiMoVN16-2	mM sp	5,11	1.4406	X2CrNiMoN17-11-2	aM std	2,8
1.4029	X29CrS13	mP sp	5,11,16	1.4162	X2CrMnNiN21-5-1	dP std	3,9,14	1.4410	X2CrNiMoN25-7-4	dM sp	3,9,18,19
1.4031	X39Cr13	mP std	5,11,16	1.4301	X5CrNi18-10	aP std	2,8,13,18,19	1.4415	X2CrNiMoV13-5-2	mM sp	5,11
1.4034	X46Cr13	mP std	5,16,18	1.4303	X4CrNi18-12	aP std	2,8,18,19	1.4418	X4CrNiMo16-5-1	mM std	5,11,16