

Pb2Bi2Te5
HSE+SOC, indirect gap 0.114 eV
E − EVBM (eV)
3
2
1
0
−1
−2
−3
Γ
M
K
Γ
A
L
H
A|L
H
M|K
marker area ∝ share of each element-orbital (Kramers pairs drawn once)
Pb-s
Pb-p
Bi-s
Bi-p
Te (s+p)