

STRENGTH ACTIVITY INDEX (SAI) TEST RESULTS						
Cube Size: 50mm × 50mm Unit: kN Test: Compressive Load						
Mix / Binder	Specimen No.	Load (kN)	Compressive Strength (N/mm²)	Avg Load (kN)	Avg Strength (N/mm²)	SAI (%)
OPC (Control)	1	57.77	23.11	61.29	24.52	Reference
	2	55.91	22.36			
	3	70.20	28.08			
Mix 1	1	72.85	29.14	80.30	32.12	131.01%
	2	82.79	33.12			
	3	85.25	34.10			
Mix 2	1	75.48	30.19	66.13	26.45	107.90%
	2	65.12	26.05			
	3	57.79	23.12			
Mix 3	1	63.30	25.32	60.45	24.18	98.63%
	2	58.05	23.22			
	3	60.00	24.00			
Mix 4	1	68.00	27.20	66.69	26.68	108.81%
	2	65.59	26.24			
	3	66.48	26.59			
Mix 5	1	67.50	27.00	69.27	27.71	113.01%
	2	69.06	27.62			
	3	71.26	28.50			

