



ME TESTING AND CALIBRATION LABORATORY PVT. LTD.

Doc. No.: METCLPL/FF/48

Head Office: 103, 1st Floor, Plot No. C-1/2 Naniwala Bagh,
Commercial Complex, Azadpur, Delhi, India - 110033
Mobile: +91 7535000491, +91 9034341490 | Email: metclplddn@gmail.com

Lab.: Harbanswala, Telpur Chowk, Shimla Bypass Road,
Dehradun, Uttarakhand, India - 248171
Mobile: +91 7535000491, +91 7535000492 | Email: metclddn@gmail.com

TEST REPORT

Issued To: M/s Tons Builders, Near Telephone Exchange, Purola, Uttarkashi (U.K.).				Report No.: METCLPL/DDN/21042025/31 Sample Id: 210425/31 Date of Receipt: 21/04/2025 Date of performance of Testing: 12/05/2025 Date of Issue of Report: 12/05/2025			
Sample Description: CC Cube Sample Quantity: 3 Nos. Sample Condition: Receipt as OK Sample Plan & Sampling Method: N/A. Environment Condition (Temp. & Humidity): 25.0 ⁰ ±5 ⁰ C & NA Addition to, Deviation or Exclusion from the Method: NA				Grade: M-30 Date of Casting: 14/04/2025 Casting: Abutment A2 Raft Test Performed at: Lab			
N.O.W.: Construction of 84 M span Steel Girder Motor Bridge over Kotigaad in KM 01 of Tikochi – Duchanu – Kiranu – Sirtoli Motor Road in Dist. Uttarkashi under EPC Mode. Contract Agreement No.: 13/U-PREPARE/24/BR/RFB-EPC/UGRIDP/2023 Dated 18-09-2024							
COMPRESSIVE STRENGTH After 28 Days							
S. No.	Wt. of Specimen Kg.	Dimension of Specimen, mm. (L×B)	Cross Sectional Area, mm ²	Maximum Applied Load (N)	Comp. Stg. N/mm ²	Average Comp. Stg. N/mm ²	Method of Test Ref to:
1	8.140	150×150	22500	784400	34.86	35.50	IS 516:P-I: Sec-1: 2021
2	8.390	150×150	22500	804800	35.77		
3	8.210	150×150	22500	810900	36.04		

Note: 1. The Above Test refers only to the Items tested.

2. Statement of Conformity & Decision Rule (In case of Borderline): NA

3. Opinion & Interpretations: NA

*****End of Report*****

Reviewed By



Mr. Rahul Rohilla (Q.M./T.M)

Authorized Signatory

1. The result listed refer only to the tested samples and applicable parameters endorsement of product is neither inferred nor implied.
2. Total liability of our Lab. is limited to the invoiced amount.
3. Samples will be destroyed after 30 Days from the date of issue of test report.
4. This report is not be reproduced wholly or in part and cannot be used as an evidence in the court of law and should not be used in any advertising media without our special permission in writing.

NABL ACCREDITED & ISO 9001:2015 CERTIFIED LAB.