



# DEVBHOOMI TESTING LABORATORY DEHRADUN

NABL Accredited, Govt. Approved, MSME Registered, & ISO : 9001:2015 & 14001: 2015 Certified Laboratory

Neelkanth Enclave, Harbhajwala, Telpur Chowk, Shimla By Pass Road, Dehradun 248171

Mob: +91-7217360360, +91-7579118238, 8859392493, 9760764229

Email: devbhoomilab@gmail.com

## TEST REPORT

Description of Sample: Surface Water	Report No.: DTL/DDN/2024/3110/02
Sample Id: 31102024/02	Date of Report: 08/11/2024
Sample Quantity: As per requirement	Date of Sampling: 31/10/2024
Sample Condition: Receipt as OK	Start Date of Testing: 04/11/2024
Sample Plan & Sampling Method: NA	Date of Completion: 08/11/2024
Environment Condition (Temp. & Humidity): NA	Page 1 of 1
Addition to, Deviation or Exclusion from the Method: NA	
N.O.W : "Construction of 48M Span Intermediate Lane Motor Bridge in& its approach over Meeng Gadera Km-1 of Gadhani Motor Road in District Chamoli."	
Issued to: Mr.Umashankar Singh Rawat, Tharali Chamoli, Uttarakhand	

### Sample: 01

S. No.	Characteristics	Test Value	Max. Permissible Limit as per IS: 456-2000 (Clause 5.4)	Method of test ref to:
1.	Requirement of 0.02 N-Noah to neutralize 100ml. of water sample using Phenolphthalein indicator	0.5	5.0 ml.	IS-3025 (P-22) 1986RA:2019
2.	Requirement of 0.02 N-H <sub>2</sub> SO <sub>4</sub> to neutralize 100ml of water sample using mixed indicator	6.0	25.0 ml.	IS-3025 (P-23) 1986RA:2019
3.	Organics, mg/l.	79	200	IS: 3025 (P-18) 2022
4.	Inorganic, mg/l.	108	3000	IS: 3025 (P-18) 2022
5.	Sulphate as SO <sub>3</sub> , mg/l.	25	400	IS: 3025(P-24)1986 RA:2019
6.	Chloride as Cl, mg/l	29	500 mg /l for RCC & 200mg/l for concrete without embedded steel.	IS: 3025 (P-32) 1988RA:2019
7.	pH	7.68	Not less than 6.0	IS: 3025 (P-11) 2022
8.	Suspended matter, mg/l	1.52	2000	IS: 3025 (P-17) 2022

\*\*\*\*\*End of Report\*\*\*



Devbhoomi Testing Laboratory  
Technical Manager

Checked & Issued by  
Authorised Signatory

- The result Listed refer only to the tested sample & applicable parameters endorsement of products is neither inferred nor implied.
- Total liability of our lab is limited to the invoiced amount.
- Sample not drawn by lab and sample will be destroyed after 30 days from the date of issue of test report.
- This report is not be reproduced wholly or in part and cannot be used as an evidence in the court of law and should not be used in any advertising media without our special permission in writing.



# DEVBHOOMI TESTING LABORATORY DEHRADUN

NABL Accredited, Govt. Approved, MSME Registered, & ISO : 9001:2015 & 14001: 2015 Certified Laboratory

Neelkanth Enclave, Harbhajwala, Telpur Chowk, Shimla By Pass Road, Dehradun 248171

Mob: +91-7217360360, +91-7579118238, 8859392493, 9760764229

Email: devbhoomilab@gmail.com

## TEST REPORT

Description of Sample: Surface Water	Report No.: DTL/DDN/2024/3110/03
Sample Id: 31102024/03	Date of Report: 08/11/2024
Sample Quantity: As per requirement	Date of Sampling: 31/10/2024
Sample Condition: Receipt as OK	Start Date of Testing: 04/11/2024
Sample Plan & Sampling Method: NA	Date of Completion: 08/11/2024
Environment Condition (Temp. & Humidity): NA	Page 1 of 1
Addition to, Deviation or Exclusion from the Method: NA	
N.O.W : "Construction of 48M Span Intermediate Lane Motor Bridge in& its approach over Meeng Gadera Km-1 of Gadhani Motor Road in District Chamoli."	
Issued to: Mr.Umashankar Singh Rawat, Tharali Chamoli, Uttarakhand	

### Sample: 02

S. No.	Characteristics	Test Value	Max. Permissible Limit as per IS: 456-2000 (Clause 5.4)	Method of test ref to:
1.	Requirement of 0.02 N-Noah to neutralize 100ml. of water sample using Phenolphthalein indicator	0.2	5.0 ml.	IS-3025 (P-22) 1986RA:2019
2.	Requirement of 0.02 N-H <sub>2</sub> SO <sub>4</sub> to neutralize 100ml of water sample using mixed indicator	5.8	25.0 ml.	IS-3025 (P-23) 1986RA:2019
3.	Organics, mg/l.	78	200	IS: 3025 (P-18) 2022
4.	Inorganic, mg/l.	104	3000	IS: 3025 (P-18) 2022
5.	Sulphate as SO <sub>3</sub> , mg/l.	24	400	IS: 3025(P-24)1986 RA:2019
6.	Chloride as Cl, mg/l	27	500 mg /l for RCC & 200mg/l for concrete without embedded steel.	IS: 3025 (P-32) 1988RA:2019
7.	pH	7.73	Not less than 6.0	IS: 3025 (P-11) 2022
8.	Suspended matter, mg/l	1.55	2000	IS: 3025 (P-17) 2022

\*\*\*\*\*End of Report\*\*\*\*\*



Checked & Issued by  
Authorised Signatory

- The result Listed refer only to the tested sample & applicable parameters endorsement of products is neither inferred nor implied.
- Total liability of our lab is limited to the invoiced amount.
- Sample not drawn by lab and sample will be destroyed after 30 days from the date of issue of test report.
- This report is not be reproduced wholly or in part and cannot be used as an evidence in the court of law and should not be used in any advertising media without our special permission in writing.