



CIVIL TECH LABORATORY

Kh. No. 48, Vill.- Belda, Near RTO Office, Roorkee, Distt.- Haridwar, U.K.- 247667

+91-9911860667, 8076576367 civiltechlabuk@gmail.com

www.civiltechlaboratory.com



TEST REPORT

Format No.: CTL/F/7.8/01

This report is not valid without a Hologram

Letter Ref.No.: 5170/1C, Dated: 03/11/2025

Sample Description: HYSD/TMT Bar (32 mm) (Reinforcement Steel)

Make: SEL Tiger

Issued To,

The Executive Engineer

Provincial Division, PWD

Haridwar, Uttarakhand

Location of Performance of Test: In Lab

Date of Performance of Test: 04/11/2025 to 10/11/2025

Addition to Deviation or Exclusion from the Method: NA

Name of Work: Construction of 240 M Span Double lane RCC Motor Bridge over Suswa River in Bullawala to Sattiwala Motor Road in District Dehradun.

Agreement No.: 12/U-PREPARE/23/BR/RFB-EPC/UGRIDP/2023, Dated: 18/09/2024

Name of Agency: M/s R. C. C. Developers, 109 City Centre, Children Park, Meerut, Uttar Pradesh

ULR No: TC1583225000000651F

Report Number: CTL/MECH/251104022A

Date of Report: 11/11/2025

Job Order No.: 251104022

Sample Received On: 04/11/2025

Sample Quantity: 01 Mtr X 03 Pcs.

Sample Condition: Satisfactory

Sample Drawn By: Customer

Environment Condition (Temp. & RH) : 25±5°C & NA



TC-15832

I-Mechanical Testing

Page No: 01 of 01

1-Mechanical Properties of Metals

S. No.	Test Parameter	Test-Method	Result	Requirement As per IS: 1786-2008 (Fe-550D)
1.	Yield stress, N/mm ²	IS:1608(Part-1): 2022	584	550 Min.
2.	Tensile Strength, N/mm ²	IS:1608(Part-1): 2022	689	600 Min.
3.	Tensile Strength/Yield Stress ratio	IS:1786: 2008	1.180	≥ 1.08
4.	% Elongation on Gauge Length 5.65√A Where A= Cross Sectional Area	IS:1608(Part-1): 2022	18.6	14.5 Min.
5.	Bend Test	IS:1599: 2019	Satisfactory	No rupture or crack in the bent portion
6.	Rebend Test	IS IS:1786: 2008 & IS:1599-2019	Satisfactory	No rupture or crack in the rebent portion
7.	Weight, kg/mtr.	IS:1786: 2008	6.24	6.31±3%

Reviewed By
Sujeet Kumar Sada
Quality Manager



*** End of Report ***



(1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. (2) Total Liability of our Lab is limited to the invoiced amount. (3) Samples will be destroyed after 30 days from the date of testing unless otherwise specified. (4) This report is not be reproduced wholly or in part and can not be used as an evidence in the Court of Law and should not be used in any advertising media without our special permission in writing. (5) Report refer to the sample submitted to us and not drawn by Civil Tech Laboratory unless Mentioned otherwise.

An ISO : 9001 : 2015 & ISO 14001 : 2015 Certified Laboratory



CIVIL TECH LABORATORY

Kh. No. 48, Vill.- Belda, Near RTO Office, Roorkee, Distt.- Haridwar, U.K.- 247667

+91-9911860667, 8076576367

civiltechlabuk@gmail.com

www.civiltechlaboratory.com



TEST REPORT

Format No.: CTL/F/7.8/01

This report is not valid without a Hologram

Letter Ref.No.: 5170/1C, Dated: 03/11/2025

Sample Description: HYSD/TMT Bar (32 mm) (Reinforcement Steel)

Make: SEL Tiger

Issued To,

The Executive Engineer

Provincial Division, PWD

Haridwar, Uttarakhand

Location of Performance of Test: In Lab

Date of Performance of Test: 04/11/2025 to 10/11/2025

Addition to Deviation or Exclusion from the Method: NA

Name of Work: Construction of 240 M Span Double lane RCC Motor Bridge over Suswa River in Bullawala to Sattiwala Motor Road in District Dehradun.

Agreement No.: 12/U-PREPARE/23/BR/RFB-EPC/UGRIDP/2023, Dated: 18/09/2024

Name of Agency: M/s R. C. C. Developers, 109 City Centre, Children Park, Meerut, Uttar Pradesh

Report Number: CTL/MECH/251104022B

Date of Report: 11/11/2025

Job Order No.: 251104022

Sample Received On: 04/11/2025

Sample Quantity: 01 Mtr X 03 Pcs.

Sample Condition: Satisfactory

Sample Drawn By: Customer

Environment Condition (Temp. & RH) : 25±5°C & NA

I-Chemical Testing

Page No: 01 of 01

I-Metals & Alloys

S. No.	Test Parameter	Test-Method	Result	Requirement As per IS: 1786-2008 (Fe-550D)
1.	Carbon (as C), % by mass	IS:228 (Part-1):2025	0.14	0.25 Max.
2.	Sulphur (as S), % by mass	IS:228 (Part-9):1989	0.018	0.040 Max.
3.	Phosphorus (as P), % by mass	IS:228 (Part-3):2024	0.048	0.040 Max.
4.	Sulphur + Phosphorus, %	IS: 1786-2008	0.066	0.075 Max.

Reviewed By

Sujeet Kumar Sada

Quality Manager

*** End of Report***



(1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. (2) Total Liability of our Lab is limited to the invoiced amount. (3) Samples will be destroyed after 30 days from the date of testing unless otherwise specified. (4) This report is not be reproduced wholly or in part and can not be used as an evidence in the Court of Law and should not be used in any advertising media without our special permission in writing. (5) Report refer to the sample submitted to us and not drawn by Civil Tech Laboratory unless Mentioned otherwise.

An ISO : 9001 : 2015 & ISO 14001 : 2015 Certified Laboratory



CIVIL TECH LABORATORY

Kh. No. 48, Vill.- Belda, Near RTO Office, Roorkee, Distt.- Haridwar, U.K.- 247667

+91-9911860667, 8076576367 civiltechlabuk@gmail.com

www.civiltechlaboratory.com



TEST REPORT

Format No.: CTL/F/7.8/01

This report is not valid without a Hologram

Letter Ref.No.: 5170/1C, Dated: 03/11/2025

Sample Description: HYSD/TMT Bar (20 mm) (Reinforcement Steel)

Make: SEL Tiger

Issued To,

The Executive Engineer

Provincial Division, PWD

Haridwar, Uttarakhand

Location of Performance of Test: In Lab

Date of Performance of Test: 04/11/2025 to 10/11/2025

Addition to Deviation or Exclusion from the Method: NA

Name of Work: Construction of 240 M Span Double lane RCC Motor Bridge over Suswa River in Bullawala to Sattiwala Motor Road in District Dehradun.

Agreement No.: 12/U-PREPARE/23/BR/RFB-EPC/UGRIDP/2023, Dated: 18/09/2024

Name of Agency: M/s R. C. C. Developers, 109 City Centre, Children Park, Meerut, Uttar Pradesh

ULR No:TC1583225000000652F

Report Number: CTL/MECH/251104023

Date of Report: 11/11/2025

Job Order No.: 251104023

Sample Received On: 04/11/2025

Sample Quantity: 01 Mtr X 03 Pcs.

Sample Condition: Satisfactory

Sample Drawn By: Customer

Environment Condition (Temp. & RH) : 25±5°C & NA



TC-15832

I-Mechanical Testing

Page No: 01 of 01

1-Mechanical Properties of Metals

S. No.	Test Parameter	Test-Method	Result	Requirement As per IS: 1786-2008 (Fe-550D)
1.	Yield stress, N/mm ²	IS:1608(Part-1): 2022	581	550 Min.
2.	Tensile Strength, N/mm ²	IS:1608(Part-1): 2022	682	600 Min.
3.	Tensile Strength/Yield Stress ratio	IS:1786: 2008	1.17	≥ 1.08
4.	% Elongation on Gauge Length 5.65√A Where A= Cross Sectional Area	IS:1608(Part-1): 2022	19.1	14.5 Min.
5.	Bend Test	IS:1599: 2019	Satisfactory	No rupture or crack in the bent portion
6.	Rebend Test	IS IS:1786: 2008 & IS:1599-2019	Satisfactory	No rupture or crack in the rebent portion
7.	Weight, kg/mtr.	IS:1786: 2008	2.54	2.47±3%

Reviewed By
Sujeet Kumar Sada
Quality Manager



*** End of Report***

Auth. Sign.
R.K Choudhary
Technical Manager

(1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. (2) Total Liability of our Lab is limited to the invoiced amount. (3) Samples will be destroyed after 30 days from the date of testing unless otherwise specified. (4) This report is not be reproduced wholly or in part and can not be used as an evidence in the Court of Law and should not be used in any advertising media without our special permission in writing. (5) Report refer to the sample submitted to us and not drawn by Civil Tech Laboratory unless Mentioned otherwise.

An ISO : 9001 : 2015 & ISO 14001 : 2015 Certified Laboratory



CIVIL TECH LABORATORY

Kh. No. 48, Vill.- Belda, Near RTO Office, Roorkee, Distt.- Haridwar, U.K.- 247667

+91-9911860667, 8076576367

civiltechlabuk@gmail.com

www.civiltechlaboratory.com



TEST REPORT

Format No.: CTL/F/7.8/01

This report is not valid without a Hologram

Letter Ref.No.: 5170/1C, Dated: 03/11/2025

Sample Description: HYSD/TMT Bar (20 mm) (Reinforcement Steel)

Make: SEL Tiger

Issued To,

The Executive Engineer

Provincial Division, PWD

Haridwar, Uttarakhand

Location of Performance of Test: In Lab

Date of Performance of Test: 04/11/2025 to 10/11/2025

Addition to Deviation or Exclusion from the Method: NA

Name of Work: Construction of 240 M Span Double lane RCC Motor Bridge over Suswa River in Bullawala to Sattiwala Motor Road in District Dehradun.

Agreement No.: 12/U-PREPARE/23/BR/RFB-EPC/UGRIDP/2023, Dated: 18/09/2024

Name of Agency: M/s R. C. C. Developers, 109 City Centre, Children Park, Meerut, Uttar Pradesh

Report Number: CTL/MECH/251104023B

Date of Report: 11/11/2025

Job Order No.: 251104023

Sample Received On: 04/11/2025

Sample Quantity: 01 Mtr X 03 Pcs.

Sample Condition: Satisfactory

Sample Drawn By: Customer

Environment Condition (Temp. & RH) : 25±5°C & NA

I-Chemical Testing

Page No: 01 of 01

1-Metals & Alloys

S. No.	Test Parameter	Test-Method	Result	Requirement As per IS: 1786-2008 (Fe-550D)
1.	Carbon (as C), % by mass	IS:228 (Part-1):2025	0.18	0.25 Max.
2.	Sulphur (as S), % by mass	IS:228 (Part-9):1989	0.019	0.040 Max.
3.	Phosphorus (as P), % by mass	IS:228 (Part-3):2024	0.038	0.040 Max.
4.	Sulphur + Phosphorus, %	IS: 1786-2008	0.057	0.075 Max.

Reviewed By

Sujeet Kumar Sada

Quality Manager

*** End of Report***



(1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. (2) Total Liability of our Lab is limited to the invoiced amount. (3) Samples will be destroyed after 30 days from the date of testing unless otherwise specified. (4) This report is not be reproduced wholly or in part and can not be used as an evidence in the Court of Law and should not be used in any advertising media without our special permission in writing. (5) Report refer to the sample submitted to us and not drawn by Civil Tech Laboratory unless Mentioned otherwise.

An ISO : 9001 : 2015 & ISO 14001 : 2015 Certified Laboratory



CIVIL TECH LABORATORY

Kh. No. 48, Vill.- Belda, Near RTO Office, Roorkee, Distt.- Haridwar, U.K.- 247667

+91-9911860667, 8076576367 civiltechlabuk@gmail.com

www.civiltechlaboratory.com



TEST REPORT

Format No.: CTL/F/7.8/01

This report is not valid without a Hologram

Letter Ref.No.: 5170/1C, Dated: 03/11/2025

Sample Description: HYSD/TMT Bar (16 mm) (Reinforcement Steel)

Make: SEL Tiger

Issued To,

The Executive Engineer

Provincial Division, PWD

Haridwar, Uttarakhand

Location of Performance of Test: In Lab

Date of Performance of Test: 04/11/2025 to 10/11/2025

Addition to Deviation or Exclusion from the Method: NA

Name of Work: Construction of 240 M Span Double lane RCC Motor Bridge over Suswa River in Bullawala to Sattiwala Motor Road in District Dehradun.

Agreement No.: 12/U-PREPARE/23/BR/RFB-EPC/UGRIDP/2023, Dated: 18/09/2024

Name of Agency: M/s R. C. C. Developers, 109 City Centre, Children Park, Meerut, Uttar Pradesh

Report Number: CTL/MECH/251104024B

Date of Report: 11/11/2025

Job Order No.: 251104024

Sample Received On: 04/11/2025

Sample Quantity: 01 Mtr X 03 Pcs.

Sample Condition: Satisfactory

Sample Drawn By: Customer

Environment Condition (Temp. & RH) : 25±5°C & NA

I-Chemical Testing

Page No: 01 of 01

1-Metals & Alloys

S. No.	Test Parameter	Test-Method	Result	Requirement As per IS: 1786-2008 (Fe-550D)
1.	Carbon (as C), % by mass	IS:228 (Part-1):2025	0.12	0.25 Max.
2.	Sulphur (as S), % by mass	IS:228 (Part-9):1989	0.013	0.040 Max.
3.	Phosphorus (as P), % by mass	IS:228 (Part-3):2024	0.040	0.040 Max.
4.	Sulphur + Phosphorus, %	IS: 1786-2008	0.053	0.075 Max.

Reviewed By
Sujeet Kumar Sada
Quality Manager

*** End of Report***



(1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. (2) Total Liability of our Lab is limited to the invoiced amount. (3) Samples will be destroyed after 30 days from the date of testing unless otherwise specified. (4) This report is not be reproduced wholly or in part and can not be used as an evidence in the Court of Law and should not be used in any advertising media without our special permission in writing. (5) Report refer to the sample submitted to us and not drawn by Civil Tech Laboratory unless Mentioned otherwise.

An ISO : 9001 : 2015 & ISO 14001 : 2015 Certified Laboratory



CIVIL TECH LABORATORY

Kh. No. 48, Vill.- Belda, Near RTO Office, Roorkee, Distt.- Haridwar, U.K.- 247667

+91-9911860667, 8076576367 civiltechlabuk@gmail.com

www.civiltechlaboratory.com



TEST REPORT

Format No.: CTL/F/7.8/01

This report is not valid without a Hologram

Letter Ref.No.: 5170/IC, Dated: 03/11/2025

Sample Description: HYSD/TMT Bar (16 mm) (Reinforcement Steel)

Make: SEL Tiger

Issued To,

The Executive Engineer

Provincial Division, PWD

Haridwar, Uttarakhand

Location of Performance of Test: In Lab

Date of Performance of Test: 04/11/2025 to 10/11/2025

Addition to Deviation or Exclusion from the Method: NA

Name of Work: Construction of 240 M Span Double lane RCC Motor Bridge over Suswa River in Bullawala to Sattiwala Motor Road in District Dehradun.

Agreement No.: 12/U-PREPARE/23/BR/RFB-EPC/UGRIDP/2023, Dated: 18/09/2024

Name of Agency: M/s R. C. C. Developers, 109 City Centre, Children Park, Meerut, Uttar Pradesh

ULR No: TC1583225000000653F

Report Number: CTL/MECH/251104024A

Date of Report: 11/11/2025

Job Order No.: 251104024

Sample Received On: 04/11/2025

Sample Quantity: 01 Mtr X 03 Pcs.

Sample Condition: Satisfactory

Sample Drawn By: Customer

Environment Condition (Temp. & RH) : 25±5°C & NA



TC-15832

I-Mechanical Testing

Page No: 01 of 01

1-Mechanical Properties of Metals

S. No.	Test Parameter	Test-Method	Result	Requirement As per IS: 1786-2008 (Fe-550D)
1.	Yield stress, N/mm ²	IS:1608(Part-1): 2022	554	550 Min.
2.	Tensile Strength, N/mm ²	IS:1608(Part-1): 2022	629	600 Min.
3.	Tensile Strength/Yield Stress ratio	IS:1786: 2008	1.135	≥ 1.08
4.	% Elongation on Gauge Length 5.65√A Where A= Cross Sectional Area	IS:1608(Part-1): 2022	15.3	14.5 Min.
5.	Bend Test	IS:1599: 2019	Satisfactory	No rupture or crack in the bent portion
6.	Rebend Test	IS IS:1786: 2008 & IS:1599-2019	Satisfactory	No rupture or crack in the rebent portion
7.	Weight, kg/mtr.	IS:1786: 2008	1.506	1.58±5%

Reviewed By
Sujeet Kumar Sada
Quality Manager



*** End of Report***



(1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. (2) Total Liability of our Lab is limited to the invoiced amount. (3) Samples will be destroyed after 30 days from the date of testing unless otherwise specified. (4) This report is not be reproduced wholly or in part and can not be used as an evidence in the Court of Law and should not be used in any advertising media without our special permission in writing. (5) Report refer to the sample submitted to us and not drawn by Civil Tech Laboratory unless Mentioned otherwise.

An ISO : 9001 : 2015 & ISO 14001 : 2015 Certified Laboratory