

Introducing
F86SM1/DTF Ultra



Instant **"Hot"** Peel,

"Oil Free"*,

No Powder Clinging,

High Ink Absorption,

Single Matte,

No Second Press.

CONSISTENT & HIGH QUALITY **DTF FILM**

Grade: F86SM1/DTF **Ultra**

Heat Transfer Release Film - DTF Inkjet Printing.

Grade F86SM1/DTF Ultra: Is Single matte DTF film, 1 side DTF printable matte coating and Back side gloss antistatic coating.

Typical Properties

1.	Appearance	: Translucent Film
2.	Base - PET Film	: 75μ
3.	Printing side coating	: 2layers Even & Smooth Finish
4.	Back Side Gloss & Antistatic	: $10^9 \Omega - 10^{10} \Omega$
5.	Coating thickness (all layers)	: 11μ (+ / - 2μ)
6.	Matte value of release coating	: 10 GU (+ / - 1GU)
7.	Standard Size	: Sheets: On customer requirement Rolls: 1200mm, 900mm, 800mm, 600mm, 300 X 100Mtrs
8.	Print Hold Out	: Medium to High Depends on Ink and Adhesive.
9.	Release force	: Medium to Low (Hot, Warm & Cold Peel)

Special Benefits:

Quick Ink drying / Trouble free powder application / Heat Stable / Vibrant colors / Oil Free / Hot* Warm & Cold Peel / Matte finish to transfers / Soft Feel Hand Feel and Many more.....

Guidelines for printing & transfer:

- It is recommended to wear gloves while handling rolls or sheets to avoid damage on the film surface. Rolls should be packed in the moisture proof bags after use.
- Always keep the rubber gripper clean and keep unwinding tension low on printing machine for better registration.
- Preheat the printed film if required before powder application.
- In drying process we recommend powder shaker set temperature 100°C to 140°C (212°F to 284°F) for 7 minutes to 4 Minutes. Some preliminary testing on various temperature is required.
- It is necessary to cool the film before winding to avoid sticking while winding.
- Transfers should be applied from 125°C to 180°C (257°F to 356°F) for 15 to 4 seconds with 2 to 4 bars Pneumatic pressure. Note: Transfer parameters varies with type of fabric and type of machine varies Case to Case.

Note: "Oil Free"* or Moisture Free DTF Transfers needs sufficient amount of drying in Ultranex DTF Film we have tried to manage as much possible moisture evaporation trapped in the coating after printing.

- * **For instant Hot Peel:** Please ensure press machine setting like Temperature, Pressure and Pressure is Equal at all corners are correct or 1time orientation trials may be required with waste cloths. Pneumatic machines are the best for

Disclaimer: Changes can be done on above specification for improvements, Above specification data is our test values and not limits decided & derived by our best possible knowledge of printing & transfer trials / results, "results may vary with user to user in different processes, process controls & Allied materials like ink & / or hotmelt adhesive used which film manufacturer has no control", film manufacturer cannot accept or not be liable for any claims on rejection of any kind, . No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. User should test Film with required functionality with series of trials before mass productions. Suggested in house testing on sampling basis for bulk user before using in production. We reserve the right to make any changes according to technological progress or further developments.

Mfg By: