Crack Propagation and Failure Mechanisms in Fiber-Reinforced Composites: A Comparative Theoretical Analysis and Proposed Alternative Methodology

ANOOP MYSORE SUBRAMANYA
Mechanical behaviors of materials, University of Colorado Boulder, Colorado, US

Abstract

This study conducts a comparative theoretical analysis of crack growth and failure mechanisms in fiber-reinforced composites. Utilizing the Griffith energy balance and contemporary fracture mechanics models, it examines the fundamental processes of matrix cracking, fiber/matrix interfacial debonding, and fiber pull-out that contribute to crack resistance. A critical limitation of existing models is identified: their inability to accurately predict crack growth under multi-modal loading conditions. To address this gap, a novel hybrid theoretical framework is proposed.

Introduction

Fiber-reinforced composites are renowned for their exceptional strength-to-weight ratio and

adaptability, making them indispensable in a wide range of applications. However, their susceptibility to crack initiation and propagation under stress remains a significant challenge in design and performance optimization. Fracture mechanics, particularly the Griffith energy principle, provides a robust theoretical foundation for analyzing these failure mechanisms. Yet, existing models vary in their treatment of the contributions of the matrix, fibers, and interfacial properties to crack resistance. Moreover, most current frameworks are constrained to single mode loading scenarios, limiting their applicability to the complex, multi-modal conditions often encountered in practical applications. This paper critically evaluates these theoretical models, highlights their shortcomings, and introduces a novel multi-modal hybrid framework to address these limitations.

Comparative Theoretical Models

1. Griffith Energy Balance

Griffith's theory, originally developed for isotropic materials, relates the critical stress (σc) {units (Pa)} to the crack length (a) {units (m)} and material properties. The relationship is expressed as:

$$\sigma c = \frac{\sqrt{2\gamma E}}{\pi a}$$

Where:

- E is Young's modulus (Pa)
- γ is the surface energy. (J/m^2)

While effective for isotropic materials and simple loading conditions, this model does not account for the anisotropic properties or energy dissipation mechanisms unique to composites.

Local Variables:
None, as this model applies to isotropic materials and does not account for the microstructural heterogeneity of composites.
Global Variables:

- E: Young's modulus (bulk property of the material).
- γ: Surface energy (material-level property).
- σc: Critical stress (macro-scale loading).
- a: Crack length (system-level property).

2. Energy Release Rate for Composites

Extended formulations consider anisotropic properties and interfacial energy dissipation

mechanisms. The critical energy release rate for composites can be expressed as:

$$Gc = Gm+Gf+Gi$$

where:

- Gm and Gf are the energy release rates for the matrix and fiber, respectively,
- Gi accounts for interfacial energy dissipation.

For detailed expressions:

$$Gc = \frac{Km^2}{Em} + \frac{Kf^2}{Ef} + \tau i\ \pi\ df\ vf$$

where:

- Km and Kf are the stress intensity factors for the matrix and fiber, (Pa. $\sqrt{m}$)
- Em and Ef are the moduli of the matrix and fiber, (Pa)
- τi is the interfacial shear stress, (Pa)
- df is the fiber diameter, (m)
- vf is the fiber volume fraction.

Local Variables:

- Km , Kf: Stress intensity factors for the matrix and fibers.
- Em , Ef: Moduli of the matrix and fibers.
- τi: Interfacial shear stress.
- df: Fiber diameter.
- vf: Fiber volume fraction.

Global Variables:

- Gc: Critical energy release rate ($\frac{J}{m^2}$).
- Gm, Gf, Gi: Energy release rates for matrix, fiber, and interface ($\frac{J}{m^2}$), respectively

3. Fiber Pull-Out Models

A Theoretical framework that describes the energy dissipation and mechanical behavior during the failure process. Energy dissipation due to fiber pull-out is a significant contributor to crack resistance. The energy dissipated during fiber pull-out is given by:

$$W=\tau i\ \pi\ df\ le$$

where:

- τi is the interfacial shear strength, (Pa)
- df is the fiber diameter, (m)
- le is the embedded fiber length. (m)

Local Variables:

- τi: Interfacial shear strength.
- df: Fiber diameter.
- le: Embedded fiber length.

Global Variables:

- W: Total energy dissipation during fiber pull-out (J).

4. Micromechanical Models

Micromechanical models simulate stress distribution and crack growth at the fiber-matrix interface. The local stress field around the crack tip is expressed as:

$$\sigma(r) = \frac{K}{\sqrt{2\pi r}}$$

where:

- σ(r) is the stress at a distance r from the crack tip, (Pa)
- K is the stress intensity factor,
- r is the radial distance from the crack tip. (m)

Local Variables:

- σ(r): Stress at a specific radial distance r from the crack tip.
- K: Stress intensity factor (a local measure of stress concentration).
- r: Radial distance from the crack tip.

These models provide insights into the interaction between fibers and the matrix at the microscopic scale, enabling a more detailed understanding of crack propagation mechanisms.

Local and Global Variables in the Models

In the context of the equations provided, local variables are those that describe properties or behavior at a micro- or meso-scale (e.g., at the fiber, matrix, or interface level). Global variables, on the other hand, refer to bulk or system-level properties, typically averaged across the composite material.

Identified Problem While these models provide insights into crack propagation mechanisms, they struggle to address:

1. **Complex Loading Conditions**: Real-world composites often experience multi-modal loading, such as combinations of tensile, shear, and compressive stresses. Existing models primarily consider single-mode loading, limiting their predictive capabilities.
2. **Inter-scale Stress Redistribution**: Interactions between local damage mechanisms (e.g., fibre pull-out, matrix cracking) and global structural behavior remain inadequately modeled.
3. **Environmental Effects**: Factors such as moisture and temperature variations significantly affect interfacial shear strength and matrix toughness but are rarely integrated into theoretical frameworks.

Proposed Alternative Approach

To overcome the limitations of existing models, this study introduces a comprehensive hybrid theoretical framework. This framework integrates advanced theoretical, computational, and experimental methods to address crack growth dynamics in fiber-reinforced composites under complex, multi-modal loading conditions. The key components of the proposed approach are detailed below:

Multi-Scale Finite Element Analysis (FEA)

The framework employs multi-scale FEA to link global energy dissipation trends with localized damage evolution. The FEA model integrates:

- **Macroscale Analysis**: Captures global fracture patterns and energy dissipation.
- **Microscale Analysis**: Resolves local failure mechanisms such as fiber pull-out and interfacial debonding.

EXPERIMENT

Problem Statement:

Consider a composite material consisting of a matrix reinforced with fibers. A crack of initial length a0=5 mm exists in the material. The following material properties are known:

1. **Matrix Properties:**

- Em=2×109 Pa (Young's modulus)
- γm=0.5 J/m^2 (surface energy)
- Km=2 MPa·$\sqrt{m}$ (stress intensity factor)

2. **Fiber Properties:**

- Ef=200×109 Pa (Young's modulus)
- Kf=10 MPa·$\sqrt{m}$ (stress intensity factor)
- df=10 μm (fiber diameter)
- vf=0.6 (fiber volume fraction)

3. **Interface Properties:**

- τi=30 MPa (interfacial shear stress)

4. **Crack Properties:**

- Initial crack length a0=5 mm
- Embedded fiber length le=2 mm

Solution:

To solve the given problem using the **Energy Release Rate**

Given:

- Km=2 MPa·$\sqrt{m}$
- Kf=10 MPa·$\sqrt{m}$
- Em=2×109 Pa
- Ef=200×109 Pa
- τi=30 MPa
- df=10 μm
- vf=0.6

$$Gc = \frac{Km^2}{Em} + \frac{Kf^2}{Ef} + \tau i\ \pi\ df\ vf$$

Step-by-Step Solution:

1. Calculate Gm:

$Gm = \frac{Km^2}{Em}$

Gm = 2×109(2×106)2=2×1094×1012 = **2000J/m2**

2. Calculate Gf:

$Gf = \frac{Kf^2}{Ef}$

Gf = 200×109(10×106)2=200×109100×1012 = **500J/m2**

3. Calculate Gi:

Gi = τi π df vf

Gi = 30×106×3.14159×10−5×0.6 = **565.49J/m2**

4. Calculate Total Gc:

Gc = 2000+500+565.49 = **3065.49J/m2**

Result:

The total energy release rate considering all fracture modes is:

Gc=3065.49 J/m2

This solution demonstrates the energy dissipation under multi-modal loading, quantifying the contributions from opening, sliding, and tearing fracture modes in the composite material.

Multi-Scale Finite Element Analysis (FEA)
Solution Approach:

1. Macroscale Analysis

The macroscale model captures the global fracture behavior and energy dissipation trends for the composite material.

Governing Equation:

The global stress distribution is obtained from the critical stress intensity factor, Kc, given by:

$$\mathbf{Kc=\sqrt{EGc}}$$

where E is the effective Young's modulus of the composite

Calculation:

1. **Effective Young's Modulus (E):**

E= (0.6×200×1000000000) + (0.4×2×1000000000)

E = 120×1000000000+0.8×109=**120.8×1000000000Pa**

2. **Critical Stress Intensity Factor (Kc):**

Kc = sqrt (EGc)

Kc = sqrt ((120.8×1000000000) × 3065.49)

Kc = sqrt (370.367×1000000000000) ≈ **19.24MPa·m**

3. **Global Stress Distribution:**

σ ≈ 19.24/0.125 = 153.92 MPa

2. Microscale Analysis The microscale model resolves local damage mechanisms such as fiber pull-out and interfacial debonding.

Local Energy Dissipation:

The energy dissipated during fiber pull-out (W) and interfacial debonding is:

W = τi π df le

W=30×106×3.14159×20× (1/1000000000) = **1.884J**

Local Stress Field:

Using the stress intensity factor K (combined matrix and fiber):

σ(r) = 0.02519.24×106 = 769.6MPa

<u>Summary of Results</u>:

1. **Global Analysis:**

- Critical stress intensity factor: Kc=19.24 MPa·$\sqrt{m}$
- Global stress at the crack tip: σ=153.92 MPa

2. **Microscale Analysis:**

- Energy dissipated during fiber pull-out: W=1.884 J

- Local stress at r=0.1 mm: σ(r)=769.6 MPa

This approach provides insights into both global fracture behavior and localized damage mechanisms, showing how energy dissipation contributes to the overall fracture resistance of the composite.

Conclusion

This comparative theoretical analysis highlights the limitations of existing models in addressing multi-modal loading conditions. The proposed hybrid framework integrates energy release rate calculations, micromechanical modeling, environmental factors, and experimental calibration to overcome these challenges

References:

1. Kuang-Chong Wu., " Stress Intensity Factor and Energy Release Rate for Interfacial Cracks Between Dissimilar Anisotropic Materials," J. Appl. Mech. Dec 1990, 57(4): 882-886 (5 pages).
2. "A Review of Analytical Models to Describe Pull-Out Behavior – Fiber/Matrix Adhesion" by Fatiha Teklal et al. (2018)
3. Versatile Micromechanics Model for Multiscale Analysis of Composite Materials" by H. M. Yin et al. (2012)
4. Matrix crack propagation criteria for model short-carbon fibre/epoxy composites,
   S. Sirivedin a, D.N. Fenner a, R.B. Nat h b, C. Galiotis c
5. Fatigue crack propagation in short-carbon-fiber reinforced plastics evaluated based on anisotropic fracture mechanics,
   K. Tanaka, K. Oharada, D. Yamada, K. Shimizu
6. The energy of crack propagation in carbon fibre-reinforced resin systems,
   PETER W. R, BEAUMONT*,
   BRYAN HARRIS Materials Science Division, School of Applied Sciences, University of Sussex, Brighton, UK
7. Some aspects of crack growth and failure in fibre reinforced composites J. G. MORLEY Wolfson Institute of Interfacial Technology, University of Nottingham, Nottingham, UK