Refname	DD:sdf.tol
Label	J_{tol}
Units	
Equation	$J_{tol} = \log\left(\log\left(\frac{1}{1-P_{btol}}\right)\frac{\left(\frac{a}{1000}\frac{b}{1000}\right)^{m-1}}{k\left((E*1000)\left(\frac{h}{1000}\right)^2\right)^m*LDF}\right)$
Description	J_{tol} is the stress distribution factor (Function) based on Pbtol P_{btol} is the tolerable probability of breakage a is the plate length (long dimension) b is the plate width (short dimension) m is the surface flaw parameter k is the surface flaw parameter E is the modulus of elasticity of glass h is the actual thickness LDF is the load duration factor