Fabric Inspection

Every roll of fabric is inspected on the 4-point system before cutting.
A roll with more than 40 penalty points per 100 square yards is rejected.

Shade Matching

Shade variation between rolls of the same lot is checked under D65 light.
Colour fastness to washing must be grade 4 or better.

Garment Audit

Final inspection uses AQL 2.5 for major defects and AQL 4.0 for minor defects.
A failed lot is fully re-inspected by the quality team before re-offering to the buyer.

Measurement Tolerance

Chest and length measurements may vary by at most 1 cm from the size chart.