

Nexivarin 10 mg Tablets — eCTD Submission
Module 3 — Quality

Submission Type	NDA — 505(b)(1)	Sequence Number	0000
Submission Date	2021-03-15	Section	3.2.P.3
Prepared by	PharmaCorp Inc.	Confidentiality	Proprietary and Confidential

Table of Contents — [3.2.P.3](#) Drug Product — Manufacture

Section	Title	Description
3.2.P.3	Manufacture — Nexivarin 10 mg Film-Coated Tablets	Manufacturing overview
3.2.P.3.1	Manufacturer(s)	PharmaCorp Manufacturing LLC, Newark, NJ — all manufacturing stages
3.2.P.3.2	Batch Formula	Commercial batch formula (500,000 tablets; 90 kg batch)
3.2.P.3.3	Description of Manufacturing Process	Process flow diagram — wet granulation, compression, film coating
3.2.P.3.4	Controls of Critical Steps and Intermediates	Key process parameters and in-process acceptance criteria
3.2.P.3.5	Process Validation and/or Evaluation	Blend uniformity, dissolution, and content uniformity validation

PharmaCorp Inc.
NDA 123456

Nexivarin 10 mg Tablets

Section 3.2.P.3
Drug Product — Manufacture

Submission Type	NDA — 505(b)(1)
Sequence Number	0000
Submission Date	2021-03-15
Prepared by	PharmaCorp Inc.
Confidentiality	Proprietary and Confidential

3.2.P.3 Manufacture — Nexivarin 10 mg Film-Coated Tablets

3.2.P.3.1 Manufacturer(s)

Role	Facility	Address
Manufacturing Site (Tablet)	PharmaCorp Manufacturing LLC	200 Production Blvd, Newark, NJ 07102
Batch Release	PharmaCorp QC Laboratory	200 Production Blvd, Newark, NJ 07102
Primary Packaging	PharmaCorp Packaging Div.	200 Production Blvd, Newark, NJ 07102

3.2.P.3.2 Batch Formula

Commercial batch size: 500,000 tablets (90 kg batch)

Component	Per Tablet (mg)	Per Batch (kg)	% w/w
Nexivarin Hydrochloride (API)	10.00	5.00	5.56
MCC PH102	80.00	40.00	44.44
Lactose Monohydrate	55.00	27.50	30.56
Croscarmellose Sodium	8.00	4.00	4.44
Colloidal Silicon Dioxide	2.00	1.00	1.11
Magnesium Stearate	2.00	1.00	1.11
Core Tablet	157.00	78.50	87.22
Opadry White 03F280023	13.00	6.50	7.22
Purified Water (removed)*	q.s.	q.s.	—
Film-Coated Tablet	180.00	90.00	100.00

*Purified water is evaporated during film coating

3.2.P.3.3 Description of Manufacturing Process

Step	Unit Operation	Key Process Parameters	In-Process Controls
1	Dispensing & sieving	Sieve API and excipients through 30-mesh screen	Visual inspection; weight check
2	High-shear granulation (HSG)	Impeller speed: 200–300 rpm; Granulation liquid: purified water (8–12% w/w); Endpoint: power consumption	Granule LOD (3–5%)
3	Fluid bed drying	Inlet air temp: 55–65°C; Product temp: 40–50°C; Airflow: 800–1000 CFM	LOD NMT 2.0%
4	Milling	Comil 197S; Screen 1.5 mm; Impeller speed 1500 rpm	Particle size distribution
5	Lubrication blending	Bin blender; 5 min at 10 rpm; Add Mg stearate	Blend uniformity (RSD ≤ 5.0%)
6	Tablet compression	Fette 3090 press; Target weight 157 mg ± 3%; Hardness 10–14 kP; Speed 70,000 tab/h	Weight, hardness, friability, disintegration

Step	Unit Operation	Key Process Parameters	In-Process Controls
7	Film coating	Pan coating; Inlet air 60°C; Product temp 42–46°C; Spray rate 150–200 g/min; 7.22% weight gain	Weight gain; appearance; moisture
8	Packaging	HDPE 60cc bottles; 30 tablets per bottle; Induction seal + child-resistant cap	Tablet count; seal integrity; torque