


A-75 – FIBERGLASS MESH

Product:	A-75 - fiberglass mesh	
Size, packaging:	1m*50m = 50sqm/roll	
Application:	Strengthening mesh for internal cementous surface plasters for reducing risk of crackings. It is also applicable for replastering of cracked surfaces.	
Material:	"C" glass; treatment: alkali-resistant without emollient, obstructing yarn drifting	

Properties	Relevant standards	Technical data
Length	Manufacturer's declared value (MDV)	50m (±1%)
Width	MDV	100cm (±1%)
Treated fabric thickness	MDV	min. 0,40mm
Square dimension	MDV	5x5mm
Treated fabric weight	MDV	75g/m ² (±10%)
Combustible matter content	MDV	~10%
Setting per 10 cm (warp/weft)	MDV	20x2 / 20
Tensile strength (warp/weft)	ETAG 004	850 N/5cm / 1200 N/5cm
Elongation (warp/weft)	ETAG 004	3,1% / 2,9%
Tensile strength after aging (warp/weft)	ETAG 004	650 N/5cm / 800 N/5cm
Elongation (warp/weft)	ETAG 004	1,8% / 1,7%

Storage and handling

Packed rolls are to be stored in dry rooms, protect against UV and heat, practically packed in plastic foil, vertically in cardboard box, on a wooden pallet. The temperature of storing shall be between (-)10°C and (+)50°C.

Guarantee, warranty

In accordance with the current legislations and the conditions of the distributor. The observation of the application rules of the product and presentation of the invoice constitute a prerequisite for possible future warranty claims.

Health and safety

No labelling required in accordance with the relevant regulation (EC) No. 1907/2006 of the European Parliament and of the Council (REACH).

This datasheet corresponds to our current knowledge, experiences and general informations on the subject, but may be revised as new knowledge and/or experience becomes available. It does not imply any legally binding assurance. The product possesses the given technical characteristics. Since all variations of end-using of the product can not be anticipated, the designer/end-user's responsibility to make sure of the suitability of this product for particular purposes, structures.

This technical datasheet is applied to products sold by Estucalia Morteros, S.L and valid until withdrawal or until modification. Since this datasheet may be subject to revision, it is the responsibility of designer/end-user to make sure of possessing the latest version of the datasheet (*see date of issuing). Most recent version of this datasheet can be also accessed under www.grupoestucalia.com. Modification of this technical datasheet repeals the previously issued versions!

*Issued: 2012. 01. 01.