

Composite Laminate Tool v3: progressive failure and validation status

Report No. 2 · 7 October 2026 · Author: Artem · App: <https://composite-laminate-tool.streamlit.app/> · Code: <https://github.com/Artyom09062002/composite-laminate-tool>
Educational and screening tool. Not a certified design calculation.

1. Purpose

This report documents version 3 of the laminate tool, which now covers a filament-wound pressure vessel with a geodesic dome and a progressive (ply-by-ply) failure model. It states what changed after an independent review of the Hashin and progressive-failure code, and reports the first attempt to compare the model with published burst-test data. The result of that comparison is mostly negative, and it is reported as such.

2. What changed since v2

- Dome: geodesic winding (Clairaut), thickness build-up and membrane resultants along the dome; the cylinder junction and the polar-opening zone are flagged and excluded from the headline value.
- Hashin criterion (plane stress, four modes, active mode, strength ratio) reported next to Maximum Stress and Tsai-Wu.
- Progressive failure: load factor from first-ply to the last-ply stopping point, failure sequence, ABD rebuilt after every failure, load-strain curve.
- Pressure vessel tab: CLT first-ply, Hashin first-ply, last-ply and the netting estimate side by side, with editable degradation factors.
- Review corrections (Section 4) and a validation harness (validation/). Historical baselines: 43 tests in v2, 120 at C4. Current refinement checks are recorded in verification/AUDIT.md.

3. Method summary

Vessel wall. A closed thin cylinder of radius R under pressure p carries $N_x = pR/2$ and $N_y = pR$. Netting theory (fibres only) balances both at the winding angle $\tan^2\theta = 2$, $\theta = 54.74^\circ$; the app solves axial and hoop fibre-only equilibrium, without strain compatibility or shear equilibrium. CLT first-ply uses Maximum Stress and Tsai-Wu.

Hashin initiation (plane-stress, Hashin-1980-inspired; σ_3 , τ_{13} , τ_{23} are not assessed). Fibre tension: $(\sigma_1/X_t)^2 + \alpha(\tau_{12}/S)^2$, $\alpha = 1$; fibre compression: $(\sigma_1/X_c)^2$; matrix tension: $(\sigma_2/Y_t)^2 + (\tau_{12}/S)^2$; matrix compression: $(\sigma_2/2S_T)^2 + [(Y_c/2S_T)^2 - 1]\sigma_2/Y_c + (\tau_{12}/S)^2$. The load factor solves $\text{index}(\lambda\sigma) = 1$. $\alpha = 1$ is a chosen setting, and $S_T = Y_c/(2 \tan 53^\circ)$ is an assumption used when no transverse shear strength is given.

Progressive failure (ply discount, load-controlled, linear between failures). At each failure the failed ply is degraded (fibre failure: $E_1 \times 0.01$; matrix failure: E_2 and $G_{12} \times 0.1$), ABD is rebuilt and the next failure load is found exactly. A ply loaded beyond its original strength again is degraded a second time; a third exceedance stops the run (a two-level residual-stiffness termination rule). The degradation factors and this rule are model assumptions, not material data. The last-ply value is where the algorithm stops, not a validated ultimate or burst load.

4. Independent review and what it changed

A second AI model reviewed the Hashin and progressive-failure code in 12 comments. Each was verified by derivation or by running the code before any change: 3 confirmed as defects, 6 confirmed as claims stronger than the model supports (wording, labelling), 3 partly confirmed, none rejected outright (five parts were deliberately not acted on, with reasons in the audit file). The Hashin formulas and the load-factor solver were not changed.

Finding (confirmed)	Consequence found by test	Action
Pure in-plane shear with $\alpha = 1$ gives $FT = MT = 1$	Progressive model degraded fibres and matrix in all plies of a UD laminate under pure shear (8 events, $E_1 \times 0.01$ with no fibre stress)	Initiation unchanged; a fibre-tension index driven by its shear term is applied as matrix damage (documented choice, not validated)
$S_T = Y_c/(2 \tan 53^\circ)$ is not a measured property	The check $MC = 1$ at $\sigma_2 = -Y_c$ holds for any S_T ; the default (92.7 MPa) exceeds $S_{12} = 68$ MPa for T300/5208	Marked ASSUMED in every result; S_T varied as sensitivity
"Last-ply" read as an ultimate load	All residual stiffnesses stay positive; no stability check; load factor never reduced	Renamed "model stop"; held steps flagged


Finding (confirmed)	Consequence found by test	Action
Stopping and new failures at the same load	New failures at the stopping load were dropped from the failure list	Single batch rule, tested

Not acted on: calibrated mode-specific degradation rules and fracture-energy regularisation (no calibration data, out of scope for a screening model), stability-aware solution control, and the claimed dependence on splitting a ply (load factors were identical for 1 to 8 sub-plyes in the cases tried; only event counts change).

5. Validation against published burst-test data

Four research cases (three conditional, none usable for a like-for-like comparison) were assembled with an AI research assistant and are unverified. The supplied text does not explicitly report the inner radius, and the two Type III vessels have a metal liner the model does not contain. Pressures in bar unless stated. No parameter was tuned to any measurement.

Case (source)	Measured [bar]	CLT first-ply	Hashin first-ply	Last-ply (stop)	Netting	Status
Kangal GF P1	919	19	19	168	242	composite wall only; steel liner not modelled
Kangal GF P2	879	18	18	161	232	composite wall only; steel liner not modelled
Kangal hybrid P1	922	23-47	23-47	202-342	291-485	two material assignments; stack order unsourced
Kangal hybrid P2	887	20-41	20-41	175-297	253-421	two material assignments; stack order unsourced
Alam T800S (p-R, kN/m)	161 (mean of 3)	725	719	833	789	radius unsourced; equals measured at R = 45-52 mm
Kartav ALCF10-13 (netting)	1355-1480	n/a	n/a	n/a	393-449 (R = 153 mm); 786-898 (R = 76.5 mm)	radius ambiguous; Al liner; order unsourced



Reading. The comparison cannot confirm or reject the model. (i) The composite-only netting estimate is 0.26 of the measured total for the Kangal glass vessels; omitted liner load sharing prevents a like-for-like interpretation. (ii) The measured gain over the bare steel liner (mean 657 bar) is 262 and 222 bar against netting 242 and 232 bar (ratios 0.92 and 1.05); this is a plausibility check only, since a yielding liner does not share load additively and the bare liners themselves scatter by 622-692 bar. (iii) First-ply is 19 bar, about 2 % of burst: matrix cracking, not burst. (iv) The last-ply value moves from 64 to 243 bar with the unsourced stack order of the same 12 plies and by a factor of 3.5 over the residual factors, while netting stays at 242 bar. (v) For Alam the separate calculated thresholds equal measured mean pressure at implied radii 45-52 mm. The radius is not reported in the supplied text, so this coincidence cannot be scored as validation. (vi) Using Kartav's transcribed radius (153 mm), the composite-only netting estimate is 29-32 % of the measured total burst. This mismatch does not establish an error in the paper: liner load sharing is omitted and the geometry interpretation needs Figure 1.

Likely causes of the gaps: liner not modelled; dome and end effects; fibre-to-ply strength translation (netting uses the ply X_t); unsourced radius, dome and stack order; free-plate CLT for unsymmetric walls; test scatter (919 vs 879 bar for one design, 6 % between identical Kartav configurations).

6. Limits

Not modelled: liner and boss, dome progressive failure, interlaminar stresses and delamination, thermal and cure stresses, moisture and temperature, fatigue, impact, holes and concentrators, manufacturing defects, fibre kinking, crack growth, leakage and stability of the softening path. Strengths are literature values, not qualified allowables. Use physical ply layers; there is no fracture-energy regularisation, so discretisation-independent softening is not established.

7. Next steps

- Read the radius, polar opening and dome from the paper figures (Alam, Kangal, Kartav) and re-run `validation/run_validation.py`.
- Prefer a Type IV case with a published burst value (Lüders 2025: extract the burst event from the public CSV) so that the liner does not dominate.
- Add the liner as a simple load-sharing element only when its properties are sourced.
- Thermal residual stresses and labelled cylinder layup screening were added after this C4 comparison; their verification is recorded separately.
- Repeat the stack-order test with a shell-restrained wall instead of free-plate CLT.

8. AI workflow

Two AI models were used, and each reviewed the other's work. Claude wrote and ran the code and verified every review comment by derivation or by running the code before acting. ChatGPT assembled the published burst-test data and acted as independent reviewer of the dome module (10 comments: 4 confirmed, 6 rejected as errors after verification) and of the Hashin and progressive-failure code (12 comments, Section 4). Claude in turn checked ChatGPT's data for internal consistency and recorded 11 flags, among them the missing inner radius in every source. The list of confirmed and rejected review comments, with reasons, is in `verification/AUDIT.md`, with per-round tables in `verification/REVIEW_C3.md` and `verification/REVIEW_C4.md`. Reviewer remarks that cite the literature were not independently checked against the sources.