



TECHNICAL DATA SHEET

M ONE Zink Spray

Product description

M ONE Zinc Spray for galvanizing and repairing damaged areas on galvanized parts, welding and... Interfaces in steel construction and hobby areas. M ONE Zinc Spray takes over the task there Corrosion protection and provides a visual appearance due to its color similarity to freshly galvanized materials compensation.

The special advantages of M ONE Zinc Spray are:

- Quick-drying, smooth film
- High adhesion
- Can be painted over
- Heat resistant up to 200°C and briefly up to 300°C

Application instructions

M ONE Zinc Spray is used in areas of industry, crafts and other trades, always where galvanized metals have been processed or damaged. The main application of M ONE Zinc Spray can be found in the area of air conditioning and ventilation technology, on heating systems, in pipeline construction and at machine housings.

Processing instructions

Optimal processing temperature: 16°C-25°C. Shake the can vigorously before each spraying for 2 minutes audible stop of the ball and test spray. Derust and degrease spray surfaces beforehand. From one Apply M ONE Zinc Spray crosswise at a distance of 25-30 cm. For multiple layers, 5-8 minutes each Take a break. After about 8 minutes the surface is dust dry and after 20-25 minutes it is touch-proof. M ONE Zinc Spray dries completely after about 24 hours.

M ONE
At Kapellenberg 11
97246 Eibelstadt
Tel: +49 9366 90710
info@m-one.net www.m-one.net

With this information we want to advise you to the best of our knowledge based on our experiments and experiences. A guarantee for that However, we can determine the processing results in individual cases due to the large number of possible uses and those beyond our control We do not accept the storage and processing conditions of our products. Carry out your own experiments. Slight discoloration of sealants under UV radiation possible. Minor color variations between batches due to product technology. There is no guarantee for absolute color fidelity taken over. Use material from the same batch for each object. Our technical and commercial advisory service is at your disposal.

With the publication of this data sheet, all previous editions become invalid.

Issue: 08.24