
Framework view

Descriptor summary

Prediction audit

A




IRMOF-6-like Cu framework


Severe topology/metal error

Split	Topology-grouped
Topology	pcu
Metal cluster	2157.0
Df / PLD	7.252 Å
Di / LCD	7.748 Å
Density	0.965 g cm^{-3}
AVAf	0.112
ASA	306.3 m^2 g^{-1}
POAVA	851.8

Severe grouped underprediction; metal-cluster 2157.0 stress-test case.



B




Dia-linked Cu framework


Geometry/pore-regime error

Split	Geometry-grouped
Topology	dia
Metal cluster	108.0
Df / PLD	8.351 Å
Di / LCD	8.712 Å
Density	1.035 g cm^{-3}
AVAf	0.171
ASA	322.5 m^2 g^{-1}
POAVA	976.7

Geometry hold-out; pore-regime transfer difficulty.



C



MOF-177-like tbo framework

Shortlist dropout

Split	Topology-grouped
Topology	tbo
Metal cluster	1866.0
Df / PLD	12.399 Å
Di / LCD	24.182 Å
Density	0.309 g cm^{-3}
AVAf	0.524
ASA	4690.9 m^2 g^{-1}
POAVA	21111.7

Random elite candidate strongly demoted under topology grouping.

