

Aishangjia BAYAG Resin Washed Stone

1.Product description:

ingredient	Two-component system
intensity	high-intensity
viscosity	3000±750
solidify	Chemical solidification
purpose	Used for indoor and outdoor walls,floors,stairs,garages,lanes,balconies,and pool edge surfaces



Aishangjia BAYAG Resin Washed Stone is a two-component high-strength building material. It does not contain solvents, is non-corrosive, has high hardness, superior compressive strength, high and low temperature resistance, acid and alkali resistance, oil and water resistance, ultraviolet resistance, excellent chemical resistance, excellent adhesion and compatibility, and excellent maintenance convenience. Therefore, it is one of the most suitable materials for outdoor use.

2.Purpose:

For use on interior and exterior walls, floors, stairs, garages, driveways, balconies, and pool edges。

3. Performance parameters:

Chemical type	polyurethane resin
Color	colorful
Low temperature tolerance	No cracks found when bent at -25℃-ETAG026
High temperature tolerance	No cracks found when bent at 180℃-ETAG026
Chemical tolerance	Performance retention rate after acid-base salt corrosion-ETAG026
Complete curing time	48 hours
Surface drying time(25℃)	6 hours
Hardness(Shore)	82
Compressive strength	65MPa
Bending strength (flexural strength)	32MPa
Water absorption rate	0.09%
UV resistance/weather resistance	After 3000 hours of accelerated aging with QUV,AE(color difference)1.3 passed the 10000 hour artificial climate aging test without powdering or cracking
Chemical resistance	After soaking in a 10% sulfuric acid/sodium hydroxide solution for 28 days, the mass change rate was 0.15%, and there was no significant decrease in surface gloss and hardness

4. Solidification characteristics:

Aishangjia BAYAG Resin Washed stone is mainly cured through chemical curing; it is cured on-site at room temperature and is easy to use; it is non-corrosive to metals.

5. Packaging:

The product is packed in a 20-liter barrel, with a net weight of 25 kilograms per barrel.

6.Instructions for use:

- (1) Base treatment: The surface of the base should be clean and solid, without dust or other phenomena;
- (2) Construction method: Open the bucket, stir the resin in the bucket in advance, then stir the resin with the colored stones to ensure that the colored stones are completely wrapped by the resin, and then use a trowel to scrape and level it. One-time molding, reference dosage is about 7 kilograms per square meter, and it is recommended that the total thickness of the coating be between 1.5 and 1.8 centimeters;
- (3) Recommended total dosage: 7-9 kg/m², depending on the density of the substrate;
- (4) Note: No water is allowed, and construction is not allowed on rainy days.

7.Storage conditions:

- (1) It must be stored in a ventilated and dry warehouse with a temperature between 5-35°C.

This product cannot come into contact with water, as this will affect the quality of the product's curing.

(3) This product has a shelf life of 24 months from the date of manufacture. It is recommended to conduct a performance evaluation before use after the shelf life has expired.

8.Precautions:

- (1) Construction cannot be carried out on rainy days;
- (2) No stepping within 8 hours after construction;
- (3) The resin and colored stones must be thoroughly mixed;
- (4) The ground should be free of water or dust;
- (5) If it accidentally gets into your eyes, please rinse them with clean water immediately and seek medical attention in a timely manner;
- (6) Prevent accidental ingestion.

9.Disclaimers:

All data contained in the report is for informational purposes only, and the company is not responsible for the results of methods beyond our control. If you have any questions, please contact the company's technical department.