

BAYAG Resin Washed Stone TDS

JILIN Province Aishangjia Environmental Protection New Materials Co., Ltd.
Address: Hongxing International Plaza, No.826 Yuanda Street, Changchun
Tel: 0431- 80857777

1. Product Description

Item	Specification	
Composition	Two-component	
Strength	High-strength	
Viscosity	3000±750 mPa·s (25℃)	
Curing mode	Chemical curing	
Application	Interior & exterior wall, floor, stair, garage, driveway, balcony, pool edge	

BAYAG Resin Washed Stone is a two-component high-strength flooring decorative composite material. It is solvent-free and non-corrosive. Featuring high hardness, excellent compressive strength, resistance to high & low temperature, acid-alkali, oil-water and UV radiation. Long-term non-yellowing for outdoor application. It delivers outstanding chemical resistance, excellent adhesion and compatibility, easy maintenance, ideal for outdoor landscape and traffic-bearing paving areas.

2. Application

Suitable for interior and exterior walls, floors, stairs, garages, driveways, balconies and pool edges.

3. Technical Data

Item	Value
Resin type	Polyurethane resin
Colour	Multi-colour aggregate
Low-temperature resistance	No crack under bending at -25℃-ETAG 026
High-temperature resistance	No crack under bending at 180℃-ETAG 026
Chemical resistance	Retention under acid-salt-alkali exposure-ETAG 026
Pot life	45-60 min (25℃)
Full curing time	72 hours (full load-bearing strength)
Surface dry time (25℃)	6 h
Hardness (Shore-D)	82
Compressive strength	65 MPa
Flexural strength	32 MPa
Water absorption	0.09%
UV-aging resistance	3000 h QUV accelerated test, no chalking, no cracking, long-term non-yellowing outdoors
Chemical performance	28-day immersion in 10% H ₂ SO ₄ / NaOH solution, mass change 0.15%, no obvious drop in gloss & hardness
Water permeability coefficient	≥1.0×10 ⁻² cm/s, comply with GB/T25993-2023
Anti-slip performance (BPN, JGJ/T331-2014)	Dry ≥62 BPN; Wet ≥58 BPN

4. Curing Behaviour

BAYAG Resin Washed Stone cures by chemical reaction. Cures at ambient temperature, easy for on-site application, non-corrosive to metal substrates.

5. Packaging

Supplied in 20L bucket, net weight 25 kg per set.

Decorative washed stone aggregate pre-filled inside bucket. Resin Part A & Part B are supplied in separate sealed bottles inside bucket. Mixing ratio A:B = 1.2:1 by weight. Each set for one-time use only, do not split.

6. Installation Instruction

- (1) Substrate preparation: Substrate must be sound, clean, free of dust, grease and contamination.
- (2) Application: Open bucket, fully mix Part A and Part B resin, then blend thoroughly with pre-filled stone aggregate until all stones are fully coated by resin. Trowel and compact in one pass. Reference coverage approx. 7 kg/m². Recommended thickness: 1.5-1.8 cm.
- (3) Recommended consumption: 7-9 kg/m², subject to substrate condition.
- (4) Note: Do NOT add water. Do not install under rainy conditions.

7. Storage

- (1) Store in dry & ventilated warehouse, storage temperature: 5-35°C.
- (2) Keep away from moisture, water contact will impair curing performance.
- (3) Shelf life: 24 months from production date. Technical evaluation is recommended if expired.

8. Safety & Notice

- (1) Do not apply in rainy weather.
- (2) No foot traffic within 12 hours after installation; vehicle access permitted after 72 hours.
- (3) Ensure thorough mixing of resin and aggregate.
- (4) Substrate must be dry and dust-free.
- (5) In case of eye contact, rinse immediately with plenty clean water and seek medical advice.
- (6) Keep out of reach of children.

9. Disclaimer

All data provided is for reference only. Manufacturer assumes no liability for performance loss caused by improper application beyond controllable conditions. Please contact our technical department for further advice.