

matsci.py: materials science at the atomic-scale with Python

Petr Grigorev^{1*}, Lucas Frérot^{2*}, Fraser Birks³, Adrien Gola^{2,4}, Jacek Golebiowski¹, Jan Griebner², Johannes L. Hörmann², Andreas Klemenz⁵, Gianpietro Moras⁵, Wolfram G. Nöhring², Jonas A. Oldenstaedt², Thomas Reichenbach⁵, Lakshmi Shenoy³, Michael Walter⁸, Simon Wengert⁷, James R. Kermode^{3*}, and Lars Pastewka^{2,8*}

¹ Aix-Marseille Université, CNRS, CINaM UMR 7325, Campus de Luminy, 13288 Marseille, France ² Department of Microsystems Engineering, University of Freiburg, 79110 Freiburg, Germany ³ Warwick Centre for Predictive Modelling, School of Engineering, University of Warwick, Coventry CV4 7AL, United Kingdom ⁴ Institute for Applied Materials, Karlsruhe Institute of Technology, Engelbert-Arnold-Straße 4, 76131 Karlsruhe, Germany ⁵ Fraunhofer IWM, MikroTribologie Centrum μ TC, Wöhlerstraße 11, 79108, Freiburg, Germany ⁶ Department of Materials, Imperial College London, London SW7 2AZ, UK ⁷ Fritz Haber Institute of the Max Planck Society, Faradayweg 4-6, D-14195, Berlin, Germany ⁸ Cluster of Excellence livMatS, Freiburg Center for Interactive Materials and Bioinspired Technologies, University of Freiburg, Georges-Köhler-Allee 105, 79110, Freiburg, Germany ¶ Corresponding author * These authors contributed equally.

DOI: [10.xxxxxx/draft](https://doi.org/10.xxxxxx/draft)

Software

- [Review](#)
- [Repository](#)
- [Archive](#)

Editor: [Open Journals](#)

Reviewers:

- [@openjournals](#)

Submitted: 01 January 1970

Published: unpublished

License

Authors of papers retain copyright and release the work under a Creative Commons Attribution 4.0 International License ([CC BY 4.0](#)).

Summary

Behaviour of materials is governed by physical phenomena that occur at an extreme range of length and time scales. Computational modelling requires multiscale approaches. Simulation techniques operating on the atomic scale serve as a foundation for such approaches, providing necessary parameters for upper scale models. The physical models employed for atomic simulations can vary from electronic structure calculations to empirical force fields. However, construction, manipulation and analysis of atomic systems are independent of the given physical model but dependent on the specific application. matsci.py implement such tools for applications in materials science, including fracture, plasticity, tribology and electrochemistry.

Statement of need

The Python package matsci.py contains a set of tools for researchers using atomic-scale models in materials science. In atomic-scale modelling, the primary numerical object is a discrete point in three-dimensional space that represents the position of an individual atom. Simulations are often dynamical, where configurations change over time and each atom carries a velocity. Complexity emerges from the interactions of many atoms, and numerical tools are required for generating initial atomic configurations and for analyzing output of such dynamical simulations, most commonly to connect local geometric arrangements of atoms to physical processes. An example, described in more detail below, is the detection of the tip of a crack that moves through a solid body.

We never see individual atoms at macroscopic scales. To understand the behaviour of everyday objects, atomic-scale information needs to be transferred to the continuum scale. This is the primary objective of multi-scale modelling. matsci.py focuses on atomic representations of materials, but implements tools for connecting to continuum description in mechanics and

transport theory. Each of the application domains described in the following therefore relies on the computation of continuum fields, that is realized through analytic or numerical solutions.

There is no other package that we are aware of, which fills the particular niche of the application domains in the next section. The package addresses the boundary between atomic-scale and continuum modelling in materials with particular emphasis on plasticity, fracture and tribology. The atomman atomistic manipulation toolkit (Hale, 2022) and the atomsk package (Hirel, 2015) have some overlapping objectives but are restricted to a narrower class of materials systems, principally point defects, stacking faults and dislocations. We target interoperability with the widely used Atomic Simulation Environment (ASE) (Larsen et al., 2017), which offers great flexibility and interoperability by providing a Python interface to tens of simulation codes implementing different physical models. While ASE's policy is to remain pure Python, we augment some of ASE's functionality with more efficient implementations in C, such as the computation of the neighbour list. Large scale molecular dynamics (MD) simulations are most efficiently performed with optimized codes such as LAMMPS (Thompson et al., 2022), with matsciPy's main contribution being to setup input structures and to post-process output trajectories.

The central class in ASE is the Atoms class, which is a container that stores atomic positions, velocities and other properties. Calculators describe relationships between atoms, and are used for example to compute energies and forces, and can be attached to Atoms objects. All other matsciPy functionality is implemented as functions acting on Atoms objects. This is comparable to the design of numpy (Harris et al., 2020) or scipy (Virtanen et al., 2020), that are collections of mathematical functions operating on core array container objects. In our experience, separating code into functions and containers lowers the barrier to entry for new users and eases testability of the underlying code base.

We point out that other generic multi-scale coupling packages exist. Examples of open-source codes are libmultiscale (Anciaux, 2007; Anciaux et al., 2018), MultiBench (Miller & Tadmor, 2009) and Green's function molecular dynamics (GFMD) (Campaña & Müser, 2006; Pastewka et al., 2012). These packages target two-way coupling between atomic-scale and continuum formulations, while matsciPy focuses on constructing atomic domains from continuum information and extracting continuum field from atomic structures. matsciPy has only limited capabilities for two-way coupling, which makes it significantly easier to use and reduces the barrier to engaging in multi-scale modelling of materials.

Application domains

Within materials science, the package has different application domains:

- **Elasticity.** Solids respond to small external loads through a reversible elastic response. The strength of the response is characterized by the elastic moduli. matsciPy.elasticity implements functions for computing elastic moduli from small deformation that consider potential symmetries of the underlying atomic system, in particular for crystals. matsciPy also implements analytic calculation of elastic moduli for some interatomic potentials, described in more detail below. The computation of elastic moduli is a basic prerequisite for multi-scale modelling of materials, as they are the most basic parameters of continuum material models. matsciPy was used to study finite-pressure elastic constants and structural stability in crystals (Grießer, Frérot, et al., 2023) and glasses (Grießer, Moras, et al., 2023).
- **Plasticity.** For large loads, solids can respond with irreversible deformation. One form of irreversibility is plasticity, that is carried by extended defects, the dislocations, in crystals. The module matsciPy.dislocation implements tools for studying structure and movement of dislocations. Construction and analysis of model atomic systems is implemented for compact and dissociated screw, as well as edge dislocations in cubic crystals. The implementation supports ideal straight as well as kinked dislocations. Some

of the dislocation functionality requires the atomman and/or OVITO packages as optional dependencies Stukowski (2009). The module was employed in a study of interaction of impurities with screw dislocations in tungsten (Grigorev et al., 2020, 2023).

- **Fracture mechanics.** Cracking is the process of generating new surface area by splitting the material apart. The module `matscopy.fracture_mechanics` provides functionality for calculating continuum linear elastic displacement fields near crack tips, including support for anisotropy in the elastic response (Sih et al., 1965). The module also implements generation of atomic structures that are deformed according to this near-tip field. This functionality has been used to quantify lattice trapping, which is the pinning of cracks due to the discreteness of the atomic lattice, and to compare simulations with experimental measurements of crack speeds in silicon (Kermode et al., 2015). There is also support for flexible boundary conditions in fracture simulations using the formalism proposed by Sinclair (Sinclair, 1975), where the finite atomistic domain is coupled to an infinite elastic continuum. Finally, we provide an extension of this approach to give a flexible boundary scheme that uses numerical continuation to obtain full solution paths for cracks (Buze & Kermode, 2021).
- **Tribology.** Tribology is the study of two interfaces sliding relative to one another, as encountered in frictional sliding or adhesion. Molecular dynamics simulations of representative volume elements of tribological interfaces are routinely used to gain insights into the atomistic mechanisms underlying friction and wear. The module `matscopy.pressurecoupling` provides tools to perform such simulations under a constant normal load and sliding velocity. It includes an implementation of the pressure coupling algorithm described by Pastewka et al. (2010). By dynamically adjusting the distance between the two sliding surfaces according to the local pressure, the algorithm ensures mechanical boundary conditions that account for the inertia of the bulk material which is not explicitly included in the simulation. This algorithm was used to study friction (Seidl et al., 2021a) and wear (G. Moras et al., 2011; Gianpietro Moras et al., 2018; Pastewka et al., 2011; Peguiron et al., 2016; Reichenbach et al., 2021).
- **Electrochemistry.** Electrochemistry describes the motion and spatial distribution of charged atoms and molecules (ions) within an external electric field. Classical treatment of charged systems leads to continuous field that describe mean charge distributions, while true atomic systems consist of discrete particles with fixed charges. The `matscopy.electrochemistry` module provides tools that statistically sample discrete coordinate sets from continuum fields and apply steric corrections (Martinez et al., 2009) to avoid overlap of finite size species. To generate continuum charge distributions, the package also contains a control-volume solver (Selberherr, 1984) for the one-dimensional Poisson–Nernst–Planck equations (Bazant et al., 2006), as well as an interface to the finite-element solver FEniCS (Logg et al., 2012). This was used to study friction in electrochemical environments (Hörmann et al., 2023; Seidl et al., 2021b).

All-purpose atomic analysis tools

As well as these domain-specific tools, `matscopy` contains general utility functionality which is widely applicable:

- **Neighbour list.** An efficient linear-scaling neighbour list implemented in C delivers orders-of-magnitude faster performance for large systems than the pure Python implementation in ASE (Larsen et al., 2017), see Figure 1. The neighbour list is stored in a data structure comparable to coordinate (C00) sparse matrix storage format (Saad, 1990), where two arrays contain the indices of the neighbouring atoms and further arrays store distance vectors, absolute distances, and other properties associated with an atomic pair. This allows compact code for evaluating properties that depend on pairs, such as pair-distribution function or interatomic potential energies and forces. Most of the

tools described in the following rely on this neighbour list format. The neighbour list is becoming widely used for post-processing and structural analysis of the trajectories resulting from molecular dynamics simulations, and even to accelerate next-generation message passing neural networks such as MACE (Batatia, Kovacs, et al., 2022; Batatia, Batzner, et al., 2022).




Figure 1: Neighbor list computation time comparison between ASE and Matscipy implementations.

- Atomic strain.** Continuum mechanics is formulated in terms of strains, which characterizes the fractional shape changes of small volumes. Strains are typically only well defined if averaged over sufficiently large volumes, and extracting strain fields from atomic-scale calculations is notoriously difficult. matscipy implements calculations of strain by observing changes in local atomic neighbourhoods across trajectories. It fits a per-atom displacement gradient that minimizes the error in displacement between two configurations as described by M. L. Falk & Langer (1998). The error resulting from this fit quantifies the non-affine contribution of the overall displacement and is known as D_{\min}^2 . We used this analysis to quantify local strain in the deformation of crystals (Gola et al., 2019, 2020) and glasses (Jana et al., 2019).
- Radial, spatial and angular correlation functions.** Topological order in atomic-scale systems is often characterized by statistical measures of the local atomic environment. The simplest one is the pair-distribution or radial-distribution function, that gives the probability $g_2(r)$ of finding an atom at distance r . For three atoms, we can define a probability of finding a specific angle, yielding the angular correlation functions. matscipy has utility function for computing these correlation functions to large distances, including the correlation of arbitrary additional per-atom properties such as per-atom strains.
- Ring analysis.** Topological order in network glasses can be characterized by statistics of shortest-path rings (Franzblau, 1991). matscipy implements calculations of these rings using a backtracking algorithm in C. We regularly use matscipy to characterize shortest-path rings in amorphous carbon (Jana et al., 2019; Pastewka et al., 2008).
- Topology building for non-reactive MD simulations.** Non-reactive force fields for MD simulations consist of non-bonded and bonded interaction terms (Jorgensen et al., 1996). The latter require an explicit specification of the interatomic bonding topology, i.e. which atoms are involved in bond, angle and dihedral interactions. The module matscipy.opls provides efficient tools to generate this topology for an atomic structure based on matscipy's neighbour list, and then assign the relevant force field parameters to each interaction term. Input and output routines for reading and writing the corresponding control files for LAMMPS (Thompson et al., 2022) are implemented in the module matscipy.io.opls. We used this functionality in various studies on tribology, wetting

and nanoscale rheology (K. Falk et al., 2020, 2022; Goedel et al., 2021; Mayrhofer et al., 2016; Reichenbach et al., 2020)

Interatomic potentials and other calculators

Besides generating and analysing atomic-scale configurations, matsci.py implements specific interatomic potentials (Müser et al., 2023). The goal here is not to provide the most efficient implementation of computing interatomic forces. We rather aim to provide simple implementations for testing new functional forms, or testing new features such as the computation of derivatives of second order.

- **Interatomic potentials.** The module `matsci.py.calculators` has implementations of classical pair-potentials, Coulomb interactions, the embedded-atom method (EAM) (Daw & Baskes, 1984) and other many-body potentials (e.g. Stillinger & Weber, 1985; Tersoff, 1989).
- **Second-order derivatives.** The thermodynamic and elastic properties of solid materials are closely connected to the Hessian of the overall system, that contains the second derivatives of the total energy with respect to position and macroscopic strains. `matsci.py` implements analytic second-order potential derivatives for pair-potentials (Lennard-Jones, 1931), EAM potentials (Daw & Baskes, 1984), bond-order potentials (Brenner, 1990; Kumagai et al., 2007; Tersoff, 1989), cluster potentials (Stillinger & Weber, 1985) and electrostatic interaction (Van Beest et al., 1990). This is achieved through a generic mathematical formulation of the manybody total energy (Griesser2023b?) in `matsci.py.calculators.manybody`. The module `matsci.py.numerical` additionally provides routines for the numerical (finite-differences) evaluation of these properties. These analytic second-order derivatives allow a fast and accurate computation of the aforementioned properties in crystals, polymers and amorphous solids, even for unstable configurations where numerical methods are not applicable.
- **Quantum mechanics/molecular mechanics.** The module `matsci.py.calculators.mcfm` implements a generalised force-mixing potential (Bernstein et al., 2009) with support for multiple concurrent QM clusters, named MultiClusterForceMixing (MCFM). It has been applied to model failure of graphene-nanotube composites (Gołębowski et al., 2018, 2020).
- **Committee models.** The module `matsci.py.calculators.committee` provides support for committees of interatomic potentials with the same functional form but differing parameters, in order to allow the effect of the uncertainty in parameters on model predictions to be estimated. This is typically used with machine learning interatomic potentials (MLIPs). The implementation follows the approach of (Musil et al., 2019) where the ensemble of models is generated by training models on different subsets of a common overall training database.

Acknowledgements

We thank Arnaud Allera, Manuel Aldegunde, Kristof Bal, James Brixey, Alexander Held, Jan Jansen, Till Junge, Henry Lambert, Punit Patel and Zhilin Zheng for contributions and bug fixes. `matsci.py` was partially funded by the Deutsche Forschungsgemeinschaft (projects 258153560, 390951807 and 461911253), the European Research Council (ERC StG 757343), the Engineering and Physical Sciences Research Council (grants EP/P002188/1, EP/R012474/1 and EP/R043612/1) and the Leverhulme Trust under grant RPG-2017-191.

References

- Anciaux, G. (2007). *Simulation multi-échelles des solides par une approche couplée dynamique moléculaire/éléments finis. De la modélisation à la simulation haute performance.*
- Anciaux, G., Junge, T., Hodapp, M., Cho, J., Molinari, J.-F., & Curtin, W. A. (2018). The coupled Atomistic/Discrete-Dislocation method in 3d part i: Concept and algorithms. *J. Mech. Phys. Solids*, 118, 152–171.
- Batatia, I., Batzner, S., Kovács, D. P., Musaelian, A., Simm, G. N. C., Drautz, R., Ortner, C., Kozinsky, B., & Csányi, G. (2022). *The design space of $e(3)$ -equivariant atom-centered interatomic potentials* (No. arXiv:2205.06643). <https://doi.org/10.48550/arXiv.2205.06643>
- Batatia, I., Kovacs, D. P., Simm, G. N. C., Ortner, C., & Csanyi, G. (2022). MACE: Higher order equivariant message passing neural networks for fast and accurate force fields. In A. H. Oh, A. Agarwal, D. Belgrave, & K. Cho (Eds.), *Advances in neural information processing systems*. <https://openreview.net/forum?id=YPpSngE-ZU>
- Bazant, M. Z., Chu, K. T., & Bayly, B. J. (2006). Current-Voltage Relations for Electrochemical Thin Films. *SIAM Journal on Applied Mathematics*. <https://doi.org/10.1137/040609938>
- Bernstein, N., Kermode, J. R., & Csányi, G. (2009). Hybrid atomistic simulation methods for materials systems. *Rep. Prog. Phys.*, 72(2), 026501. <https://doi.org/10.1088/0034-4885/72/2/026501>
- Brenner, D. W. (1990). Empirical potential for hydrocarbons for use in simulating chemical vapor deposition of diamond films. *Phys. Rev. B*, 42(15), 9458–9471.
- Buze, M., & Kermode, J. R. (2021). Numerical-continuation-enhanced flexible boundary condition scheme applied to mode-I and mode-III fracture. *Phys. Rev. E*, 103(3), 033002. <https://doi.org/10.1103/PhysRevE.103.033002>
- Campaña, C., & Müser, M. H. (2006). Practical green's function approach to the simulation of elastic semi-infinite solids. *Phys. Rev. B*, 74(7), 075420.
- Daw, M. S., & Baskes, M. I. (1984). Embedded-atom method: Derivation and application to impurities, surfaces, and other defects in metals. *Physical Review B*, 29, 6443–6453. <https://doi.org/10.1103/PhysRevB.29.6443>
- Falk, K., Reichenbach, T., Gkagkas, K., Moseler, M., & Moras, G. (2022). Relating dry friction to interdigitation of surface passivation species: A molecular dynamics study on amorphous carbon. *Materials*, 15(9), 3247. <https://doi.org/10.3390/ma15093247>
- Falk, K., Savio, D., & Moseler, M. (2020). Nonempirical free volume viscosity model for alkane lubricants under severe pressures. *Phys. Rev. Lett.*, 124, 105501. <https://doi.org/10.1103/PhysRevLett.124.105501>
- Falk, M. L., & Langer, J. S. (1998). Dynamics of viscoplastic deformation in amorphous solids. *Phys. Rev. E*, 57(6), 7192–7205.
- Franzblau, D. S. (1991). Computation of ring statistics for network models of solids. *Phys. Rev. B*, 44(10), 4925–4930.
- Goedel, S. von, Reichenbach, T., König, F., Mayrhofer, L., Moras, G., Jacobs, G., & Moseler, M. (2021). A combined experimental and atomistic investigation of PTFE double transfer film formation and lubrication in rolling point contacts. *Tribology Letters*, 69, 136. <https://doi.org/10.1007/s11249-021-01508-9>
- Gola, A., Schwaiger, R., Gumbsch, P., & Pastewka, L. (2020). Pattern formation during deformation of metallic nanolaminates. *Phys. Rev. Mater.*, 4(1), 013603.

- 266 Gola, A., Zhang, G.-P., Pastewka, L., & Schwaiger, R. (2019). Surface flaws control strain
267 localization in the deformation of Cu|Au nanolaminate pillars. *MRS Communications*, 9(3),
268 1067–1071.
- 269 Gołębowski, J. R., Kermode, J. R., Haynes, P. D., & Mostofi, A. A. (2020). Atomistic
270 QM/MM simulations of the strength of covalent interfaces in carbon nanotube-polymer
271 composites. *Phys. Chem. Chem. Phys.* <https://doi.org/10.1039/d0cp01841d>
- 272 Gołębowski, J. R., Kermode, J. R., Mostofi, A. A., & Haynes, P. D. (2018). Multiscale
273 simulations of critical interfacial failure in carbon nanotube-polymer composites. *J. Chem.*
274 *Phys.*, 149(22), 224102. <https://doi.org/10.1063/1.5035508>
- 275 Griebner, J., Frérot, L., Oldenstaedt, J. A., Müser, M. H., & Pastewka, L. (2023). *Analytic*
276 *elastic constants in molecular calculations: Finite strain, non-affine displacements, and*
277 *many-body interatomic potentials.* <https://arxiv.org/abs/2302.08754>
- 278 Griebner, J., Moras, G., & Pastewka, L. (2023). Yielding under compression and the polyamorphic
279 transition in silicon. *Phys. Rev. Mater.*, 7(5), 055601.
- 280 Grigorev, P., Goryaeva, A. M., Marinica, M.-C., Kermode, J. R., & Swinburne, T. D. (2023).
281 Calculation of dislocation binding to helium-vacancy defects in tungsten using hybrid ab
282 initio-machine learning methods. *Acta Materialia*, 247, 118734. <https://doi.org/https://doi.org/10.1016/j.actamat.2023.118734>
- 283
284 Grigorev, P., Swinburne, T. D., & Kermode, J. R. (2020). Hybrid quantum/classical study
285 of hydrogen-decorated screw dislocations in tungsten: Ultrafast pipe diffusion, core
286 reconstruction, and effects on glide mechanism. *Phys. Rev. Materials*, 4, 023601.
287 <https://doi.org/10.1103/PhysRevMaterials.4.023601>
- 288 Hale, L. (2022). <https://github.com/usnistgov/atomman>
- 289 Harris, C. R., Millman, K. J., Walt, S. J. van der, Gommers, R., Virtanen, P., Cournapeau, D.,
290 Wieser, E., Taylor, J., Berg, S., Smith, N. J., Kern, R., Picus, M., Hoyer, S., Kerkwijk, M.
291 H. van, Brett, M., Haldane, A., Río, J. F. del, Wiebe, M., Peterson, P., ... Oliphant, T. E.
292 (2020). Array programming with NumPy. *Nature*, 585(7825), 357–362.
- 293 Hirel, P. (2015). AtomsK: A tool for manipulating and converting atomic data files. *Comput.*
294 *Phys. Commun.*, 197, 212–219.
- 295 Hörmann, J. L., Liu, C., Meng, Y., & Pastewka, L. (2023). Molecular simulations of sliding
296 on SDS surfactant films. *J. Chem. Phys.*, 158(24).
- 297 Jana, R., Savio, D., Deringer, V., & Pastewka, L. (2019). Structural and elastic properties
298 of amorphous carbon from simulated quenching at low rates. *Modell. Simul. Mater. Sci.*
299 *Eng.*, 27, 085009.
- 300 Jorgensen, W. L., Maxwell, D. S., & Tirado-Rives, J. (1996). Development and testing of the
301 OPLS all-atom force field on conformational energetics and properties of organic liquids.
302 *Journal of the American Chemical Society*, 118(45), 11225–11236. <https://doi.org/10.1021/ja9621760>
- 303
304 Kermode, J. R., Gleizer, A., Kovel, G., Pastewka, L., Csányi, G., Sherman, D., & De Vita, A.
305 (2015). Low speed crack propagation via kink formation and advance on the silicon (110)
306 cleavage plane. *Phys. Rev. Lett.*, 115(13), 135501. <https://doi.org/10.1103/PhysRevLett.115.135501>
- 307
308 Kumagai, T., Izumi, S., Hara, S., & Sakai, S. (2007). Development of bond-order potentials
309 that can reproduce the elastic constants and melting point of silicon for classical molecular
310 dynamics simulation. *Computational Materials Science*, 39(2), 457–464.
- 311 Larsen, A. H., Mortensen, J. J., Blomqvist, J., Castelli, I. E., Christensen, R., Duřak, M.,
312 Friis, J., Groves, M. N., Hammer, B., Hargus, C., Hermes, E. D., Jennings, P. C.,

- Jensen, P. B., Kermode, J., Kitchin, J. R., Kolsbjerg, E. L., Kubal, J., Kaasbjerg, K., Lysgaard, S., ... Jacobsen, K. W. (2017). The atomic simulation environment—a python library for working with atoms. *Journal of Physics: Condensed Matter*, 29(27), 273002. <https://doi.org/10.1088/1361-648x/aa680e>
- Lennard-Jones, J. E. (1931). Cohesion. *Proc. Phys. Soc.*, 43(5), 461–482.
- Logg, A., Mardal, K.-A., Wells, G. N., & others. (2012). *Automated solution of differential equations by the finite element method* (A. Logg, K.-A. Mardal, & G. N. Wells, Eds.). Springer. <https://doi.org/10.1007/978-3-642-23099-8>
- Martinez, L., Andrade, R., Birgin, E. G., & Martínez, J. M. (2009). PACKMOL: A package for building initial configurations for molecular dynamics simulations. *Journal of Computational Chemistry*, 30(13), 2157–2164. <https://doi.org/10.1002/jcc.12345>
- Mayrhofer, L., Moras, G., Mulakaluri, N., Rajagopalan, S., Stevens, P. A., & Moseler, M. (2016). Fluorine-terminated diamond surfaces as dense dipole lattices: The electrostatic origin of polar hydrophobicity. *Journal of the American Chemical Society*, 138, 4018–4028. <https://doi.org/10.1021/jacs.5b04073>
- Miller, R. E., & Tadmor, E. B. (2009). A unified framework and performance benchmark of fourteen multiscale atomistic/continuum coupling methods. *Modell. Simul. Mater. Sci. Eng.*, 17(5), 053001.
- Moras, Gianpietro, Klemenz, A., Reichenbach, T., Gola, A., Uetsuka, H., Moseler, M., & Pastewka, L. (2018). Shear melting of silicon and diamond and the disappearance of the polyamorphic transition under shear. *Phys. Rev. Materials*, 2(8), 083601.
- Moras, G., Pastewka, L., Gumbsch, P., & Moseler, M. (2011). Formation and oxidation of linear carbon chains and their role in the wear of carbon materials. *Tribol. Lett.*
- Müser, M. H., Sukhomlinov, S. V., & Pastewka, L. (2023). Interatomic potentials: Achievements and challenges. *Advances in Physics: X*, 8(1), 2093129.
- Musil, F., Willatt, M. J., Langovoy, M. A., & Ceriotti, M. (2019). Fast and accurate uncertainty estimation in chemical machine learning. *J. Chem. Theory Comput.*, 15(2), 906–915. <https://doi.org/10.1021/acs.jctc.8b00959>
- Pastewka, L., Moser, S., Gumbsch, P., & Moseler, M. (2011). Anisotropic mechanical amorphization drives wear in diamond. *Nat. Mater.*, 10(1), 34–38.
- Pastewka, L., Moser, S., & Moseler, M. (2010). Atomistic insights into the running-in, lubrication, and failure of hydrogenated diamond-like carbon coatings. *Tribology Letters*, 39(1), 49–61. <https://doi.org/10.1007/s11249-009-9566-8>
- Pastewka, L., Pou, P., Pérez, R., Gumbsch, P., & Moseler, M. (2008). Describing bond-breaking processes by reactive potentials: Importance of an environment-dependent interaction range. *Phys. Rev. B Condens. Matter*, 78(16), 161402(R).
- Pastewka, L., Sharp, T. A., & Robbins, M. O. (2012). Seamless elastic boundaries for atomistic calculations. *Phys. Rev. B*, 86, 075459.
- Peguiron, A., Moras, G., Walter, M., Uetsuka, H., Pastewka, L., & Moseler, M. (2016). Activation and mechanochemical breaking of C–C bonds initiate wear of diamond (110) surfaces in contact with silica. *Carbon N. Y.*, 98, 474–483.
- Reichenbach, T., Mayrhofer, L., Kuwahara, T., Moseler, M., & Moras, G. (2020). Steric effects control dry friction of h- and f-terminated carbon surfaces. *ACS Applied Materials & Interfaces*, 12, 8805–8816. <https://doi.org/10.1021/acsami.9b18019>
- Reichenbach, T., Moras, G., Pastewka, L., & Moseler, M. (2021). Solid-Phase silicon homoepitaxy via Shear-Induced amorphization and recrystallization. *Phys. Rev. Lett.*, 127(12), 126101.

- 360 Saad, Y. (1990). *SPARSKIT: A basic tool kit for sparse matrix computations* (NAS
361 1.26:185876). ntrs.nasa.gov.
- 362 Seidl, C., Hörmann, J. L., & Pastewka, L. (2021b). Molecular Simulations of Electrotunable
363 Lubrication: Viscosity and Wall Slip in Aqueous Electrolytes. *Tribology Letters*, 69(1), 22.
364 <https://doi.org/10.1007/s11249-020-01395-6>
- 365 Seidl, C., Hörmann, J. L., & Pastewka, L. (2021a). Molecular simulations of electrotunable
366 lubrication: Viscosity and wall slip in aqueous electrolytes. *Tribol. Lett.*, 69(1), 22.
- 367 Selberherr, S. (1984). *Analysis and simulation of semiconductor devices*. Springer Science &
368 Business Media.
- 369 Sih, G. C., Paris, P. C., & Irwin, G. R. (1965). On cracks in rectilinearly anisotropic bodies.
370 *Int. J. Fract. Mech.*, 1(3), 189–203. <https://doi.org/10.1007/BF00186854>
- 371 Sinclair, J. E. (1975). The influence of the interatomic force law and of kinks on the propagation
372 of brittle cracks. *Philos. Mag.*, 31, 647–671.
- 373 Stillinger, F. H., & Weber, T. A. (1985). Computer simulation of local order in condensed
374 phases of silicon. *Phys. Rev. B*, 31(8), 5262.
- 375 Stukowski, A. (2009). Visualization and analysis of atomistic simulation data with OVITO—the
376 open visualization tool. *Modell. Simul. Mater. Sci. Eng.*, 18(1), 015012. <https://doi.org/10.1088/0965-0393/18/1/015012>
- 377
- 378 Tersoff, J. (1989). Modeling solid-state chemistry: Interatomic potentials for multicomponent
379 systems. *Phys. Rev. B*, 39(8), 5566.
- 380 Thompson, A. P., Aktulga, H. M., Berger, R., Bolintineanu, D. S., Brown, W. M., Crozier, P.
381 S., in 't Veld, P. J., Kohlmeyer, A., Moore, S. G., Nguyen, T. D., Shan, R., Stevens, M. J.,
382 Tranchida, J., Trott, C., & Plimpton, S. J. (2022). LAMMPS - a flexible simulation tool
383 for particle-based materials modeling at the atomic, meso, and continuum scale. *Computer
384 Physics Communications*, 271, 108171. <https://doi.org/10.1016/j.cpc.2021.108171>
- 385 Van Beest, B., Kramer, G. J., & Van Santen, R. (1990). Force fields for silicas and alu-
386 minophosphates based on ab initio calculations. *Phys. Rev. Lett.*, 64(16), 1955.
- 387 Virtanen, P., Gommers, R., Oliphant, T. E., Haberland, M., Reddy, T., Cournapeau, D.,
388 Burovski, E., Peterson, P., Weckesser, W., Bright, J., Walt, S. J. van der, Brett, M.,
389 Wilson, J., Millman, K. J., Mayorov, N., Nelson, A. R. J., Jones, E., Kern, R., Larson, E.,
390 ... Vázquez-Baeza, Y. (2020). SciPy 1.0: Fundamental algorithms for scientific computing
391 in python. *Nat. Methods*, 17(3), 261–272.