

T, °C	3BeO + 2NF _{3(g)} = 3BeF ₂ + N _{2(g)} + 1.5O _{2(g)}			BeO + 2HF _(g) = BeF ₂ + H ₂ O _(g)		
	ΔH,	ΔS	ΔG	ΔH	ΔS	ΔG
	kJ/mol F	J/K/mol F	kJ/mol F	kJ/mol F	J/K/mol F	kJ/mol F
100	-164.4	17.5	-171.0	-56.3	-59.3	-34.23
200	-163.7	19.2	-172.8	-56.0	-58.8	-28.3
300	-163.3	20.0	-174.8	-55.7	-57.9	-22.5
400	-163.2	20.2	-176.8	-55.5	-57.6	-16.7
500	-163.1	20.3	-178.8	-55.3	-57.3	-11.0
600	-160.4	23.5	-181.0	-52.4	-53.8	-5.4
700	-160.0	24.0	-183.4	-51.6	-53.0	-0.1
800	-159.4	24.6	-185.8	-50.7	-52.1	5.190
900	-158.7	25.2	-188.3	-49.7	-51.2	10.353
1000	-158.0	25.8	-190.8	-48.5	-50.2	15.423