

T, °C	3Be(OH) ₂ +2NF _{3(g)} =N _{2(g)} +3BeF ₂ +3H ₂ O _(g) +1.5O _{2(g)}			Be(OH) ₂ +2HF=BeF ₂ +2H ₂ O _(g)		
	ΔH	ΔS	ΔG	ΔH	ΔS	ΔG
	kJ/mol F	J/K/mol F	kJ/mol F	kJ/mol F	J/K/mol F	kJ/mol F
100	-139.0	91.7	-173.2	-30.9	14.9	-36.4
200	-139.1	91.5	-182.4	-31.3	13.8	-37.9
300	-139.6	90.4	-191.5	-32.0	12.6	-39.2
400	-140.6	88.9	-200.4	-32.9	11.2	-40.4
500	-141.6	87.6	-209.3	-33.7	10.0	-41.4
600	-140.0	89.4	-218.1	-32.0	12.1	-42.5
700	-140.7	88.7	-227.0	-32.3	11.7	-43.7
800	-141.2	88.2	-235.9	-32.6	11.5	-44.9
900	-141.7	87.8	-244.7	-32.6	11.4	-46.0
1000	-142.0	87.5	-253.4	-32.6	11.4	-47.2