

T, °C	3Li ₂ O + 2NF _{3(g)} = 6LiF + N _{2(g)} + 1.5O _{2(g)}			Li ₂ O + 2HF _(g) = 2LiF + H ₂ O _(g)		
	ΔH	ΔS	ΔG	ΔH	ΔS	ΔG
	kJ/mol F	J/K/mol F	kJ/mol F	kJ/mol F	J/K/mol F	kJ/mol F
100	-273.5	14.9	-279.1	-165.4	-62.0	-142.3
200	-272.9	16.3	-280.6	-165.2	-61.3	-136.1
300	-272.5	17.1	-282.3	-164.8	-60.7	-130.0
400	-272.1	17.8	-284.1	-164.4	-60.0	-124.0
500	-271.8	18.2	-285.9	-163.9	-59.4	-118.0
600	-271.4	18.6	-287.7	-163.4	-58.7	-112.1
700	-271.1	18.9	-289.6	-162.8	-58.1	-106.3
800	-270.9	19.2	-291.5	-162.2	-57.5	-100.5
900	-243.5	43.6	-294.7	-134.5	-32.8	-96.0
1000	-243.4	43.7	-299.0	-134.0	-32.4	-92.8