

T, °C	SiC + 2.667NF _{3(g)} = SiF _{4(g)} + CF _{4(g)} + 1.333N _{2(g)}			SiC + 4HF _(g) = SiF _{4(g)} + CH _{4(g)}		
	ΔH	ΔS	ΔG	ΔH	ΔS	ΔG
	kJ/mol F	J/K/mol F	kJ/mol F	kJ/mol F	J/K/mol F	kJ/mol F
100	-265.7	11.0	-269.8	-131.9	-62.4	-108.6
200	-265.8	10.8	-270.9	-132.5	-63.8	-102.3
300	-265.9	10.5	-271.9	-133.0	-64.7	-95.9
400	-266.1	10.2	-273.0	-133.2	-65.1	-89.4
500	-266.3	9.9	-274.0	-133.3	-65.2	-82.9
600	-266.5	9.7	-275.0	-133.3	-65.2	-76.4
700	-266.7	9.5	-275.9	-133.1	-65.0	-69.9
800	-266.9	9.2	-276.8	-132.9	-64.8	-63.4
900	-267.2	9.0	-277.8	-132.7	-64.6	-56.9
1000	-267.4	8.8	-278.7	-132.4	-64.3	-50.4